

## ROOFING

### 16 Double Coverage Cement



**\*Read Safety Data Sheet before using this product.\***

**DESCRIPTION:** 16 Double Coverage Cement is a bituminous based adhesive sealant designed for the application and repair of rolled roofing bituminous single-ply membranes. When properly utilized, this product adheres the membrane and seals the laps to prevent water intrusion.

**USES:** 16 Double Coverage Cement is use as a lap cement, rolled roofing adhesive sealant and blind nailing cement for bituminous single-ply membranes.

**SURFACE PREPARATIONS:** 16 Double Coverage Cement is applied by brush, broom or squeegee. The area to be coated must be free and clean of all debris, dust and dirt. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

**APPLICATION:** Following the bituminous single-ply membrane manufacturer's application guidelines, apply 16 Double Coverage Cement with a roofing brush, broom or squeegee at the rate of 2 to 3 gallons per 100 sq. ft.

**COVERAGE RATE:** Apply at the rate of 2 to 3 gallons per 100 sq. ft.

**CAUTION:** Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. Keep out of reach of children. Store in a heated room and keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying. Exterior use only.

**PACKAGING:** Available in 5-gallon pails and 1-gallon cans.

If further information is needed, contact KARNAK Technical services at 800-526-4236.

#### PHYSICAL PROPERTIES & SPECIFICATIONS

Weight per Gallon: 8.28 lbs.

Solids by Weight: 74% Nominal

Solids by Volume: 68% Nominal

Color: Black

Application Temp.: 40°F to 120°F

Service Temp  
(Cured Film): 15°F to 180°F

VOC Content: 250 g/L MAX

ASTM D3019 Type III

