

Sealants, Caulking, Flooring

237-2% Neo-Asphalt (Brush Grade)



Read Safety Data Sheet before using this product.

DESCRIPTION: 237-2% Neo-Asphalt is a cold applied, rubberized asphalt cement, designed especially for use as an adhesive for paving blocks and pressed asphalt bricks. Eliminates the need for a hot kettle.

USES: 237-2% Neo-Asphalt is expressly designed for adhering concrete, brick and pressed asphalt brick pavers to horizontal surfaces.

SURFACE PREPARATIONS: All surfaces should be clean, free from oil, grease or other foreign matter. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

APPLICATION: 237-2% Neo-Asphalt can be applied to either concrete or macadam (blacktop) using a brush or 1/16" serrated squeegee. For best results, 237 2% Neo-Asphalt should be allowed to have a minimum of 2-3 hours open air time or until material becomes tacky and just skins over, prior to embedding the paving bricks. Recommended application temperature 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

COVERAGE RATE: Apply at the rate of 1.5 - 2 gallons per 100 sq. ft. (approximately 1/32" thick maximum). Do not exceed coverage rate.

NOTE: 237-2% Neo-Asphalt should be thoroughly **mechanically mixed** prior to application. Macadam (blacktop) surfaces should be cured prior to applying 237-2% Neo-Asphalt.

CAUTION: Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. Keep out of reach of children. Store in a heated room and keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner. For exterior use only.

PACKAGING: Available in 5-gallon pails and 55-gallon drums.

If further information is needed, contact KARNAK Technical services at 800-526-4236.

PHYSICAL PROPERTIES & SPECIFICATIONS

| | |
|----------------------------------|---------------|
| Weight per Gallon: | 8.2 lbs |
| Solids by Weight: | 71% Nominal |
| Solids by Volume: | 65% Nominal |
| Color: | Black |
| Softening Point of rubber blend: | 150°F |
| % Inorganic Material: | 6.5 |
| % Long Fiber: | 10 |
| % Neoprene: | 2, minimum |
| Application Temp.: | 40°F to 120°F |
| VOC Content: | 250 g/L MAX |