

# CAULKS & SEALANTS

## 44 Klear Seal Caulk



\*Read Safety Data Sheet before using this product.\*

**DESCRIPTION:** 44 Klear Seal Caulk is a multi-purpose, terpolymer acrylic caulk that's specially formulated to provide a clear water-resistant seal. It's manufactured to a smooth, creamy consistency for ease of application by standard caulking gun. 44 Klear Seal Caulk provides outstanding adhesion and flexibility for long service life.

**USES:** 44 Klear Seal Caulk can be used for exterior and interior applications for creating a water resistant seal on wood, drywall, plaster, brick, concrete, masonry, tile and metal surfaces above grade. Its sag resistant properties and clear color make it an excellent sealant for cracks around windows, doors, trim, molding, window air conditioners, metal chimney flashings, siding and general-purpose use for vertical applications. Do not use in areas subject to water ponding.

### FEATURES, BENEFITS & ADVANTAGES:

- Dries to a Clear, Translucent Color
- Low Odor, for Exterior and Interior Applications
- Paintable
- Outstanding Flexibility
- Excellent Adhesion
- Quick-Drying
- Meets ASTM C834
- VOC Compliant, CARB and SCAQMD Compliant

**SURFACE PREPARATIONS:** All surfaces to be caulked must be dry, clean and free from mildew, loose paint or coatings, oil, grease, rust, dirt, and other foreign matter. Recommended application temperature is 40°F to 120°F.

**APPLICATION:** Cut spout at an angle to desired bead size and load into a standard caulking gun. 44 Klear Seal Caulk should be applied with even pressure directly over the crack or joint. Before the caulk begins to skin over, tool with even pressure directly over the crack or joint. Before the caulk begins to skin over, tool with even pressure to create a positive seal with the substrate. Excess caulk should be wiped away with a damp cloth before skinning over. An application rate of a 1/4" x 1/4" bead of caulk will yield approximately 25 lin. ft. per 10.1 oz. caulking cartridge. Coverage rate may vary depending on desired thickness and surface to be caulked. Apply when temperatures of the caulk, substrate and ambient air are 40°F and rising. 44 Klear Seal Caulk dries quickly to the touch in about 1 hour and may be painted over after 4-6 hours dry time (depending on temperature and humidity).

**COVERAGE RATE:** A 1/4" x 1/4" head of caulk will yield approximately 25 lin. ft. per 10.1 oz. caulking cartridge. Coverage rate may vary depending on desired thickness and surface being caulked.

**CAUTION:** Do not apply to wet surfaces or when rain or freezing temperatures are expected within 24-36 hours. Cold temperatures and high humidity will retard curing. Protect unused product from freezing. Coating must be cured before exposure to water. Store in a heated room between 50°F and 100°F. Keep container away from heat. Avoid prolonged contact with skin. Wash exposed areas with soap and water. Avoid breathing vapors in confined areas. If product gets into eyes, immediately flush with large amounts of water while holding the eyelids open then seek medical attention. Do not take internally. If swallowed, **do not** induce vomiting. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. Dispose of in an environmentally safe manner.

**PACKAGING:** Available in 10.1 oz. cartridges

If further information is needed, contact KARNAK Technical services at 800-526-4236.

### PHYSICAL PROPERTIES & SPECIFICATIONS

Weight per Gallon:	13.0 lbs
Solids by Weight:	80% Nominal
Solids by Volume:	71% Nominal
Color:	Milky White (Uncured) Clean (Cured)
Elongation:	365%
Tensile Strength:	175 psi
Shore Hardness (A):	48
Application Temp.:	40°F to 120°F
Cure Time:	24-36 hrs. at 77°F and 50% Relative Humidity
Service Temp (Cured Film):	0°F to 200°F
VOC Content:	g/L MAX
ASTM C834	