



Performance+[®]

Equipment Liner M with ECOSE[®] Technology

Product-Data-Sheet

Description

Performance+[®] Equipment Liner M with ECOSE Technology is a flexible fiberglass blanket with a black mat facing adhered to the air stream side. The product provides a smooth, tough air stream surface which resists damage during installation and operation.

Application

- Noise reduction and thermal insulation for equipment (HVAC) where air erosion resistance is required.
- Designed for systems operating at temperatures up to 250° F (121° C) and velocities up to 6,000 ft./min. (1,829 m/min.)

Indoor Air Quality

- **Asthma & Allergy Friendly[®]** Certified
- Verified Healthier Air[™]
- UL Environment
 - GREENGUARD Certified
 - GREENGUARD Gold Certified
 - Validated to be Formaldehyde-Free
- Does not contain polybrominated diphenyl ethers (PBDE) such as: Penta – BDE, Octa – BDE or Deca – BDE
- EUCEB Certified

Certifications



The Asthma & Allergy Friendly[®] Certification Mark is a Registered Certification Mark of the Asthma Allergy Foundation of America (AAFA) and Allergy Standards Ltd (ASL). Verified Healthier Air[™] is a trademark of Airmid Healthgroup. USGBC[®] and the related logo are trademarks owned by the U.S. Green Building Council[®] and are used with permission.

Contractor: _____

Job: _____

Date: _____

Technical Data

Property (Unit)	Test	Performance
Corrosiveness	ASTM C665	Does not accelerate corrosion of steel
Corrosion	ASTM C1617	Pass
Air Velocity	ASTM C1071	Maximum 6,000 ft./min. (1,829 m/min.)
Water Vapor Sorption (by weight)	ASTM C1104	Less than 3%
Maximum Service Temperature	ASTM C411	250° F (121° C)
Mold Growth	ASTM C1338, ASTM G21	Pass. The airstream surface mat facing is treated with an EPA-registered anti-microbial agent to aid in the prevention of fungal and bacterial growth
Surface Burning Characteristics (flame spread/smoke developed)	ASTM E84, NFPA 90A and 90B UL 723, CAN S102	UL Classified FHC 25/50

Sound Absorption Coefficients | ASTM C423, Type A Mounting

Octave Band Center Frequency (cycles/sec)								
Type		125	250	500	1000	2000	4000	NRC
1.5 PCF (24 kg/m³)	1" (25 mm)	0.18	0.28	0.73	0.85	0.91	0.90	0.70
	1½" (38 mm)	0.23	0.50	0.87	0.92	0.93	0.93	0.80
	2" (51 mm)	0.37	0.76	1.02	1.00	0.98	0.92	0.95
2.0 PCF (32 kg/m³)	½" (13 mm)	0.10	0.17	0.43	0.59	0.73	0.75	0.50
	1" (25 mm)	0.25	0.35	0.69	0.89	0.96	1.01	0.70
	1½" (38 mm)	0.27	0.55	0.87	0.99	1.00	0.98	0.85

Forms Available

Density	Thickness	Width	Length	Current Minimum (ft²)
1.5 PCF (24 kg/m³)	1" (25 mm)	34"-36" (864 mm-915 mm)	100' (30.48 m)	38,000
	1½" (38 mm)		50' (15.24 m)	27,000
	2" (51 mm)		50' (15.24 m)	20,000
2.0 PCF (32 kg/m³)	½" (13 mm)	46"-48" (1,168 mm-1,219 mm)	100' (30.48 m)	54,000
	1" (25 mm)		50' (15.24 m)	31,000
	1½" (38 mm)		50' (15.24 m)	20,000

Thermal Resistance | ASTM C518, 75° F Mean Temperature

Density	Thickness	R-Value @ 75° F (24° C)
1.5 PCF (24 kg/m ³)	1" (25 mm)	R-4.2
	1½" (38 mm)	R-6.0
	2" (51 mm)	R-8.0
2.0 PCF (32 kg/m ³)	½" (13 mm)	R-2.1
	1" (25 mm)	R-4.2
	1½" (38 mm)	R-6.3

FIBERGLASS AND MOLD

Fiberglass insulation will not sustain mold growth. However, mold can grow on almost any material when it becomes wet and contaminated. Carefully inspect any insulation that has been exposed to water. If it shows any sign of mold it must be discarded. If the material is wet but shows no evidence of mold, it should be dried rapidly and thoroughly. If it shows signs of facing degradation from wetting, it should be replaced. Air handling insulation used in the air stream must be discarded if exposed to water.

Check with your Knauf Insulation Territory Manager to ensure information is current.

The chemical and physical properties of this product represent average values determined in accordance with accepted test methods. The data is subject to normal manufacturing variations. The data is supplied as a technical service and is subject to change without notice. References to numerical flame spread ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

Consult with or follow local building and energy codes to determine appropriate R-values and need for and placement of a vapor retarder.

Knauf Insulation, Inc.

One Knauf Drive
Shelbyville, IN 46176

Technical Support

Phone: (317) 398-4434 Option 6

info.us@knaufinsulation.com

www.knaufnorthamerica.com

This product is covered by one or more U.S. and/or other patents.

See patent www.knaufnorthamerica.com/patents

© 2025 Knauf Insulation, Inc.

The trademarks KNAUF, PERFORMANCE+, ECOSE, the design elements and colors, and related marks are trademarks of Knauf Insulation, Inc. or its affiliates.