



# STURDY-DEK™

## ASPHALTIC COVER BOARD

### DESCRIPTION

**STURDY-DEK** is a multi-ply, semi-rigid asphaltic panel composed of a mineral-fortified asphaltic core, formed between two asphalt-saturated fiberglass liners and a plastic separator sheet.

**STURDY-DEK** is designed to be used as a base material in flat or low-slope roofing. It may be installed over wood, concrete, rigid insulation or as a recover sheet over an existing roof surface which is to be recovered.

### USES

**STURDY-DEK** is used as a separator board, a roof recovery board, a levelling board in re-roofing applications under modified bitumen applications.

### APPLICATION

The surfaces to be covered with **STURDY-DEK** must be dry and debris-free. Ensure underlying substrate and decking is free from trapped moisture. All blisters, ridges, and other surface irregularities must be repaired so that the surface is smooth. Remove loose gravel from existing roofs. Apply only as much **STURDY-DEK** as can be covered by roof membrane the same day.

As the sheets are taken from the pallet, remove the polyethylene separator sheet. Fit panels together and secure via hot asphalt, cold adhesive, low rise foam adhesive, or mechanical attachment. Fastening density and patterns may vary based upon specific membrane manufacturer assemblies. Refer to membrane manufacturer fastening requirements.

Cut sheets with a roofer's knife for fitting as required. Elastomeric roofing membranes, modified bitumen membranes, or built-up roofing may be heat-welded or hot-mopped directly to **STURDY-DEK**. The asphalt board then becomes an integral part of the roof membrane, making it stronger and more puncture-resistant.

### FEATURES/BENEFITS

- Dimensionally stable, water-resistant, tough, durable panels.
- Acts as both a base sheet and levelling board over built-up roofs.
- Modified bitumen roofing systems can be heat-weld torched directly to the board surface. Refer to CERTA requirements for safe and proper torch application.
- Limited number of sheets per pallet to accommodate easier roof loading and distribution.
- UL Classified to ANSI/UL 790 as a component in Class A rated roof systems, reference TGFU.R20803.
- ULC Classified to Canadian Standard CAN/ULC-S107 as a component in Class A rated roof systems, reference TGFU7.R20803.

### TECHNICAL AND PACKAGE DATA

	1/8"	1/4"
Thickness (Nominal)	0.125" (3.2 mm)	0.250" (6.4 mm)
Weight per Sq. Ft.	0.67 lb (0.30 kg)	1.58 lb. (0.72 kg)
Asphalt % by weight	>72%	>72%
Sheet Size	4' x 8' (1.2 x 2.4 m)	4' x 8' (1.2 x 2.4 m)
Pallet Quantity	100 sheets	50 sheets
Pallet Weight	2200 lbs (998 kg)	2600 lbs (1179 kg)
Water Absorption ASTM D994 24H	<1%	<1%
Compressive Strength ASTM D545 50%	9000 psi	4000 psi
Puncture Resistance ASTM E154	75 lbf	105 lbf

### PRECAUTIONS

Moisture conditions during installation may affect the performance of the product and the roof system. Avoid application during rain, heavy fog, dew, and any other conditions that may deposit moisture on surfaces. Cover **STURDY-DEK** promptly after installation. Do not leave exposed. Do not place on wet membranes or adhesives until solvents have completely evaporated. Use only rubber-tired construction equipment. Boards should remain stacked on the pallets on which they are shipped and stored on a smooth, flat surface to prevent deformation before being applied. **DO NOT STACK PALLETS IN STORAGE.** **STURDY-DEK** may be double stacked on a short-term basis only for transportation. Not to be used in applications where contact with a coal-tar based waterproofing system is possible.

BLUE RIDGE FIBERBOARD will not be responsible for deficiencies in design, construction, or workmanship; and for product moisture exposure before, during or after installation.

#### LEED INFORMATION

May help contribute to LEED credits:

MR Credit Construction Waste Management

MR Credit Recycled Content

MR Credit Regional Materials

---

**Limited Warranty:** BLUE RIDGE FIBERBOARD, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

**Disclaimer:** The information contained herein is included for illustrative purpose only, and to the best of our knowledge, is accurate and reliable. BLUE RIDE FIBERBOARD, INC. cannot however under any circumstance make any guarantee of results or assume any obligation or liability in connection with the use of this information. As BLUE RIDGE FIBERBOARD, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

© 2022 BLUE RIDGE FIBERBOARD, INC.