

LP Legacy[™] Sub-Flooring Louisiana-Pacific Corporation

PR-N127

Revised March 16, 2021

Product: LP Legacy[™] Sub-Flooring LP Building Products, Louisiana-Pacific Corporation, 414 Union St., Suite 2000 Nashville, TN, 37219 (888) 820-0325 www.lpcorp.com

1. Basis of the product report:

- 2021 International Building Code (IBC), 2018 IBC, and 2015 IBC: Sections 104.11 Alternative materials and 2303.1.5 Wood structural panels
- 2012 IBC: Sections 104.11 Alternative materials and 2303.1.4 Wood structural panels
- 2021 International Residential Code (IRC), 2018 IRC, 2015 IRC, and 2012 IRC: Sections R104.11 Alternative materials and R503.2 Wood structural panel sheathing
- DOC PS 2, Performance Standard for Wood Structural Panels
- ASTM D7033, Standard Practice for Establishing Design Capacities for Oriented Strand Board (OSB) Wood-Based Structural-Use Panels
- APA Reports T2006P-17, T2008P-99, T2008P-100, T2008P-101, T2008P-102, T2017P-29, T2019P-19, T2019P-59A, T2019P-64, and T2020P-24, and other qualification data

2. Product description:

LP Legacy[™] Sub-Flooring is made with strands of various species and strand classifications, meeting DOC PS 2 with a floor sheathing span rating and is in accordance with the in-plant manufacturing standard approved by APA. LP Legacy Sub-Flooring is available in performance categories of 19/32, 5/8, 23/32, 7/8, and 1-1/8, and in 4x8-foot nominal panel size. The 23/32 sheathing also meets the PS 2 requirements for 48/24 Structural I Rated Sheathing and 24oc Structural I Rated Single Floor .

3. Design properties:

Table 1 lists the panel design capacities of LP Legacy Sub-Flooring. Additional design information is available from the manufacturer (www.lpcorp.com). LP Legacy Sub-Flooring shall be permitted for use as floor sheathing in accordance with an approved span rating identified in the panel trademark. Table 2 provides equivalent specific gravity values for LP Legacy Sub-Flooring for connection design using smooth-shank or screw-shank nails with a diameter of 1/4 inch or less.

Product installation:

LP Legacy Sub-Flooring recognized in this report shall be used in accordance with the recommendations provided by the manufacturer (see link above) and *APA Engineered Wood Construction Guide*, Form E30 (www.apawood.org/resource-library).

Limitations:

- a) LP Legacy Sub-Flooring recognized in this report shall be designed in accordance with the applicable engineering practices using the design properties specified in this report and shall be permitted for use as floor sheathing in accordance with an approved span rating identified in the panel trademark.
- b) LP Legacy Sub-Flooring is limited to dry service conditions that result in the average equilibrium moisture content of sawn lumber of less than 16 percent.
- c) LP Legacy Sub-Flooring is produced at Louisiana-Pacific Corporation facilities in the following qualified performance categories: Hanceville, Alabama 23/32, 7/8, and 1-1/8,

Roxboro, North Carolina – 23/32, and Sagola, Michigan – 19/32, 5/8, 23/32, 7/8, and 1-1/8.

d) This report is subject to re-examination in one year.

Identification:

The LP Legacy Sub-Flooring described in this report is identified by a label bearing the manufacturer's name (Louisiana-Pacific Corporation) and/or trademark, the APA assigned plant number (442 for the Hanceville, AL plant, 456 for the Roxboro, NC plant, and 407 for the Sagola, MI plant), the product performance category, the APA logo, the report number PR-N127, and a means of identifying the date of manufacture.

Table 1. Panel Design Capacities for LP Legacy Sub-Flooring (a)

	J		Bending	Bending	Axial	Planar
Span	Performance	Strength	Stiffness,	Strength,	Stiffness,	Shear,
Rating	Category ^(b)	Axis ^(c)	EI ^(d)	F₀S	EA	F _s (Ib/Q)
			(lbf-in. ² /ft)	(lbf-in./ft)	(lbf/ft)	(lbf/ft)
20 o.c.	19/32	Primary	224,390	900	5,300,000	NA
		Secondary	92,680	500	3,300,000	NA
	5/8	Primary	229,270	1,000	5,400,000	NA
		Secondary	107,320	600	3,500,000	NA
24 o.c.	23/32 ^(e)	Primary	395,120	1,300	6,100,000	385
		Secondary	160,980	750	3,700,000	385
32 o.c.	7/8	Primary	707,320	1,800	NA	NA
		Secondary	NA	NA	5,400,000	NA
48 o.c.	1-1/8	Primary	1,150,000	1,900	NA	NA
		Secondary	NA	NA	4,600,000	NA

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 0.454 kg, 1 psi = 6.9 kPa.

(d) The tabulated value is apparent EI. The total panel deflection shall be calculated as follows:

For a single-span condition: $\Delta = \frac{w (L_3)^4}{921.6 \ EI}$

For a two-span condition: $\Delta = \frac{w (L_3)^4}{2220 \, EI}$

For a three-span condition: $\Delta = \frac{w (L_3)^4}{1743 \, El}$

where:

 Δ = total deflection (in.) w = uniform load (psf)

EI = tabulated bending stiffness capacity (lbf-in.2/ft)

 L_3 = clear span + SW (in.)

SW = support-width factor, equal to 0.25 in. for two-inch-nominal lumber framing and 0.625 in. for four-inch-nominal lumber framing

(e) The 23/32 sheathing also meets the PS 2 requirements for 24oc Structural I Rated Single Floor.

⁽a) Design capacity is a single value that represents the product of the allowable stress and corresponding section property per 1-foot width of panel for a given load condition.

⁽b) Performance Category is linked to the nominal panel thickness designations used in the International Building Code (IBC) and International Residential Code (IRC).

⁽c) Primary strength axis corresponds to direction parallel to the panel strength axis, which is typically the panel length direction, and the secondary strength axis corresponds to the direction perpendicular to the panel strength axis, which is typically the panel width direction.

Table 2. Equivalent Specific Gravity (ESG) for Nailed Connections with LP Legacy Sub-Flooring

			- 9 7 9
Span Rating	Performance Category ^(a)	Withdrawal ^(b)	Lateral ^(b)
20 o.c.	19/32 or 5/8	0.40	0.50
24 o.c.	23/32	0.44	0.50
32 o.c.	7/8	0.40	0.50
48 o.c.	1-1/8	0.40	0.50

⁽a) Performance Category is linked to the nominal panel thickness designations used in the International Building Code (IBC) and International Residential Code (IRC).

APA – The Engineered Wood Association is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, and Validation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

APA - THE ENGINEERED WOOD ASSOCIATION

HEADQUARTERS

7011 So. 19th St. • Tacoma, Washington 98466 Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: <u>www.apawood.org</u>

PRODUCT SUPPORT HELP DESK

(253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – The Engineered Wood Association, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.

⁽b) For smooth-shank or screw-shank nails with a diameter of 1/4 in. or less.