

SELF-LEVELING TOPPING QUICK TURNAROUND

SUPER FLOWCRETE®

USE AS WEARING SURFACE
USE AS AN UNDERLAYMENT
USE AS DECORATIVE FLOORING SURFACE

PRODUCT DESCRIPTION

SUPER FLOWCRETE is a technically advanced portland cement based material which is self-leveling, self-drying and will perform very well as an interior finished floor, wearing surface or underlayment. It is a one component, polymer modified scientific blend of cements, select graded silica and special additives. **SUPER FLOWCRETE** is self-drying through an internal chemical reaction which uses the water not needed for hydration.

SUPER FLOWCRETE gives a smooth, flat finished floor which is suitable for quick application of floor coverings or use as a finished wearing surface.

PRODUCT APPLICATIONS

SUPER FLOWCRETE is designed to be used as a self-leveling wearing surface topping, underlayment or decorative finished floor. It is easy to apply and provides a smooth, tough finished floor. Use it as a new floor or for floor repairs in residential, retail, commercial, warehouses, utility areas and light manufacturing facilities. **SUPER FLOWCRETE** is suitable for hard rubber tire forklift traffic.

When **SUPER FLOWCRETE** is used as an underlayment, breathable floor coverings such as carpet, tile, etc., may be applied as soon as the material has dried (normally 6-8 hours). Non-breathable coverings or coatings such as epoxy, urethane and seamless flooring, may be applied as soon as 24 hours later.

SUPER FLOWCRETE is also designed to be used as an interior decorative floor for retail, hotel, restaurants and similar applications. Integral concrete colors and stains may be used to make decorative patterns and designs.

PACKAGING

SUPER FLOWCRETE is packaged in 45 lb. moisture resistant bags, with 70 bags per pallet.

PRODUCT FEATURES

- Self-Leveling
- Self-Drying
- Light Gray Concrete Color, Also Available in White
- Use for Warehouses/Forklift Traffic
- Underlayment from Feather to 2 Inches
- Wearing Surface from 1/4 Inch to 2 Inches
- Easy to Mix and Apply
- Not a Gypsum Product
- Pumpable

PRODUCT SPECIFICATIONS

Color:	Light Gray or White		
Flow and Self-Heal Time:	10 - 12 Minutes		
Working Time:	25 Minutes		
Initial Set (ASTM C-191):	19 Minutes		
Final Set (ASTM C-191):	49 Minutes		
COMPRESSIVE STRENGTH (ASTM C-109, Air Cured)			
1 Day	3 Days	7 Days	28 Days
2600 PSI	3900 PSI	5300 PSI	6100 PSI
FLEXURAL STRENGTH (ASTM C-348, Air Cured)			
3 Days		7 Days	28 Days
925 PSI		1316 PSI	1360 PSI
SLANT SHEAR BOND STRENGTH (ASTM C-1042, Air Cured)			
28 Days - 935 PSI		P-100 PRIMER	
SHRINKAGE (ASTM C-596, Air Cured)			
7 Days - .03%		28 Days - .04%	
ABRASION RESISTANCE (ASTM C-944, Internal Test)			
28 Days - .62% Wt. Loss - Very Good			

COVERAGE

One 45 lb. bag of **SUPER FLOWCRETE** will cover 45 sq. ft. at 1/8" thickness.

SURFACE PREPARATION

All surfaces must be clean and structurally sound; free of dust, grease, oil, paint, sealers, curing compounds, etc. Any damaged or weak concrete and surface laitance must be removed. Prepare the surface by mechanical abrasion such as shot-blasting or scarifying to get a rough profile for bonding. If acid etching is used, the surface must be neutralized and thoroughly cleaned. Steel troweled, slick surfacing and non-porous surfaces must be mechanically abraded or use **EP-200 EPOXY PRIMER** per installation instructions on the **EP-200 Literature**.

Prime surface with **P-100 PRIMER** for concrete, masonry, wood, and exterior grade plywood. Apply primer with roller or soft bristle push broom. Remove any puddles. Allow primer to dry completely before applying **SUPER FLOWCRETE**. Primer will dry in approximately 30 minutes. When using **SUPER FLOWCRETE** as a wearing surface, **DO NOT dilute P-100 PRIMER**. We recommend using the **EP-200 EPOXY PRIMER** to maximize bond performance. Floor must be rigid and sound. Use metal lathe to hold wood and exterior grade plywood firm and rigid. Primer may be applied up to 24 hours before application of **SUPER FLOWCRETE**. Very porous concrete may require two coats of primer to prevent air bubbles and pinholes in **SUPER FLOWCRETE**.

MIXING AND APPLICATION

Mix one (1) bag of **SUPER FLOWCRETE** (45 lb.) with 4-3/4 quarts of water. Trapping air during mixing can lead to bubbles in finished surface. Place water in the drum first and add **SUPER FLOWCRETE** while mixing. Use a heavy duty (>700 RPM) 1/2" or 3/4" high speed drill and jiffy or basket mixer. **DO NOT** try to mix by hand. Mix thoroughly for about 2-3 minutes to obtain smooth, lump-free and liquid mixture. Aggressive and high speed mixing increases liquidity and flow. **DO NOT OVERWATER**. Two bags may be mixed at once and use a team approach with two mixing drums for faster installation. Use a measured pail with holes drilled so excess water above 4-3/4 quarts spills out.

Pour the liquid **SUPER FLOWCRETE** roughly into place. Spread and smooth with mortar spreader and smoother. **DO NOT TROWEL FINISH**. A trowel or smoother may be used to touch up and featheredge. Wear spiked shoes if it is necessary to walk in fresh mortar. **SUPER FLOWCRETE** has 10-12 minutes flow time at 70°F. While aggregate addition is not necessary, 3/8" pea gravel may be added up to 1/4 of total mix to extend product. Flow may be impaired and surface may not be as smooth as desired. Clean tools frequently with water. For faster installation of larger areas, **SUPER FLOWCRETE** may be pumped. Contact the factory regarding pumps.

USE AS AN UNDERLAYMENT

SUPER FLOWCRETE may be used as an underlayment from featheredge to 2" depth. A sealer should not be applied when used as an underlayment. Always follow the directions of floor covering manufacturers concerning maximum moisture content, pH levels and perform required tests.

CONTAINS PORTLAND CEMENT. Avoid eye contact or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush with plenty of water for at least 15 minutes. Consult a physician immediately. Keep out of the reach of children.

CONTAINS SILICA SAND AND FREE SILICA. Do not breathe dust. Avoid inhalation by wearing respirator. Continuous exposure and inhalation may cause silicosis and crystalline silica is classified as a known human carcinogen.

LIMITED WARRANTY

Lyons Manufacturing, Inc. warrants the high quality of its products. However, because of many factors beyond our control in their use, such as job conditions, workmanship, etc., the liability of all parties making and selling this product is expressly limited to the refund of the purchase price or replacement of the Lyons material used. Lyons Manufacturing, Inc. will replace any product proven to have a manufacturing defect, FOB Factory, provided Lyons Manufacturing, Inc. is notified of such defect within one (1) year from the date of shipment from the factory. This warranty is in lieu of all other warranties, express or implied. Lyons Manufacturing, Inc. makes no warranty of suitability of its products for any particular application and sells its products upon the condition that customer shall conduct their own test to determine the suitability of the products for their purposes. Under no circumstances will Lyons Manufacturing, Inc. be liable for economic, special, incidental or consequential damages or losses of any kind.

USE AS A WEARING SURFACE

SUPER FLOWCRETE has very good abrasion resistance and may be used as a finished floor with traffic up to and including hard rubber tire forklifts. **DO NOT USE** it where there is steel or hard plastic wheel traffic, or where heavy equipment or tools will be dragged across surface, or for heavy duty industrial use. Use from 1/4" to 2" as wearing surface. Cut down all repair edges as needed. **DO NOT FEATHEREDGE**. Cracks should be routed out and prefilled. Construction joints should be brought up through the **SUPER FLOWCRETE**. Avoid having full weight of heavy traffic on corners of **SUPER FLOWCRETE** by using joint filler, polyurea or other protection.

When using **SUPER FLOWCRETE** as a wearing surface, **DO NOT dilute P-100 PRIMER**. As bond is of critical importance for overlays, we recommend using the **EP-200 EPOXY PRIMER** to maximize bond performance, especially in decorative applications. **EP-200** can help minimize effects of substrate movement and crack telegraphing.

When used as a wearing surface, always apply a sealer to **SUPER FLOWCRETE**. A high solids acrylic sealer may be applied after 24 hours. Open for foot and light traffic as soon as sealer is dry. Open for heavier traffic after 2 days. Use of integral color may retard set and cure times.

USE OVER CUTBACK

Remove as much of cutback as possible, leaving only a thin residue firmly bonded to concrete. Remember your bond will only be as good as the bond of the cutback to the concrete. Coat the surface with a thin uniform amount of **ACRYLIC-BOND** emulsion. Let this coat dry completely, then prime with **P-100 PRIMER** without dilution with water. Let the **P-100 PRIMER** dry and install **SUPER FLOWCRETE** as previously described.

LIMITATIONS

Do not overwater. Do not trap air while mixing.

Do not apply below 45°F. Do not let **P-100 PRIMER** freeze.

Not for exterior use.

Do not trowel finish.

Protect from rapid drying from exposure to heat and a/c vents and open doorways.

Do not dilute **P-100 PRIMER** for wearing surface applications.

Use **EP-200 EPOXY PRIMER** for low porosity substrate applications.

EP-200 EPOXY PRIMER recommended for Decorative Overlays.

NOTE: Test areas should be used in all cases to be sure the product is suitable for the specific application at hand, including sealers, coatings, adhesives and floor coverings to insure compatibility.

Scan Here For More Information



LYONS MANUFACTURING, INC.

8900 Forney Road ♦ Dallas, TX 75227 ♦ 214-381-8100

www.lyonsmanufacturing.com