

Marino\WARE® Product Submittal Data

PRODUCT NAME: 800QFH300-118


MARINO\WARE PART # 800QFH300118



PROPERTIES:

A. Web (in)	8	Yield Strength Fy (KSI)	50
B. Flange (in)	3	Tensile Strength Fu (KSI)	65
C. Lip (in)	1	Design Thickness (in)	0.1242
Mils	118	Minimum Thickness (in)	0.1180
Available Finish	G60, G90	Gauge	10

05.40.00 Cold-Formed Metal Framing



SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	1.87
Weight of Member: (lb/ft)	6.37
Moment of Inertia: Ix (in ⁴)	18.1
Section Modulus: Sx (in ³)	4.53
Radius of Gyration: Rx (in)	3.11
Moment of Inertia: Iy (in ⁴)	2.27
Section Modulus: Sy (in ³)	1.09
Radius of Gyration: Ry (in)	1.10

EFFECTIVE SECTION PROPERTIES - Unpunched

Moment of Inertia-Deflection: Ixe (in ⁴)	18.1
Section Modulus: Sxe (in ³)	4.53
Allowable Bending Moment: Malx (in-k)	153
Allowable Bending Moment: Madx (in-k)	133
Moment of Inertia: Iye (in ⁴)	2.27
Section Modulus: Sye (in ³)	1.09
Allowable Bending Moment: Maly (in-k)	38.8
Allowable Bending Moment: Mady (in-k)	35.3
Allowable shear: Vag (k)	16.235

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: Jx1000 (in ⁴)	9.63
Torsional Warping Constant: Cw (in ⁶)	32.1
Shear Center to Centroid on Principal X-axis: Xo (in)	-2.24
Radius of Gyration on the Centroid Principal axis: Ro (in)	3.99
Torsional Flexural Constant: β = [1-(xo/Ro) ²]	0.684

CODES & STANDARDS

- AISI S100 & S240
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021

GREEN INFO

- LEED credits available
- Contact Technical Services for more information



For more information, please contact Marino\WARE Technical Services at 866-545-1545.

This technical information reflects the most current information available and supersedes any and all publications, effective 8/02/2024
© Copyright 2024 by Ware Industries, Inc. All rights reserved