

Marino\WARE® Product Submittal Data

PRODUCT NAME: 1000S162-68

05.40.00 Cold-Formed Metal Framing

MARINO\WARE PART # 100SS14

PROPERTIES:

A. Web (in)	10"	Yield Strength Fy (KSI)	50
B. Flange (in)	1-5/8"	Tensile Strength Fu (KSI)	65
C. Lip (in)	1/2"	Design Thickness (in)	0.0713
Mils	68	Minimum Thickness (in)	0.0677
Available Finish	G60	Gauge	14

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	0.978
Weight of Member: (lb/ft)	3.329
Moment of Inertia: I_x (in ⁴)	12.329
Section Modulus: S_x (in ³)	2.466
Radius of Gyration: R_x (in)	3.550
Gross Moment of Inertia: I_y (in ⁴)	0.247
Gross Radius of Gyration: R_y (in)	0.502

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: I_{xe} (in ⁴)	11.919
Section Modulus: S_{xe} (in ³)	2.155
Allowable Local Bending Moment: M_{al} (in-k)	64.51
Allowable Distortional Bending Moment: M_{ad} (in-k)	53.80
Allowable strong axis shear away from punch: V_{ag} (lb)	3345
Allowable strong axis shear at punch: V_{anet} (lb)	3345

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: J_{x1000} (in ⁴)	1.658
Torsional Warping Constant: C_w (in ⁶)	5.121
Shear Center to Centroid on Principal X-axis: X_o (in)	-0.798
Shear Center to Mid-Plane of the Web: m (in)	0.531
Radius of Gyration on the Centroid Principal axis: R_o (in)	3.673
Torsional Flexural Constant: β 1-(x _o /R _o) ²	0.953

CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

GREEN INFO

- LEED credits available
- Contact Technical Services for more information.

