

Marino\WARE® Product Submittal Data

PRODUCT NAME: 600S162-43

MARINO\WARE PART # 600SS18

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	6"	Yield Strength Fy (KSI)	33
B. Flange (in)	1-5/8"	Tensile Strength Fu (KSI)	45
C. Lip (in)	1/2"	Design Thickness (in)	0.0451
Mils	43	Minimum Thickness (in)	0.0428
Available Finish	G90	Gauge	18

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	0.447
Weight of Member: (lb/ft)	1.52
Moment of Inertia: Ix (in ⁴)	2.316
Section Modulus: Sx (in ³)	0.772
Radius of Gyration: Rx (in)	2.276
Gross Moment of Inertia: Iy (in ⁴)	0.148
Gross Radius of Gyration: Ry (in)	0.576

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: Ixe (in ⁴)	2.32
Section Modulus: Sxe (in ³)	0.77
Allowable Local Bending Moment: Mal (in-k)	16.70*
Allowable Distortional Bending Moment: Mad (in-k)	13.00
Allowable strong axis shear away from punch: Vag (lb)	1416
Allowable strong axis shear at punch: Vanet (lb)	1240

* Allowable Bending Moment includes cold work of forming

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: Jx1000 (in ⁴)	0.303
Torsional Warping Constant: Cw (in ⁶)	1.095
Shear Center to Centroid on Principal X-axis: Xo (in)	-1.062
Shear Center to Mid-Plane of the Web: m (in)	0.670
Radius of Gyration on the Centroid Principal axis: Ro (in)	2.577
Torsional Flexural Constant: β 1-(xo/Ro) ²	0.830

CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

GREEN INFO

- LEED credits available
- Contact Technical Services for more information.

