
### Member Designator 362JS300-68

Coating CP60

#### **Physical Properties**

Design Thickness 0.0713 in Mil 68 mil Gauge 14 Gauge Web Width 3.625 in Flange Width 3.00 in Stiffening Lip 1.00 in Yield Strength 50 ksi



## **Gross Properties**


Area	Weight	lx	Sx	Rx	ly	Ry
(in <sup>2</sup> )	(lb/ft)	(in <sup>4</sup> )	(in <sup>3</sup> )	(in)	(in⁴)	(in)
0.791	2.69	1.771	0.977	1.496	1.063	1.159

### **Effective Properties**

lx	Sx	Ma	Vag	
(in <sup>4</sup> )	(in <sup>3</sup> )	(in-k)	(lb)	
1.771	0.977	26.63	7078	

# **Torsional Properties**

J <sup>×1000</sup>	Cw	Хо	Ro	β
(in <sup>4</sup> )	(in <sup>6</sup> )	(in)	(in)	
1.341	4.556	-2.938	3.495	0.293



#### **General Notes**

- 1. Physical properties and load tables have been calculated in conformance with the 2001 NASPEC for the Design of Cold-Formed Steel Structural Members, including the 2004 Supplement, and the IBC 2006, unless noted otherwise.
- 2. All structural framing members have a protective coating conforming to ASTM C 955.
- 3. Reference ASTM specification A 1003/A 1003 M table 1 for the universe of allowable coatings for light gauge steel framing.
- 4. Stud/joists are manufactured to custom lengths. Stud/joists are manufactured with punched webs unless otherwise specified at time of order.
- 5. Track is produced in standard lengths of 10 feet unless a custom track length is indicated. Track is manufactured with unpunched webs.
- 6. Structural framing members are marked with product information per the requirements of ASTM C 955 section 12.
- 7. All delivered material must be kept dry, preferably by being stored inside a building under a roof. If it is necessary to store material outside, it must be stacked off the ground, properly supported on a level platform, and fully protected from the weather. Reference ASTM C 754 section 8 and ASTM C 1007 section 4.

#### **LEED Green Building Credits**

MR Credit 2: Construction Waste Management – MBA steel framing is 100% recyclable.

MR Credit 4: Recycled Content – MBA steel framing is formed from no less than 25.5% post-consumer and 6.8% pre-consumer recycled content. MR Credit 5: Regional Materials – MBA has manufacturing facilities in multiple states.

