
## Submittal Data - Jamb Stud

# Member Designator 362JS300-97

Coating CP60

## **Physical Properties**

Design Thickness 0.1017 in Mil 97 mil Gauge 12 Gauge Web Width 3.625 in Flange Width 3.00 in Stiffening Lip 1.00 in Yield Strength 50 ksi



### **Gross Properties**


| Area               | Weight  | lx    | Sx                 | Rx    | ly                 | Ry    |
|--------------------|---------|-------|--------------------|-------|--------------------|-------|
| (in <sup>2</sup> ) | (lb/ft) | (in⁴) | (in <sup>3</sup> ) | (in)  | (in <sup>4</sup> ) | (in)  |
| 1.114              | 3.79    | 2.449 | 1.351              | 1.483 | 1.461              | 1.146 |

# **Effective Properties**

| lx                 | Sx    | Ma     | Vag  |  |
|--------------------|-------|--------|------|--|
| (in <sup>4</sup> ) | (in³) | (in-k) | (lb) |  |
| 2.444              | 1.351 | 40.24  | 9865 |  |

# **Torsional Properties**

| J <sup>x1000</sup> | Cw                 | Хо     | Ro    | β     |
|--------------------|--------------------|--------|-------|-------|
| (in <sup>4</sup> ) | (in <sup>6</sup> ) | (in)   | (in)  |       |
| 3.840              | 6.115              | -2.902 | 3.454 | 0.294 |



#### **General Notes**

- 1. Physical properties and load tables have been calculated in conformance with the 2001 NASPEC for the Design of Cold-Formed Steel Structural Members, including the 2004 Supplement, and the IBC 2006, unless noted otherwise.
- 2. All structural framing members have a protective coating conforming to ASTM C 955.
- 3. Reference ASTM specification A 1003/A 1003 M table 1 for the universe of allowable coatings for light gauge steel framing.
- 4. Stud/joists are manufactured to custom lengths. Stud/joists are manufactured with punched webs unless otherwise specified at time of order.
- 5. Track is produced in standard lengths of 10 feet unless a custom track length is indicated. Track is manufactured with unpunched webs.
- 6. Structural framing members are marked with product information per the requirements of ASTM C 955 section 12.
- 7. All delivered material must be kept dry, preferably by being stored inside a building under a roof. If it is necessary to store material outside, it must be stacked off the ground, properly supported on a level platform, and fully protected from the weather. Reference ASTM C 754 section 8 and ASTM C 1007 section 4.

#### **LEED Green Building Credits**

MR Credit 2: Construction Waste Management – MBA steel framing is 100% recyclable.

MR Credit 4: Recycled Content – MBA steel framing is formed from no less than 25.5% post-consumer and 6.8% pre-consumer recycled content.

MR Credit 5: Regional Materials – MBA has manufacturing facilities in multiple states.

