

Sales: (888)248-8076 Fax: (847)680-7883 www.mbastuds.com

| Member Designator Coating | 600PT150-30 G40 EQ | Y |
|------------------------------|------------------------------|---------------|
| Physical Properties | | |
| Design Thickness | 0.0312 in | Inside |
| Mil | 30 mil | Web X |
| Gauge | 20 Gauge | Width |
| Web Width | 6.00 in | |
| Flange Width | 1.50 in | |
| Yield Strength | 33 ksi | |
| | | Leg Length |

| | | Gross Properties | | | | | |
|------------------|--------------------|------------------|-------|-------|-------|-------|-------|
| Gross Properties | Area | Weight | Ix | Sx | Rx | ly | Ry |
| | (in ²) | (lb/ft) | (in⁴) | (in³) | (in) | (in⁴) | (in) |
| | 0.281 | 0.955 | 1.422 | 0.466 | 2.251 | 0.051 | 0.427 |

| Effective Properties | | | | | |
|----------------------|--------------------|--------------------|----------|--|--|
| Ae Ixe | | Sxe | Ma | | |
| (in²) | (in ⁴) | (in ³) | (in-lbs) | | |
| 0.090 | 1.136 | 0.244 | 4818 | | |

Effective Properties

| | Torsional | | | | |
|--------------------|--------------------|---------|--------|-------|--|
| J ^{×1000} | Cw | Хо | Ro | β | |
| (in⁴) | (in ⁶) | (in) | (in) | | |
| 0.09 | 1 0.34 | 7 -0.68 | 6 2.39 | 0.918 | |

General Notes

- 1. MBA Building Supplies is a SSMA member company. MBA adheres to the product standards and quality standards as required by SSMA.
- Physical properties and load tables have been calculated in conformance with the 2001 NASPEC for the Design of Cold-Formed Steel Structural Members, including the 2004 Supplement, and the IBC 2006, unless noted otherwise.
- 3. Allowable composite heights are calculated using ICC-ES AC86-2010. The 1/3 stress increase was not used.
- 4. Drywall framing members have a protective coating conforming to ASTM spec A 653/A 653M, G-40 min, or equivalent corrosion resistance.
- 5. Reference ASTM specification A 1003/A 1003 M table 1 for the universe of allowable coatings for light gauge steel framing.
 - 6. Drywall framing members are marked with product information per the requirements of ASTM C 645 section 14.
 - All delivered material must be kept dry, preferably by being stored inside a building under a roof. If it is necessary to store material outside, it must be stacked off the ground, properly supported on a level platform, and fully protected from the weather. Reference ASTM C 754 section 8 and ASTM C 1007 section 4.
 - 8. Drywall framing [nonstructural 25 gauge, 22 gauge and 20 gauge] is not permitted in load bearing (i.e. axial load greater than 200 lbs.) or exterior applications (i.e. transverse load greater than 10 PSF). Reference ASTM C 645 section 3.2.2.

LEED Green Building Credits

MR Credit 2: Construction Waste Management – MBA steel framing is 100% recyclable.

MR Credit 4: Recycled Content – MBA steel framing is formed from no less than 25.5% post-consumer and 6.8% pre-consumer recycled content. MR Credit 5: Regional Materials – MBA has manufacturing facilities in Illinois and Alabama.

