
# Submittal Data - Structural Stud

## Member Designator 925S162-97

Coating CP60

### **Physical Properties**

Design Thickness 0.1017 in Mil 97 mil Gauge 12 Gauge Web Width 9.25 in Flange Width 1.625 in Stiffening Lip 0.50 in Yield Strength 50 ksi



## **Gross Properties**


| Area  | Weight  | lx                 | Sx                 | Rx    | ly                 | Ry    |
|-------|---------|--------------------|--------------------|-------|--------------------|-------|
| (in²) | (lb/ft) | (in <sup>4</sup> ) | (in <sup>3</sup> ) | (in)  | (in <sup>4</sup> ) | (in)  |
| 1.296 | 4.41    | 13.947             | 3.016              | 3.280 | 0.315              | 0.493 |

### **Effective Properties**

| lxx                | Sxx                | Ma     | Vag   |  |
|--------------------|--------------------|--------|-------|--|
| (in <sup>4</sup> ) | (in <sup>3</sup> ) | (in-k) | (lb)  |  |
| 13.947             | 2.963              | 88.70  | 10710 |  |

# **Torsional Properties**

| J <sup>x1000</sup> | Cw                 | Xo     | m    | Ro   | β     |
|--------------------|--------------------|--------|------|------|-------|
| (in <sup>4</sup> ) | (in <sup>6</sup> ) | (in)   | (in) | (in) |       |
| 4.468              |                    | -0.802 |      |      | 0.945 |



#### **General Notes**

- 1. Physical properties and load tables have been calculated in conformance with the 2001 NASPEC for the Design of Cold-Formed Steel Structural Members, including the 2004 Supplement, and the IBC 2006, unless noted otherwise.
- 2. All structural framing members have a protective coating conforming to ASTM C 955.
- 3. Reference ASTM specification A 1003/A 1003 M table 1 for the universe of allowable coatings for light gauge steel framing.
- 4. Stud/joists are manufactured to custom lengths. Stud/joists are manufactured with punched webs unless otherwise specified at time of order.
- 5. Track is produced in standard lengths of 10 feet unless a custom track length is indicated. Track is manufactured with unpunched webs.
- 6. Structural framing members are marked with product information per the requirements of ASTM C 955 section 12.
- 7. All delivered material must be kept dry, preferably by being stored inside a building under a roof. If it is necessary to store material outside, it must be stacked off the ground, properly supported on a level platform, and fully protected from the weather. Reference ASTM C 754 section 8 and ASTM C 1007 section 4.

#### **LEED Green Building Credits**

MR Credit 2: Construction Waste Management – MBA steel framing is 100% recyclable.

MR Credit 4: Recycled Content – MBA steel framing is formed from no less than 25.5% post-consumer and 6.8% pre-consumer recycled content. MR Credit 5: Regional Materials – MBA has manufacturing facilities in multiple states.

