Sales:(888)248-8076 Fax:(847)680-7883 www.mbastuds.com


# Submittal Data - Structural Stud

## Member Designator 800S250-68

Coating CP60

## **Physical Properties**

Design Thickness 0.0713 in Mil 68 mil Gauge 14 Gauge Web Width 8.00 in Flange Width 2.50 in Stiffening Lip 0.625 in Yield Strength 50 ksi



## **Gross Properties**


| Area  | Weight  | lx                 | Sx                 | Rx    | ly                 | Ry    |
|-------|---------|--------------------|--------------------|-------|--------------------|-------|
| (in²) | (lb/ft) | (in <sup>4</sup> ) | (in <sup>3</sup> ) | (in)  | (in <sup>4</sup> ) | (in)  |
| 0.978 | 3.33    | 9.261              | 2.315              | 3.077 | 0.752              | 0.877 |

## **Effective Properties**

| lxx   | Sxx                | Ma     | Vag  |  |
|-------|--------------------|--------|------|--|
| (in⁴) | (in <sup>3</sup> ) | (in-k) | (lb) |  |
| 9.240 | 2.059              | 61.65  | 4221 |  |

## **Torsional Properties**

| J <sup>x1000</sup> | Cw                 | Xo     | m     | Ro    | β     |
|--------------------|--------------------|--------|-------|-------|-------|
| (in <sup>4</sup> ) | (in <sup>6</sup> ) | (in)   | (in)  | (in)  |       |
| 1.658              |                    | -1.644 | 1.027 | 3.597 | 0.791 |



#### **General Notes**

- 1. Physical properties and load tables have been calculated in conformance with the 2001 NASPEC for the Design of Cold-Formed Steel Structural Members, including the 2004 Supplement, and the IBC 2006, unless noted otherwise.
- 2. All structural framing members have a protective coating conforming to ASTM C 955.
- 3. Reference ASTM specification A 1003/A 1003 M table 1 for the universe of allowable coatings for light gauge steel framing.
- 4. Stud/joists are manufactured to custom lengths. Stud/joists are manufactured with punched webs unless otherwise specified at time of order.
- 5. Track is produced in standard lengths of 10 feet unless a custom track length is indicated. Track is manufactured with unpunched webs.
- 6. Structural framing members are marked with product information per the requirements of ASTM C 955 section 12.
- 7. All delivered material must be kept dry, preferably by being stored inside a building under a roof. If it is necessary to store material outside, it must be stacked off the ground, properly supported on a level platform, and fully protected from the weather. Reference ASTM C 754 section 8 and ASTM C 1007 section 4.

#### **LEED Green Building Credits**

MR Credit 2: Construction Waste Management – MBA steel framing is 100% recyclable.

MR Credit 4: Recycled Content – MBA steel framing is formed from no less than 25.5% post-consumer and 6.8% pre-consumer recycled content. MR Credit 5: Regional Materials – MBA has manufacturing facilities in multiple states.

