Sales: (888)248-8076 Fax: (847)680-7883 www.mbastuds.com


# Submittal Data - Structural Stud

## Member Designator 1150S162-43

Coating CP60

### **Physical Properties**

Design Thickness 0.0451 in Mil 43 mil Gauge 18 Gauge Web Width 11.50 in Flange Width 1.625 in Stiffening Lip 0.50 in Yield Strength 33 ksi



## **Gross Properties**


| Area  | Weight  | lx                 | Sx                 | Rx    | ly                 | Ry    |
|-------|---------|--------------------|--------------------|-------|--------------------|-------|
| (in²) | (lb/ft) | (in <sup>4</sup> ) | (in <sup>3</sup> ) | (in)  | (in <sup>4</sup> ) | (in)  |
| 0.695 | 2.36    | 11.383             | 1.980              | 4.047 | 0.173              | 0.499 |

### **Effective Properties**

| lx                 | Sx                 | Ma     | Vag  |  |
|--------------------|--------------------|--------|------|--|
| (in <sup>4</sup> ) | (in <sup>3</sup> ) | (in-k) | (lb) |  |
| 10.537             | 1.514              | 29.92  | 725  |  |

# **Torsional Properties**

| J <sup>x1000</sup> | Cw                 | Xo     | m    | Ro   | β     |
|--------------------|--------------------|--------|------|------|-------|
| (in <sup>4</sup> ) | (in <sup>6</sup> ) | (in)   | (in) | (in) |       |
| 0.471              |                    | -0.761 |      |      | 0.966 |



#### **General Notes**

- 1. Physical properties and load tables have been calculated in conformance with the 2001 NASPEC for the Design of Cold-Formed Steel Structural Members, including the 2004 Supplement, and the IBC 2006, unless noted otherwise.
- 2. All structural framing members have a protective coating conforming to ASTM C 955.
- 3. Reference ASTM specification A 1003/A 1003 M table 1 for the universe of allowable coatings for light gauge steel framing.
- 4. Stud/joists are manufactured to custom lengths. Stud/joists are manufactured with punched webs unless otherwise specified at time of order.
- 5. Track is produced in standard lengths of 10 feet unless a custom track length is indicated. Track is manufactured with unpunched webs.
- 6. Structural framing members are marked with product information per the requirements of ASTM C 955 section 12.
- 7. All delivered material must be kept dry, preferably by being stored inside a building under a roof. If it is necessary to store material outside, it must be stacked off the ground, properly supported on a level platform, and fully protected from the weather. Reference ASTM C 754 section 8 and ASTM C 1007 section 4.

#### **LEED Green Building Credits**

MR Credit 2: Construction Waste Management – MBA steel framing is 100% recyclable.

MR Credit 4: Recycled Content – MBA steel framing is formed from no less than 25.5% post-consumer and 6.8% pre-consumer recycled content. MR Credit 5: Regional Materials – MBA has manufacturing facilities in multiple states.

