Sales: (888)248-8076 Fax: (847)680-7883 www.mbastuds.com

Submittal Data - Structural Track

Member Designator


400T200-43

Coating

CP60

Physical Properties

Design Thickness 0.0451 in Mil 43 mil Gauge 18 Gauge Inside Web Width 4.00 in Leg Length 2.00 in Yield Strength 33 ksi



Gross Properties

Gross Properties							
Area	Weight	lx	Sx	Rx	ly	Ry	
(in ²)	(lb/ft)	(in ⁴)	(in ³)	(in)	(in ⁴)	(in)	
0.360	1.23	1.002	0.482	1.668	0.146	0.637	

Effective Properties

Effective Properties (33ksi)							
lxe	Sxe	Ma	Vag				
(in ⁴)	(in ³)	(in-k)	(lb)				
0.811	0.311	6.14	1739				

Torsional Properties

Torsional								
J ^{x1000}	Cw	Xo	m	Ro	β			
(in⁴)	(in ⁶)	(in)	(in)	(in)				
0.244	0.436	-1.224	0.734	2.164	0.680			

General Notes

- 1. Physical properties and load tables have been calculated in conformance with the 2001 NASPEC for the Design of Cold-Formed Steel Structural Members, including the 2004 Supplement, and the IBC 2006, unless noted otherwise.
- 2. All structural framing members have a protective coating conforming to ASTM C 955.
- 3. Reference ASTM specification A 1003/A 1003 M table 1 for the universe of allowable coatings for light gauge steel framing.
- 4. Stud/joists are manufactured to custom lengths. Stud/joists are manufactured with punched webs unless otherwise specified at time of order.
- 5. Track is produced in standard lengths of 10 feet unless a custom track length is indicated. Track is manufactured with unpunched webs.
- 6. Structural framing members are marked with product information per the requirements of ASTM C 955 section 12.
- 7. All delivered material must be kept dry, preferably by being stored inside a building under a roof. If it is necessary to store material outside, it must be stacked off the ground, properly supported on a level platform, and fully protected from the weather. Reference ASTM C 754 section 8 and ASTM C 1007 section 4.

LEED Green Building Credits

MR Credit 2: Construction Waste Management – MBA steel framing is 100% recyclable.

MR Credit 4: Recycled Content – MBA steel framing is formed from no less than 25.5% post-consumer and 6.8% pre-consumer recycled content.

MR Credit 5: Regional Materials – MBA has manufacturing facilities in multiple states.

