

Sales: (888)248-8076 Fax: (847)680-7883 www.mbastuds.com

# Submittal Data - Structural Track


Member Designator 400T300-43

Coating CP60

Physical Properties

Design Thickness 0.0451 in Mil 43 mil Gauge 18 Gauge Inside Web Width 4.00 in Leg Length 3.00 in Yield Strength 33 ksi

Note: Flange width-to-thickness ratio exceeds 60. Effective section properties not calculated.



## **Gross Properties**

Gross Properties								
Area	Weight	lx	Sx	Rx	ly	Ry		
(in <sup>2</sup> )	(lb/ft)	(in⁴)	(in <sup>3</sup> )	(in)	(in <sup>4</sup> )	(in)		
0.451	1.53	1.384	0.665	1.753	0.439	0.987		

### **Torsional Properties**

Torsional									
J <sup>x1000</sup>	Cw	Хо	m	Ro	β				
(in <sup>4</sup> )	(in <sup>6</sup> )	(in)	(in)	(in)					
0.306	1.313	-2.097	1.210	2.906	0.479				

#### **General Notes**

- 1. Physical properties and load tables have been calculated in conformance with the 2001 NASPEC for the Design of Cold-Formed Steel Structural Members, including the 2004 Supplement, and the IBC 2006, unless noted otherwise.
- 2. Drywall framing members have a protective coating conforming to ASTM spec A 653/A 653M, G-40 min, or equivalent corrosion resistance.
- 3. Reference ASTM specification A 1003/A 1003 M table 1 for the universe of allowable coatings for light gauge steel framing.
- 4. Drywall framing members are marked with product information per the requirements of ASTM C 645 section 14.
- 5. All delivered material must be kept dry, preferably by being stored inside a building under a roof. If it is necessary to store material outside, it must be stacked off the ground, properly supported on a level platform, and fully protected from the weather. Reference ASTM C 754 section 8 and ASTM C 1007 section 4.
- 6. Drywall framing [nonstructural 25 gauge, 22 gauge and 20 gauge] is not permitted in load bearing (i.e. axial load greater than 200 lbs.) or exterior applications (i.e. transverse load greater than 10 PSF). Reference ASTM C 645 section 3.2.2.

#### **LEED Green Building Credits**

MR Credit 2: Construction Waste Management – MBA steel framing is 100% recyclable.

MR Credit 4: Recycled Content – MBA steel framing is formed from no less than 25.5% post-consumer and 6.8% pre-consumer recycled content.

 $\label{lem:manufacturing} \mbox{MR Credit 5: Regional Materials} - \mbox{MBA has manufacturing facilities in multiple states}.$ 

