
SOFFIT PANEL





ARCHITECTURAL COMMERCIAL INDUSTRIAL PANEL

CONCEALED FASTENED

12" COVERAGE SOFFIT, FASCIA, WALL OR LINER APPLICATIONS

OPEN FRAMING OR SOLID SUBSTRATE

PANEL OVERVIEW

- ► Finishes: Standard:PVDF, MS Colorfast45® and Acrylic-Coated Galvalume®
- Corrosion Protection: AZ55 per ASTM A 792 for unpainted Galvalume®

AZ50 per ASTM A 792 for painted Galvalume®

G90 per ASTM A 653 for Galvanized

- ► Gauges: 26 ga and 24 ga and 22 ga
- ▶ 12" panel coverage, 1" panel depth
- ▶ Panel Length: 26 ga: 5' maximum and 5' minimum


24 ga: 20' maximum and 5' minimum

22 ga: 20' maximum and 5' minimum

- ► Applies over open framing or solid substrate
- Concealed, direct fastened panel for soffit, fascia, wall and liner applications

Panels can be installed horizontally or vertically

► Tongue-and-groove sidelap




TESTING AND APPROVALS

- ▶ UL 263 Fire Resistance Rating per assembly
- ► ASTM E 283 Air Leakage 0.25 cfm/ft² at 6.24 psf
- ► ASTM E 331 Water Penetration none at 12 psf
- ► ASTM E 330 Structural Performance
- ► 2020 FBC Approval FL9482.5 and FL40263.1

াটি Metal Sales

SOFFIT PANEL





SECTION PROPERTIES									ALLOWABLE UNIFORM LOADS, psf For various fastener spacings											
Ga	Width in	V: - I - I	14/-1-1-4	Top In Compression Bottom In Compression			Inward Load						Outward Load							
		Yield ksi	Weight psf	lxx	Sxx in³/ft	lxx in⁴/ft	Sxx in³/ft	iliwalu Loau					Outward Load							
		KOI	Poi	in⁴/ft				2'	2.5'	3'	3.5'	4'	5'	2'	2.5'	3'	3.5'	4'	5'	
26	12	50	0.94	0.0130	0.0226	0.0290	0.0339	144	100	74	55	42	27	-	-	-	-	-	-	
24	12	50	1.23	0.0189	0.0338	0.0410	0.0480	178	129	97	75	60	40	55	55	55	55	55	-	
22	12	50	1.62	0.0278	0.0520	0.0560	0.0651	234	170	129	100	80	54	55	55	55	55	55	-	

- 1. Theoretical section properties have been calculated per AISI 2016 'North American Specification for the Design of Cold-Formed Steel Structural Members'. Ixx and Sxx are effective section properties for deflection and bending.
- 2. Allowable load is calculated in accordance with AISI 2016 specifications considering bending, shear, combined bending & shear and deflection. Allowable load does not address web crippling, fasteners, support material or load testing. Allowable load considers the three or more equal spans condition. Panel weight is not considered.
- 3. Deflection consideration is limited by a maximum deflection ratio of L/180 of span.
- 4. Allowable loads do not include a 1/3 stress increase for wind.

াটি Metal Sales

metalsales.us.com

Anchorage, AK 866.640.7663 Bay City, MI 888.777.7640 Deer Lake, PA 800.544.2577 Denver, CO 800.289.7663 Detroit Lakes, MN 888.594.1394 Fontana, CA 800.782.7953 Fort Smith, AR 877.452.3915 Independence, MO 800.747.0012 Jacksonville, FL 800.394.4419 Jefferson, OH 800.321.5833 Mocksville, NC 800.228.6119 Nashville, TN 800.251.8508 Rock Island, IL 800.747.1206 Rogers, MN 800.328.9316 Seattle, WA 800.431.3470 Sellersburg, IN 800.999.7777 Sioux Falls, SD 888.299.0024 Spokane, WA 800.572.6565 Temple, TX 800.543.4415 Woodland, CA 800.759.6019