





Streamline[®] OilShield[®] Coated Copper Tube comes coated with an orange layer of seamless, grooved polyethylene. Commonly used with the distribution of specific flammable liquids, OilShield[®] coated copper tube provides all the performance and reliability for which Streamline[®] copper tube is known but with the added advantage of high visibility, easy identification and enhanced protection by isolating the copper tube from corrosive environments common with petrochemical distribution and production. The grooved coating provides an internal channel/path that helps in recognizing and detecting any unforeseen leaks.



Standard Features

- UL Listed to UL971, Nonmetallic Underground Piping for Flammable Liquids
- .025" (minimum) polyethylene coating is extruded onto the copper providing consistent corrosion protection
- Made to ASTM & NFPA Standards
- Continuously marked with size, specification information, manufacturing code & footage every 2 feet
- Custom products & markings available upon request
- Made in Canada

Advantages

- Eliminates the need for continuous on-site tape wrapping or sleeving, creating a savings on labor & professional looking installation
- Coated tube is suitable for direct burial in concrete slabs
- Compatible with standard solder fittings & brazing techniques (alternative joining systems must comply to manufacturer's specs)
- Manufactured to reduce work hardening & stress corrosion cracking
- Provides protection against galvanic reaction



Installation



1. Cut and fold back plastic cover to reveal the copper tube

2. Install solder fittings in accordance with manufacturer's instructions and local codes

Note: If using a blowtorch, take care to keep the flame away from the plastic cover



3. When the joint is complete and cool, replace the plastic coat and wrap the joint to give continuity of protection

Note: 3M[™] Scotchrap[™] Tape 50, Shurtape® PW100 or comparable alternative is recommended to wrap the joint.

Mueller Industries' OilShield[®] meets the applicable requirements of the following codes:

- UL Listed to UL971, Nonmetallic Underground Piping for Flammable Liquids
- NFPA 31 Standard for the Installation of Oil-Burning Equipment
- International Residence Code 2006*
- CAN/CSA B139*
- Uniform Mechanical Code
- International Fuel Gas Code 2006*

Copper

- Copper Alloy is seamless UNS C12200 grade.
- Third party certified by Intertek Testing Services

Polyethylene

- · Available in orange for fuel oil applications
- Coating is grooved along tube for enhanced leak protection
- Low density polyethylene (LDPE) resin, contains
 UV inhibitors
- Meets ICC requirements for minimum thickness for corrosion protective sheathing
- Operating temperatures are in the range of 0°F -180°F with the coating remaining flexible down to -40°F.
- Provides adequate barrier to prevent galvanic





Polyethylene-Coated Copper Tube

r oryettiylene oblated oopper rube								
		ТҮРЕ К		TYPE L		COATED ACR		REFRIGERATION
Nom Dia.	O.D. Dia.	Lengths	Soft Coils	Lengths	Soft Coils	Туре К	Type L	Soft Coils
1/4"	3/8"	-	60 ft., 100 ft.	-	60 ft., 100 ft.	-	-	50 ft., 100 ft., 250 ft.
3/8"	1/2"	-	60 ft., 100 ft.	-	60 ft., 100 ft.	-	-	50 ft., 100 ft., 250 ft.
1/2"	5/8"	20 ft.	60 ft., 100 ft.	20 ft.	60 ft., 100 ft.	20 ft.	20 ft.	50 ft., 100 ft., 250 ft.
5/8"	3/4"	20 ft.	60 ft., 100 ft.	20 ft.	60 ft., 100 ft.	20 ft.	20 ft.	50 ft., 100 ft.
3/4"	7/8"	20 ft.	60 ft., 100 ft.	20 ft.	60 ft., 100 ft.	20 ft.	20 ft.	50 ft., 100 ft.
1"	1-1/8"	20 ft.	60 ft., 100 ft.	20 ft.	60 ft., 100 ft.	20 ft.	20 ft.	50 ft., 100 ft.
1-1/4"	1-3/8"	20 ft.	60 ft., 100 ft.	20 ft.	60 ft., 100 ft.	20 ft.	20 ft.	-
1-1/2"	1-5/8"	20 ft.	-	20 ft.	-	20 ft.	20 ft.	-
2"	2-1/8"	20 ft.	-	20 ft.	-	20 ft.	20 ft.	-

A BRAND OF MUELLER INDUSTRIES



The following are the three elements that cover the language needed for engineering specifications to allow the use of OilShield in petrochemical applications.

Part 1 – General

- 1.1 Summary
 - A. OilShield[®] copper tube provides protection against corrosive environments and abrasive damage through a .025" minimum wall thickness of Polyethylene LDPE resin.
 - B. OilShield copper tube is continuously marked with size, specification information, manufacturing code and footage every two feet.
 - C. UL Listed to UL971, Nonmetallic Underground Piping for Flammable Liquids

Part 2 – Materials

2.1 Materials General

- A. All material applicable to the production of OilShield copper tube meets corresponding requirements for ASTM and NFPA codes and standards along with CAN/CSA B139.
- 2.2 OilShield Material
 - A. Copper Tube
 - 1. Refrigeration Standard Copper Tube manufactured with UNS C12200 Copper Alloy.
 - B. Polyethylene Coating
 - 1. Color coated orange to establish use with petrochemical applications
 - 2. Coating is a low density polyethylene LDPE resin which enhances common corrosion protection associated with standard petrochemical production and distribution environments.
 - 3. Coating is grooved along tube to provide enhanced leak protection.
 - 4. Contains UV inhibitors to minimize derogation if exposed to ultra violate light.
 - 5. Extruded seamlessly onto copper tubing with a minimum wall thickness of .025"
 - 6. Operating temperature is in the range of 0°F 180°F
 - 7. Polyethylene coating will remaining flexible down to -40°F.
 - 8. Provides an adequate barrier between dissimilar metals to prevent galvanic corrosion.

Part 3 – Installation

- 3.1 Installation and Usage
 - A. OilShield tube should be installed and used in accordance with appropriate specifications and codes or based upon Mueller Industries technical recommendations.



Technical Information



DOW DFDA-7059 NT 7

Linear Low Density Polyethylene Resin

DOW DFDA-7059 NT 7 Linear Low Density Polyethylene Resin is an ethylene-butene copolymer which is supplied in pelleted form. It is generally recommended for slot cast thin film applications requiring both clarity and toughness. It is excellent in coextruded, slot cast stretch wrap. This resin is also suitable for use in drip irrigation and hose and tube applications.

Main Characteristics

- High clarity
- High tensile strength
- High elongation
- Good puncture resistance
- Complies with U.S. FDA 21 CFR 177.1520(c) 3.1a. Consult the regulations for complete details.

Slip Additive:	None
Antiblock Additive:	None

Properties⁽¹⁾

Typical Physical Test Method			Values(English (S.I.)		
Melt Index,		ASTM D 1238			
(I ₂) at 190°C/2.16 kg, g/10 min			2.0		
Density, g/cc		ASTM D 792	0.918		
Film ⁽²⁾ , 1mil (25 µm)					
Dart Impact(Method A), g		ASTM D 1709			
Method A			70		
Elmendorf Tear (Method B), g	MD	ASTM D 1922	50		
	CD		400		
Ultimate Tensile, psi (MPa)	MD	ASTM D 882	5,000(34)		
	CD		3,600(25)		
Ultimate Elongation, %	MD	ASTM D 882	450		
	CD		850		
Gloss, 45°		ASTM D 2457	92		
Haze, %		ASTM D 1003	2.5		

Fabrication Conditions For Cast Film:

- Extrudable by conventional slot cast film extrusion equipment with only minor machine modifications necessary for optimum use.
- Melt Temperature: 520°F (270°C)

(1) These are typical properties only and are not to be construed as specifications. Users should

- confirm results by their own tests.
- (2) Film properties are typical of slot-cast film extruded at 520°F (270°C).



Product Stewardship	and use its product philosophy by which appropriate steps to program rests with	Company and its subsidiaries ("Dow") has s, and for the environment in which we liv h we assess the safety, health, and enviro p protect employee and public health and each and every individual involved with D sale, disposal, and recycle of each product	e. This concern is the basis onmental information on our our environment. The succ ow products — from the init	for our Product Stewardship products and then take ess of our Product Stewardship		
Customer Notice	products from the s ways for which they reasonable technic	urages its customers to review both their r tandpoint of human health and environme v are not intended or tested. Dow personn al support. Dow product literature, includir rent safety data sheets are available from	ental quality to ensure that I lel are available to answer y ng safety data sheets, shou	Dow products are not used in your questions and to provide		
Medical Applications Policy	 NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS: Dow will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for: a. long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours (or for PELLETHANE™ Polyurethane Elastomers only, which exceeds 30 days); b. use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices); c. use as a critical component in medical devices that support or sustain human life; or d. use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction. 					
	Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted.					
	Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.					
Disclaimer	NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.					
	NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.					
Additional Information	North America U.S. & Canada: Mexico:	1-800-441-4369 1-989-832-1426 +1-800-441-4369	Europe/Middle East	+800-3694-6367 +32-3-450-2240		
	Latin America Argentina:	+54-11-4319-0100	South Africa	+800-99-5078		
	Brazil: Colombia: Mexico:	+55-11-5188-9000 +57-1-219-6000 +52-55-5201-4700	Asia Pacific	+800-7776-7776 +60-3-7958-3392		
www.dowplastics.com	Published October 2 © 2007 The Dow Ch					

