

Product Data Sheet

7032 series (61AJB, 61BJB)

Acrylic Elastomeric Patching Compound



Description: 7032 series (Hempel 61AJB and 61BJB) is an acrylic, water-borne, elastomeric patching compound. It is available in textured and smooth versions.

Recommended use: 7032 series is used to detail cracks and construction joints in masonry walls.

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

7032-03 (61AJB99980)	White (textured)	1-gallon
7032-04 (61BJB99980)	White (smooth)	1-gallon

Physical constants:

Adhesion	5 lbs/in	ASTM D903
Weight/gallon	13.5 lbs/gal	ASTM D1475
Weight solids	81%	ASTM D4209
Volume solids	69%	Calculated
VOC	75 g/l	EPA Method 24
Viscosity	Paste	ASTM D562
Flash point	> 212°F/100°C	ASTM D3278
Dry time, 75°F/23°C, 50% relative humidity (60 wet mils)	4 hours	ASTM D5895

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

Application method: Knife or trowel
Cleaning of tools: Water

Safety: Handle with care. Avoid contact with bare skin. Wear gloves to prevent contact. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

Surface preparation: According to Neogard system Guide Specifications.

Subsequent coat: According to Neogard system Guide Specifications.

Storage temperature: Store in a cool area (75°F/23°C). Must be stored above freezing (32°F/0°C).

Product Data Sheet

7032 series (61AJB, 61BJB)

Acrylic Elastomeric Patching Compound



Note: **7032 series is for professional use only.**

Issued by: Hempel (USA) – 61AJB, 61BJB

This Product Data Sheet (“PDS”) relates to the supplied product (“Product”) and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the “Additional Documents”):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information)

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above.

In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com.

Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product.

The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com.
NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 7032-PDS ksk 04122021.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com