

# Chemical Resistance Chart

70611 series (475JB)

Aromatic Urethane

**Rating Key: 0=No Effect; 1=Stains/Dulls Film; 2=Swells Film; 3=Blisters/Lifts Film**  
Ratings are based on 7-day spot test.

Chemical	Rating	Chemical	Rating
Acetic Acid (5%)	2	Isopropyl Alcohol	1
Acetic Acid (10%)	2	Jet Fuel	1
Acetic Acid (36%)	3	Lactic Acid (20%)	2
Ammonia (28%)	0	Lactic Acid (50%)	3
Brake Fluid	2	Lactic Acid (85%)	3
Butoxyethanol	2	Methylisobutyl Ketone	1
Butoxyethylacetate	2	Methylpyrrolidione	3
Butyl Alcohol	2	Mineral Spirits	0
Butylacrylate	3	Motor Oil	0
Calcium Chloride (10%)	0	Nitric Acid (5%)	1
Diacetone Alcohol	1	Oleic Acid	2
Ethyl Acetate	2	Phosphoric Acid (10%)	1
Ethyl Alcohol	2	Propylene Glycol	0
Ethylene Glycol	0	Restaurant Grease	2
Formic Acid (38%)	3	Sodium Hydroxide (10%)	0
Hydrobromic (48%)	3	Soya Oil	0
Hydrochloric Acid (5%)	1	Sulfuric Acid (5%)	1-2
Hydrochloric Acid (15%)	1	Sulfuric Acid (10%)	3
Hydrochloric Acid (37%)	3	Tall Oil Fatty Acid	2

Issued by: Hempel (USA) – 70611 series CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. 70611-CRC ksk 09022021.docx

Neogard<sup>®</sup>, a part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - [www.neogard.com](http://www.neogard.com)