## **Product Data Sheet**

## 70613-CA (476JB) Aromatic Roofing Urethane, SCAQMD-Compliant



**Description:** 70613-CA (Hempel 476JB) is a single-component, moisture-cured, aromatic polyurethane.

**Recommended use:** As weather-protective topcoats for polyurethane foam, concrete, metal and single-ply roof

systems, and as a base coat for metal roofs.

Features: Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

Certificates/approvals: LEED: MRc5, SSc7.2

CRRC: 0720-0003 UL: TGFU.R6034

**Availability:** Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70613-CA (476JB16640) White 55- and 5-gallon

**Physical constants:** 

ASTM D412 Tensile strength 1,500 psi Elongation ASTM D412 360% Permanent set <10% ASTM D412 Tear resistance 100 lb/in **ADTM D1004** Water resistance <3% ASTM D471 **ASTM D2240** Shore A 70-75 SRI 101 **ASTM E1980** Fire resistance Pass (as part of a system) ASTM E108

 Weight/gallon
 11.2 lbs/gal
 ASTM D1475

 Weight solids
 80%
 ASTM D4209

 Volume solids
 75%
 Calculated

 VOC
 47 g/L
 EPA Method 24

 Flash point
 78°F/25°C
 ASTM D3278

Shelf life 1 year

Cure time at 75°F/23°C and 50% 24 hours

relative humidity RH TT-S-0023OA

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further

technical information can be found at www.neogard.com.

**Application details:** 

Application method: Roller or spray (contact Neogard for spray equipment information)

Thinner (max.vol.): Acetone (10%)

Mix for 3–5 minutes before applying

Cleaning of tools: Acetone

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels

on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or

national safety regulations.

**Surface preparation:** According to Neogard Guide Specifications.

**Application conditions:** Substrate temperature must be above 40°F/5°C and/or below 100°F/37°C, and more than 5°F/3°C

above the dewpoint and rising.

**Preceding coat:** According to Neogard Guide Specifications.

**Subsequent coat:** According to Neogard Guide Specifications.

Issued: September 2021 Page: 1/2

## **Product Data Sheet**

## 70613-CA (476JB) Aromatic Roofing Urethane, SCAQMD-Compliant



Accelerators and additives: 7922 (990JB00000): Vertical additive, enhances sag resistance.

7931 (9905500000): Fast accelerator for use in low humidity environments.

7986 (994JB00000): Odor mask, synthetic vanilla scent.

7987 (995JB00000): Odor mask, orange scent.

Storage temperature: Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.

Remarks: Product may yellow or discolor when exposed to UV light. Product is sensitive to moisture; not

recommended for constant immersion. Concrete must have a full 28 day cure period prior to coating. Not compatible with asphaltic compounds. Not for use with insulating concrete such as

Zonolite, Vermiculite, Perlite, etc. Not for use over aluminized coated roofs.

Note: 70613-CA is for professional use only.

Issued by: Hempel (USA) – 476JB

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the "Additional Documents"):

No. Document Description

- 1 PDS
- 2 Guide Specification
- 3 Application Manual
- 4 Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information )

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 70613-CA-PDS ksk 09302021.docx

Neogard®, a part of Hempel 2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Issued: September 2021 Page: 2/2