

Chemical Resistance Chart

70630 (473JB)

Aromatic Urethane

Rating Key: 0 = No Effect; 1 = Softens Film; 2 = Stains/Dulls Film; 3 = Blisters/Lifts Film
Ratings are based on 7-day spot test.

Chemical	Rating	Chemical	Rating
Acetic Acid (5% wt)	2	Jet Fuel	0
Acetic Acid (36% wt)	2	Lactic Acid (20% wt)	2-3
Acetic Acid (10% wt)	2	Lactic Acid (50% wt)	2-3
Ammonia Hydroxide, 10-35% wt	0	Lactic Acid (85% wt)	2-3
Brake Fluid	1-3	Methylisobutyl Ketone (MIBK)	0
Butoxyethanol, Butyl Cellosolve	2	Mineral Spirits	0
Butoxyethylacetate, EB Acetate	1-2	Motor Oil	0
Butyl Alcohol, N-Butanol	2	Nitric Acid (5% wt)	2-3
Butylacrylate	2	N-Methylpyrrolidione	2
Calcium Chloride (10% wt)	0	Oleic Acid	3
Diacetone Alcohol, 4-Hydroxy-4-Methyl-2-Pentanone (>98%)	3	Phosphoric Acid (10% wt)	1-2
Ethyl Alcohol, Ethanol	2	Propylene Glycol	0
Ethylene Glycol	0	Restaurant Grease (Canola Oil)	0
Formic Acid (38% wt)	0	Sodium Hydroxide (10% wt)	1-2
Hydrochloric Acid (5% wt)	1-3	Soya Oil	0
Hydrochloric Acid (15% wt)	1-3	Sulfuric Acid (5% wt)	2
Hydrochloric Acid (37% wt)	1-3	Sulfuric Acid (10% wt)	2
Hydrobromic Acid (48% wt)	2-3	Tall Oil Fatty Acid (TOFA)	2-3
Isopropyl Alcohol	2		

Issued by: Hempel (USA) – 70630 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. 70630-CRC ksk 09022021.docx