

Product Data Sheet

7401 (47KJB)

Modified Aromatic Urethane



| | |
|-------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Description: | 7401 (Hempel 47KJB) is a single-component, moisture-cured, modified polyurethane. |
| Recommended use: | As a waterproofing membrane between slabs or in below-grade applications. Areas include below-grade slabs, parking garages, balconies, plaza decks, and planters. |
| Features: | Meets South Coast Air Quality Management District (SCAQMD) VOC requirements. |
| Availability: | Available in North America. Not included in Group Assortment; other regions must confirm. |

Colors and packaging:

| | | |
|--------------------------------------------------------------|-------|----------|
| 7401 (47KJB19990) | Black | 5-gallon |
| <i>Special order item only. Contact Neogard for details.</i> | | |

Physical constants:

| | | |
|------------------|--------------------|---------------|
| Tensile strength | 250 psi | ASTM D412 |
| Elongation | 500% | ASTM D412 |
| Permanent set | 25% | ASTM D412 |
| Water resistance | <3% | ASTM D471 |
| MVT at 60 mils | 0.60 English perms | ASTM E96 |
| Shore A | 30–40 | ASTM D2240 |
| Adhesion | 200 psi | ASTM D4541 |
| Weight/gallon | 10.2 lbs/gal | ASTM D1475 |
| Weight solids | 92% | ASTM D4209 |
| Volume solids | 88% | Calculated |
| VOC | 98 g/L | EPA Method 24 |
| Viscosity | 97 KU | ASTM D562 |
| Flash point | 108°F/ | ASTM D3278 |
| Shelf life | 12 months | |

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Application details:

| | |
|---------------------|--------------------------------------------------|
| Application method: | Roller or squeegee |
| Thinner (max.vol.): | Do not thin |
| Mixing: | Mix for a minimum of 3–5 minutes before applying |
| Cleaning of tools: | Hempel's Thinner 08080 (xylene) |

| | |
|----------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Safety: | Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations. |
|----------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

| | |
|--------------------------------|----------------------------------------------------------------|
| Application conditions: | Substrate temperature must be between 40°F/4°C and 110°F/43°C. |
|--------------------------------|----------------------------------------------------------------|

| | |
|------------------------|--------------------------------------------|
| Preceding coat: | According to Neogard Guide Specifications. |
|------------------------|--------------------------------------------|

| | |
|------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Accelerators and additives: | 7986 (994JB00000): Odor mask, synthetic vanilla scent. 7922 (990JB00000): Vertical additive, enhances sag resistance. 7923 (9505300000): Accelerator for single component urethanes. 7931 (9905500000): Fast accelerator for use in low humidity environments. |
|------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

| | |
|-----------------------------|-------------------------------------------------------------------------------------|
| Storage temperature: | Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C. |
|-----------------------------|-------------------------------------------------------------------------------------|

Product Data Sheet

7401 (47KJB)

Modified Aromatic Urethane



Note: **7401 is for professional use only.**

Issued by: Hempel (USA) – 47KJB

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the "Additional Documents"):

| No. | Document Description |
|-----|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 1 | PDS |
| 2 | Guide Specification |
| 3 | Application Manual |
| 4 | Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information) |

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT.

7401-PDS ksk 07092021.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com