

Product Data Sheet

FC7548/FC7964 — Integrally Textured Aliphatic Urethane 47TJB: Base 47TJ9 : Curing Agent 949JB



Description:	FC7548/FC7964 (Hempel 47TJB) is an integrally textured, two-component, fast-cure, high solids, aliphatic urethane.
Recommended use:	As a waterproofing membrane wear coat or topcoat for pedestrian traffic surfaces, designed for applications where fast turnaround time and/or solvent-free materials are required. Suitable areas include stadiums, balconies, plaza decks, walkways, rooftop recreation areas, and mechanical rooms.
Features:	Integrally textured—aggregate is already added to the material. Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.
Certificates/approvals:	LEED: MRc5, IEQc4.2, SSc7.1 Miami-Dade: NOA No.: 14-0902.10, NOA No. 15-0616.03
Availability:	Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

FC7548 (47TJ916650)	Gray	2-gallon
FC7548-03 (47TJ923820)	Tan	2-gallon
FC7548-41 (47TJ916680)	Charcoal	2-gallon
FC7548-58 (47TJ961300)	Dark Maple	2-gallon
FC7964 (949JB00000)	Clear	1-gallon

Some standard colors and/or packaging may have extended lead times and/or minimum quantities. Contact Neogard for additional colors.

Physical constants:

Tensile strength	2,000 psi	ASTM D412
Elongation	130%	ASTM D412
Permanent set	<10%	ASTM D412
Tear resistance	155 pli	ASTM D1004
Water resistance	<2% at 7 days	ASTM D471
MVT at 20 mils	1.0 English Perm	ASTM E96
Taber abrasion	95 mg/1,000 CS-17	ASTM D4060
Shore A	80–90	ASTM D2240

Peel adhesion:		
70714/70715	16.3 lbs/in	
7780/7781	6.2 lbs/in	
FC7510/FC7961	8.2 lbs/in	
FC7500/FC7960	16.1 lbs/in	ASTM D903
FC 7530/7963	12.6 lbs/in	
FC7540/FC7964	13.5 lbs/in	
70410	16.5 lbs/in	
7430	12 lbs/in	

Weight/gallon (mixed)	10.407 lbs/gal ± 0.25	ASTM D1475
Weight solids (mixed)	93% ± 2.0%	ASTM D5201
Volume solids (mixed)	90% ± 1.0%	ASTM D5201
VOC (mixed)	<100 g/L	ASTM D5201
Viscosity (mixed)	100 KU	ASTM D2196
Flash point, FC7548		Refer to SDS
Flash point, FC7964		Refer to SDS
Cure to recoat at 75°F/23°C, 50% relative humidity	3-5 hours	ASTM D5895

The above tested results are typical values. Individual lots may vary. Further technical information can be found at www.neogard.com.

Product Data Sheet

FC7548/FC7964 — Integrally Textured Aliphatic Urethane
47TJB: Base 47TJ9 : Curing Agent 949JB



Application details:

Version, mixed product	47TJB
Mixing ratio:	Base 47TJ9 : Curing Agent 949JB 2 : 1 by volume
Mixing instructions:	Pre-mix base for 3–5 minutes before adding curing agent. Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.
Application method:	Squeegee or roller (do not dip and roll from container)
Thinner (max.vol.):	Hempel's 08710 or Acetone may be added not to exceed 5% by vol. or 6 oz/gal
Accelerator:	At 40°F, 0.6 oz/gal of 99055 (See Cure Chart).
Pot life:	60 minutes at 75°F/23°C
Cleaning of tools:	Acetone or other VOC compliant multi-purpose solvents. Confirm compliance with Local, State and Federal air quality rules before use.
Safety:	Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.
Application conditions:	Substrate temperature must be between 40°F/4°C and 110°F/32°C.
Preceding coat:	According to Neogard Guide Specifications.
Storage temperature:	Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.
Remarks:	Not recommended for constant immersion. Do not apply over asphaltic compounds. For on-grade applications, substrates constructed over unvented metal decks or between-slab applications, contact Neogard Technical Service.

Note: **FC7548/FC7964 is for professional use only.**

Issued by: Hempel (USA) – 47TJB

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the "Additional Documents"):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information)

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT.

FC7548-FC7964-PDS ksk 07092021.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com