



RhinoMat® 1000 a 40 mil (1.0 mm) thick, polyethylene Reinforced Composite Geomembrane (RCG), specifically designed for use in water retention and containment applications to **Weld Easier. Install Faster. Contain Better.**™ For applications where retention and containment are critical, the durable, stress crack resistant, lightweight construction of RhinoMat® 1000 provides maximum performance in many different climates and environmental conditions.

RhinoMat® 1000 Applications:

- Containment:**

 - Agriculture & Aquaculture
 - Mining & Energy
 - Secondary Containment
- Retention:**

 - Wastewater Lagoons
 - Landfill Covers
 - Golf Course Ponds
 - Stormwater Management
 - Irrigation Storage
 - Canal Liners
 - Potable Water Reservoirs

RhinoMat® 1000 conforms to the properties below, and is manufactured at an Owens Corning facility having achieved ISO 9001:2000 certification. Owens Corning tests RhinoMat® 1000 both through independent, third party laboratories, and through internal quality control testing in laboratories accredited through the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST/METHOD	TYPICAL VALUE¹		MIN AVE. ROLL VALUE²	
		English	Metric	English	Metric
Weight	ASTM D5261	20.8 oz./yd²	705 g/m²	20.3 oz./yd²	688 g/m²
Thickness	ASTM D751	40 mil	1.01 mm	36 mil	0.92 mm
Strip Tensile Strength (MD)	ASTM D7003	303 lbf	1348 N	285 lbf	1268 N
Strip Tensile Strength (CD)	ASTM D7003	265 lbf	1179 N	259 lbf	1152 N
Strip Tensile Elongation (MD)	ASTM D7003	22%		20%	
Strip Tensile Elongation (CD)	ASTM D7003	22%		20%	
Tongue Tear (MD)	ASTM D5884	60 lbf	302 N	50 lbf	222 N
Tongue Tear (CD)	ASTM D5884	62 lbf	334 N	50 lbf	222 N
CBR Puncture	ASTM D6241	1400 lbf	6228 N	1360 lbf	6050 N
Index Puncture Resistance	ASTM D4833	242 lbf	1076 N	220 lbf	979 N
Hydrostatic Resistance	ASTM D751	740 lb/in²	5102 kPa	707 lb/in²	4875 kPa
Dimensional Stability³	ASTM D1204	2.86%			
Water Vapor Transmission³	ASTM E96	0.08 g/m²·day			
UV Resistance (Fluorescent Light Method)⁴	ASTM D7238				
a) Strength & Elongation retained after 10,000 light hours	ASTM D7003	> 90% retained		> 90% retained	
b) Response to bending	GRI GM-16	no cracking		no cracking	
Grab Tensile Strength (MD)	ASTM D751	463 lbf	2504 N		
Grab Tensile Strength (CD)	ASTM D751	397 lbf	1766 N		
Trapezoidal Tear (MD)	ASTM D4533	73 lbf	325 N		
Trapezoidal Tear (CD)	ASTM D4533	69 lbf	307 N		
Seam Strength (Shear)⁵	ASTM D7747	165 lbf	734 N		
Seam Strength (Peel)⁶	ASTM D7747	30 lbf	133 N		
Hydraulic Conductivity	ASTM E96 ('B')	1.0 x 10⁻¹⁴ cm/sec			
Carbon Black Content	ASTM D4218	> 2%			
Accelerated UV Weathering⁷	ASTM G154	> 90% @ 10,000 hrs.			
Low Temperature Brittleness	ASTM D2136	Pass (@ -60°F)	Pass (@ -51°C)		
Standard Roll Width		12 ft	3.7 m		
Standard Roll Length		1250 ft	381 m		
Approximate Roll Weight		2200 lb	998 kg		

Notes:
¹Typical values represent an average test result for the sample size, with + 10% variance
²Minimum Average Roll Values (MARV) are shown (unless otherwise noted), in accordance with GRI-GM30
³Dimensional Stability and Water Vapor Transmission values shown are maximum test result values
⁴Test samples were exposed to UV radiation using this method prior to evaluating changes in material properties
⁵Test values reflect single-track wedge welding at approximately 750° F and 14 ft/sec
⁶Test values reflect single-track wedge welding at approximately 750° F and 14 ft/sec
⁷Test valued based on A-340 lamps, 8 hours UV @ 60° C, 4 hours condensation @ 40° C

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Owens Corning does not warrant its accuracy or completeness. The user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. Owens Corning specifically disclaims all warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.

Contact your RhinoMat® Sales Representative at:

Toll Free: 800.567.9727 | Email: RhinoMat@OwensCorning.com
OwensCorning.com/RhinoMat

© 2017 Owens Corning. All Rights Reserved.

Pub. No. 10021426-C
RM1000_TDS
July 2017



RhinoMat® 1000

WELD EASIER. INSTALL FASTER. CONTAIN BETTER.™

For water retention, containment, aquaculture,
pond and canal lining applications

GRI-GM30
COMPLIANT

BE WATER SMART.

RhinoMat® 1000 is a 40 mil (1.0 mm) geomembrane specifically designed for use in water retention and containment applications to **Weld Easier. Install Faster. Contain Better.**™ For applications where containment is critical, the durable, stress crack resistant, lightweight construction of RhinoMat® geomembrane provides maximum performance in all climates and environmental conditions.

RhinoMat® 1000 is a Smart Choice

Features Strong Construction

- 40 mil (1.0 mm), our thickest geomembrane
- Inner woven core layer provides dimensional stability with impressive tensile and tear strength
- Puncture, abrasion and chemical resistant construction
- Outstanding hydrostatic resistance
- All layers contain UV protection

Meets Industry Standards


- GRI-GM30 Compliant – RhinoMat is the first portfolio of products to meet this standard
- Non-toxic, no PVC or other hazardous materials used in the construction of the geomembrane
- Impressive UV, ozone and oxidation resistance

Provides Warranty Protection

- Standard warranty: 20-years buried, 10-years exposed
- Available special registered warranty (clear water applications): 25-years buried, 20-years exposed



**ENGINEERED
LLDPE/LDPE COATING**
For flexibility, chemical resistance and protection against UV, ozone and oxidation



**HDPE HIGH STRENGTH
WOVEN CORE**
For outstanding dimensional strength and stability



UV resistant SurFlex™ technology provides excellent welding characteristics, reduces stress cracking and makes it easy to seam in the factory or field

WELD EASIER.



- Made with SurFlex™ technology, a polyolefin blend surface film which allows for superior thermal fusion welding
- Designed for optimal welding temperature and speed to create exceptional seams
- Flexible construction enables efficient seaming of a wide variety of panel shapes and sizes

INSTALL FASTER.



- Wide width flexible sheets facilitate factory fabrication to reduce field seaming time
- Factory fabricated seaming capability ensures higher quality welds which require fewer time-consuming destructive field tests
- Allows for large factory fabricated panels to be customized to accelerate project field installation

CONTAIN BETTER.



- High strength woven core and engineered coatings provide outstanding longevity and chemical resistance
- Meets or exceeds properties of Category 1 (Severe) of the GRI-GM30 specification from the Geosynthetic Institute (GSI)
- Hydrostatic, puncture, and abrasion resistance stands up to the toughest installation, maintenance and environmental stresses

