



# SOFTR® Duct Wrap FRK (Canada)



SOFTR® Duct Wrap is a blanket of glass fiber insulation factory-laminated to FRK vapor retarder facing. A 2" (50mm) stapling and taping flange is provided on one edge. This product is designed to meet existing performance standards such as NFPA 90A and 90B and other mechanical and energy codes. SOFTR® Duct Wrap FRK flexible design makes it easy and fast to install, helps prevent duct condensation, and increases building occupants thermal comfort.

- Condensation control
- Enhanced comfort control
- Easy to clean surface
- Flexible and easy to install

- SOFTR® Duct Wrap FRK is used for external insulation of commercial and residential heating, air conditioning and dual-temperature ducts operating at temperatures from 40°F (4°C) to 250°F (121°C). This insulation, when applied in accordance with installation instructions (Pub. 10021577), will provide the “installed R-value” as published for the product and printed on the facing, assuring specified in-place thermal performance and condensation control.
- SOFTR® Duct Wrap FRK is not recommended for use on duct systems subject to continuous service at temperatures in excess of 250°F (121°C). It should not be used in conditions where condensation might occur on the facing nor exposed to weathering or mechanical abuse without proper protection. It should not be used on the inside of ducts.

Standard roll width: 48" (1.2m)  
 Installed R (RSI) values: When installed in accordance with recommended installation procedures, SOFTR® Duct Wrap FRK will provide installed R (RSI) values as follows:

Nominal Thickness		Out-of-Package R (RSI) Value <sup>2</sup>		Installed Thickness <sup>3</sup>		Installed R (RSI) Value <sup>2,3</sup>	
in.	mm			in.	mm		
Type 75 – 0.75 pcf (12 kg/m <sup>3</sup> )							
1½	(38)	5.1	(0.90)	1½	(29)	4.2	(0.74)
2.2	(56)	7.4	(1.30)	1½	(42)	6.0	(1.06)
3	(76)	10.0	(1.76)	2¼	(57)	8.3	(1.46)

2. hr·ft<sup>2</sup>·°F/Btu (m<sup>2</sup>·°C/W) at 75°F (24°C) mean temperature.  
 3. Assumes 25% compression of insulation.

Property	Test Method	Value
Operating Temperature	ASTM C 411	up to 250°F (121°C)
Insulation Jacket Temperature Limit	ASTM C 1136	up to 150°F (66°C)
Jacket Puncture Resistance	ASTM C 1136	25 units (0.7 joules)
Water Vapor Permeance	ASTM E 96	0.02 perms
Water Vapor Sorption	ASTM C 1104	<3% by weight at 120°F (49°C), 95% R.H.
Fungi Resistance	ASTM C 1338	Meets requirements
Thermal Conductivity		
Out-of-Package k-Value		
k Btu·in/hr·ft <sup>2</sup> ·°F	Type 75	Type 100
(λ at 24°C Mean, W/m·°C)	0.30	0.27
	(0.043)	(0.039)
	Type 150	Type 150
	0.25	0.23
	(0.036)	(0.033)
Installed (Compressed) k-Value		
k Btu·in/hr·ft <sup>2</sup> ·°F	Type 75	Type 100
(λ at 24°C Mean, W/m·°C)	0.27	0.25
	(0.039)	(0.036)
	Type 150	Type 150
	0.23	0.23
	(0.033)	(0.033)
Surface Burning Characteristics <sup>1</sup>	ASTM E84 and CAN/ULC S102	Flame Spread 25 Smoke Developed 50

1. The surface burning characteristics of these products have been determined in accordance with ASTM E 84. Values are reported to the nearest 5 rating.

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at [www.owenscorning.com](http://www.owenscorning.com).

Out-Of Package Thickness		Installed Thickness		Stretch-Out Dimensions	
in.	(mm)	in.	(mm)	Round and Oval Ducts P+in. (mm)	Square and Rectangular Ducts P+in. (mm)
1½	(38)	1⅞	(29)	P+9½ (240)	P+8 (205)
2¾/16	(56)	1⅞	(41)	P+13 (330)	P+11 (280)
3	(76)	2¼	(57)	P+17 (430)	P+14½ (370)

P = measured duct perimeter

- ASTM C 1290, Flexible Fibrous Glass Blanket Insulation Used to Externally Insulate HVAC Ducts, Type III
- ASTM C 1136, Flexible Low Permeance Vapor Retarders for Thermal Insulation, Type II (facing only)
- ASTM C 553 Mineral Fiber Thermal Insulation: Type I – Fiberglas™ Duct Wrap Type 75; Type II – SOFTR® Duct Wrap FRK Types 100 and 150 (Operating temperatures to 250°F (121°C) and thermal values to 150°F (66°C) mean

4. Preferred specification is ASTM C 1290.

- Certified by SCS Global Services to contain an average of 53% recycled glass content, 31% pre-consumer and 22% post-consumer
- GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit [ul.com/gg](http://ul.com/gg)
- Environmental Product Declaration (EPD) has been certified by UL Environment\*
- Health Product Declaration® (HPD)



Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit [www.SCSglobalservices.com](http://www.SCSglobalservices.com). LEED® is a registered trademark of the U.S. Green Building Council.

**OWENS CORNING INSULATING SYSTEMS, LLC**  
 ONE OWENS CORNING PARKWAY  
 TOLEDO, OHIO, USA 43659  
**1-800-GET-PINK®**  
[www.owenscorning.com](http://www.owenscorning.com)

Pub. No. 10020646-B. Printed in U.S.A. August 2018.  
 THE PINK PANTHER™ & © 1964–2018 Metro-Goldwyn-Mayer Studios Inc.  
 All Rights Reserved. The color PINK is a registered trademark of Owens Corning.  
 © 2018 Owens Corning. All Rights Reserved.

