



GALVANIZED HANGER WIRE SOFT
For Hanging Suspended Ceiling Grid.



Product Specifications

SKU	Gauge	Inch/mm	Tolerance	Length	Weight of Coating*
12HW4100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	4 feet	13 microns
12HW6100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	6 feet	13 microns
12HW8100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	8 feet	13 microns
12HW10100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	10 feet	13 microns
12HW12100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	12 feet	13 microns
12HW14100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	14 feet	13 microns
12HW16100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	16 feet	13 microns
12HW18100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	18 feet	13 microns
12HW20100	12 gauge	0.106"/2.67 mm	±0.0024"/±0.06 mm	20 feet	13 microns

U-Hank Wire Product					
GWU16	16 gauge	0.0620"/1.57mm	±0.0015"/±0.04mm	45 inches	6 microns
GWU18	18 gauge	0.0476"/1.21mm	±0.0015"/±0.04mm	45 inches	6 microns

* Approximate Average

Coil Product		
SKU	Gauge	Inch/mm
8HW1800	8 gauge	0.162"/4.11 mm
9HW1800	9 gauge	0.148"/3.76 mm
12HW1800	12 gauge	0.106"/2.67 mm

Grip-Rite Hanger Wire Meets or Exceeds ASTM A641, Class 1.

Tensile Strength				
	8 gauge	9 gauge	12 gauge	18 gauge
Tensile Strength (PSI)	65-75 KSI	55-65 KSI	55-65 KSI	55-65 KSI
Breaking Strength (PSI)	65-75 KSI	55-65 KSI	55-65 KSI	55-65 KSI

Chemical Composition of Steel				
Carbon %	Silicon %	Manganese %	Phosphorus %	Sulfur %
0.11	0.27	0.37	0.04	0.04

ALL PRIMESOURCE WIRE IS MANUFACTURED IN ISO 9002 AND ISO 14001 CERTIFIED AND APPROVED FACTORIES TO PRIMESOURCE PERFORMANCE SPECIFICATIONS.