



**PENCIL ROD**



Commonly a concrete accessory. Used in many different forming applications, battered walls and foundations of unusual width where snapties are not practical.

**Product Specifications**

SKU	Gauge	Inch/mm	Tolerance	Length
14GSCW6	1/4"	0.249"/6.32 mm	±0.003"/±0.1 mm	6 feet
14GSCW8	1/4"	0.249"/6.32 mm	±0.003"/±0.1 mm	8 feet
14GSCW10	1/4"	0.249"/6.32 mm	±0.003"/±0.1 mm	10 feet
14GSCW12	1/4"	0.249"/6.32 mm	±0.003"/±0.1 mm	12 feet
14GSCW20	1/4"	0.249"/6.32 mm	±0.003"/±0.1 mm	20 feet

Weight of Coating (minimum)	
g/m <sup>2</sup>	oz/ft <sup>2</sup>
≥ 25	≥ 0.082
≥ 25	≥ 0.082

Tensile Strength	
1/4" Pencil Rod	65-85 KSI

Chemical Composition of Steel (max values)				
Carbon %	Silicon %	Manganese %	Phosphorus %	Sulfur %
0.04	0.3	0.45	0.035	0.035

ALL PRIMESOURCE WIRE IS MANUFACTURED IN ISO 9002 AND ISO 14001 CERTIFIED AND APPROVED FACTORIES TO PRIMESOURCE PERFORMANCE SPECIFICATIONS.