





**BUGLE HEAD SELF-DRILL SCREW
BLACK PHOSPHATE**
Drywall to Steel

ESR 1408



#2 Reduced Phillips

Product Specifications



Part #	Dia.	Length	TPI	Bulk Qty	Finish	Corrosion	Thread	Head Dia.	Drill Capacity
SD100	6	1	20	10M	Black Phos.	48 hr. min. B-117	FULL	8.0-8.5 mm	.033"-.112"
SD118	6	1-1/8	20	10M	Black Phos.	48 hr. min. B-117	FULL	8.0-8.5 mm	.033"-.112"
SD114	6	1-1/4	20	8M	Black Phos.	48 hr. min. B-117	FULL	8.0-8.5 mm	.033"-.112"
SD158	6	1-5/8	20	5M	Black Phos.	48 hr. min. B-117	FULL	8.0-8.5 mm	.033"-.112"
SD178	6	1-7/8	20	4M	Black Phos.	48 hr. min. B-117	FULL	8.0-8.5 mm	.033"-.112"
SD238	8	2-3/8	18	3M	Black Phos.	48 hr. min. B-117	2"	8.0-8.5 mm	.033"-.112"
SD258	8	2-5/8	18	2M	Black Phos.	48 hr. min. B-117	2"	8.0-8.5 mm	.033"-.112"
SD300	8	3	18	2M	Black Phos.	48 hr. min. B-117	2"	8.0-8.5 mm	.033"-.112"

Pro-Twist drill screws meet or exceed ASTM C-954 and/or C-1513

Dia.	Nominal Screw Dia. (in)	Metal Gauge 1 (Lb)	Tension (Pull) Lbs 1 pc	Shear Lbs. Metal to metal	Minimum Torsional Strength (Lb)
6	0.138	25	128		24
		22	176	449	
		20	263	683	
		18	426	728	
		16	598	1091	
		14	911		
8	0.164	25	97		42
		22	196	580	
		20	285	829	
		18	444	994	
		16	550	1096	
		14	924	1332	
		12	1100	1337	

Ultimate Value Charts

Screws driven into steel were driven with three exposed threads on the off side of the connection, then pulled out with testing machine.

Note that all results were obtained in strict adherence to ASTM test protocol. These ultimate figures are offered only as a guide and are not guaranteed in any way by PrimeSource Building Products. A 4:1 safety ratio is recommended.

Installation Guidelines

0-2500rpm Screwgun with torque adjustment - Overdriving may result in fastener failure or stripout of the work surface. The fastener is fully seated when the head's bearing surface is countersunk in the drywall. The fastener must penetrate beyond the metal a minimum of three threads to comply with the code.

ALL PRIMESOURCE FASTENERS ARE MANUFACTURED IN AN ISO 9002 AND ISO 14001 CERTIFIED AND APPROVED FACTORY TO PRIMESOURCE PERFORMANCE SPECIFICATIONS AND PRINT DRAWINGS.