



PROSOCO®

# Consolideck®

CONCRETE FLOORING PRODUCTS



INDOOR ADVANTAGE GOLD  
BUILDING MATERIALS

# Grind-N-Fill

Liquid Consolideck® Grind-N-Fill mixes with the dust created while grinding concrete floors to create a super-durable matrix that automatically fills pinholes, small air voids and pop-outs, micro-cracks and other gaps in the concrete surface during grinding.

Grind-N-Fill creates a monolithic surface that polishes faster, easier and more effectively. With gaps and imperfections filled, the floors accept hardener/densifiers, protective treatments and color-stains and hardeners more evenly.

Low-odor, VOC compliant Grind-N-Fill also makes floors easier to maintain by eliminating the tiny nooks and crannies in concrete that trap and accumulate soil and other contaminants.

The easy-to-apply treatment dries fast and is suitable for any floor undergoing grinding, from warehouse-industrial to highly polished aesthetic floors.

## ADVANTAGES

- Easy application with pump-up sprayer.
- Automatically fills gaps, voids and pop-outs during grinding operations.
- Quickly cures to concrete hardness.
- Dilutable with clean water to meet a variety of job site and equipment conditions
- Treated surfaces polish faster and easier.
- Protective treatments, colorants and other applications go on more smoothly and evenly.
- Treated floors are easier to maintain; less likely to trap dirt and other contaminants.
- Complies with all known AIM VOC regulations.
- Conforms to leading green building standards and code criteria.

## Limitations

- Do not freeze.

## TYPICAL TECHNICAL DATA

<b>FORM</b>	milky liquid, mild odor
<b>SPECIFIC GRAVITY</b>	1.01
<b>pH</b>	8.9
<b>WT/GAL</b>	8.40 lbs
<b>VOC CONTENT</b>	100 g/L
<b>FLASH POINT</b>	>212° F (>100° C)
<b>FREEZE POINT</b>	32° F (0° C)
<b>SHELF LIFE</b>	2 years in tightly sealed, unopened container

## REGULATORY COMPLIANCE

### VOC Compliance

Consolideck® Grind-N-Fill is compliant with the US Environmental Protection Agency's AIM VOC regulations.

Visit [www.prosoco.com/voccompliance](http://www.prosoco.com/voccompliance) to confirm compliance with individual district or state regulations.

## SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job site controls during application and handling.

**24-Hour Emergency Information:**  
**INFOTRAC at 800-535-5053**

# Product Data Sheet

## Consolideck® Grind-N-Fill

### PREPARATION

Protect people, vehicles, property, plants and all adjacent or nearby surfaces not designed to receive lithium densifier from the product, splash and wind drift. Use polyethylene or other proven protective material.

### Surface and Air Temperatures

Surface and air temperatures should be at least 50° F (10° C) and below 90° F (32° C) during application.

### Equipment

Apply using low-pressure, pump-up sprayer.

### Storage and Handling

Keep from freezing. Store in a cool, dry place. Always seal container after dispensing. Do not alter or mix with other chemicals. Published shelf life assumes upright storage of factory-sealed containers in a dry place. Maintain temperatures of 40–100° F (4–38° C). Do not double stack pallets. Dispose of in accordance with local, state and federal regulations.

### APPLICATION

Read “Preparation” and the Safety Data Sheet before use.

**ALWAYS TEST** each surface for suitability and results before overall application. Use the following application instructions. Let surface dry thoroughly before inspection.

### Dilution & Mixing

Apply as packaged. Do not dilute or alter, or use other than as specified.

Stir material thoroughly before application.

If diamonds gum up or glaze over, dilute Grind-N-Fill with up to 50 percent clean water. This may also help on concrete slabs that are hot and dry.

### Typical Coverage Rates

Coverage varies based on substrate porosity and texture. Always test. Typical coverage is:

- 200–400 sq. ft. per gallon.
- 19–37 sq. m. per gallon

### Application Instructions

Consolideck® Grind-N-Fill should be applied close to or during the final stage of metal grinding operations, or the first stages of resin-bound grinding, but **BEFORE** polishing and hardening/densifying.

Always test to determine best practices for job site conditions. Test an approximately 4 square-foot area representative of the floor to be ground. Check to see that Grind-N-Fill smoothly and evenly fills spaces in the concrete. During testing, also check to see if diamonds are gumming up or glazing over.

1. If the grinder is connected to a vacuum hose, disconnect it. Disconnecting the vacuum prior to application helps get dust into the product for a smooth, thick filler.
2. Apply Grind-N-Fill by low-pressure pump-up sprayer on the floor immediately in the grinder's path. Coat floor up to 10 feet or less in front of the grinder. Spread with a soft-bristle push broom. Saturate the floor, but do not create puddles.
3. Grind the wet floor until dry. Check to see the floor the grinder has just gone over is dry before moving on during grinding operations. Ensure the grinder reaches treated areas before Grind-N-Fill dries.  
If the floor shows signs of turning black, product application is too thick. Correct by applying clean water with a low-pressure sprayer and grinding off excess product.
4. Let the floor dry 2–12 hours for maximum curing.
5. Reconnect vacuum hose (if needed) and continue grinding and polishing.

The preceding instructions are guidelines that can be modified for specific equipment, job site conditions or personal experience.

### Dry Time

Let the floor dry 2–12 hours for maximum curing. Longer dry times are recommended for maximum cure.

### Cleanup

Clean tools and equipment with soap and water.



# Product Data Sheet Consolideck® Grind-N-Fill

## WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product

to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

## CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Call Customer Care at 800-255-4255, or visit our website at [prosoco.com](http://prosoco.com), for the name of the PROSOCO representative in your area.

