

## Consolideck® LS™ followed by Three Applications of Consolideck® <sup>LS</sup>Guard™ Chemical Resistance Testing Summary

For PROSOCO, Inc. October 2008

AMT Laboratories • 3741 Greenway Circle • Lawrence, Kansas 66046 • (888) 376-3600

## TEST METHODS: Stain Resistance - ASTM D 1308

The treatment was applied in accordance with PROSOCO, Inc. Product Data Sheet instructions and allowed to cure for 7 days prior to testing. The soiling agents were allowed to dwell on the treated and untreated substrates for times of 1 hour and 15 minutes. Evaluation consisted of a visual examination of the tested areas to determine the effect the reagent had on the sample using the following scale:

E = Excellent (No Adverse Effects)

G = Good (Limited Adverse Effects)

F = Fair (Moderate Adverse Effects)

P = Poor (Unsatisfactory)

Acids	Effect 15 min.	Effect 1 Hour	Bases	Effect 15 min.	Effect 1 Hour
10% Citric	G	G	5% Ammonium Hydroxide	Е	Е
10% Acetic	Е	G	30% Ammonium Hydroxide	Е	G
10% Oxalic	G	F	10% Potassium Hydroxide	G	G
10% Hydrochloric	G	Р	45% Potassium Hydroxide	G	G
35% Hydrochloric	G	Р	10% Sodium Hydroxide	G	G
10% Phosphoric	G	G	50% Sodium Hydroxide	G	G
70% Phosphoric	Е	G			
10% Sulfuric	G	G	Solvents		
50% Sulfuric	Р	Р	Acetone	G	G
			Mineral Spirits	G	G
Alcohols			Xylene	G	G
Benzyl Alcohol	Р	F	MEK	G	G
Ethyl Alcohol	Е	F			
Isopropyl Alcohol	Е	Е	Hydraulic Fluids / Oils / Fuels		
Methyl Alcohol	Е	Е	Gasoline	G	G
Ethylene Glycol	Е	Е	Brake Fluid	Е	E
			Motor Oil	G	G
Salts			Automatic Transmission Fluid	Е	E
Ammonium Chloride	Е	G	Skydrol	G	G
Calcium Chloride	G	G			
Sodium Bicarbonate	G	G	Other Chemicals / Misc.		
Sodium Chloride	Е	G	Cola	Е	E
Sodium Carbonate	Е	Е	Mustard	Е	G
			Ketchup	E	Е
			Red Wine	G	G
			Balsamic Vinegar	G	G
			Vegetable Oil	G	G
			Bleach (Sodium Hypochlorite)	Е	Е
			Tap Water	Е	Е
			Laundry Detergent (Tide)	Е	Е
			Lemon Juice	G	G