



PROSOCO®

Consolideck®

CONCRETE FLOORING PRODUCTS



PolishGuard

Consolideck® PolishGuard is a durable, protective coating that dramatically increases the stain resistance of interior concrete floors. This non-yellowing formulation enhances the appearance of standard gray, integrally colored, dyed, stained or color-hardened concrete floors. If preferred, treated surfaces may be burnished to produce a high-gloss finish.

PolishGuard is ideal for steel-troweled, burnished, polished or decorative concrete and cement terrazzo floors that are exposed to accidental spills of food products, household cleaners and industrial solutions.

ADVANTAGES

- Produces a long-lasting, tough protective shine on any interior concrete flatwork.
- Perfect for floors hardened/densified with Consolideck® LS®, LS/CS® or Blended Densifier.
- Adds depth and luster to colored concrete, including surfaces decorated with Consolideck® GemTone Stain or ColorHard.
- Keeps soiling and contaminants from penetrating, making maintenance cleaning faster, more effective and more economical.
- Treated floors maintain slip resistance.
- Low odor. Easy to apply. Fast drying.
- Treated surfaces “breathe” – doesn’t trap moisture.
- UV stable. Will not yellow, discolor, peel or flake.
- VOC Compliant. Non-flammable. Non-toxic. Water-based.

Limitations

- Only for use on indoor, horizontal concrete surfaces.
- Not for use around pools or fountains.
- Will not compensate for structural defects. Surfaces must be clean and in good repair before application.

TYPICAL TECHNICAL DATA

FORM	White milky liquid
SPECIFIC GRAVITY	1.01
pH	8.4
WT/GAL	8.50 lbs
ACTIVE CONTENT	15%
TOTAL SOLIDS	15%
VOC CONTENT	100 g/L maximum
FLASH POINT	>200° F (>93° C)
FREEZE POINT	32° F (0° C)
SHELF LIFE	2 years in tightly sealed, unopened container

REGULATORY COMPLIANCE

VOC Compliance

Consolideck® PolishGuard is compliant with the US Environmental Protection Agency’s AIM VOC regulations.

Visit www.prosoco.com/voccompliance to confirm compliance with individual district or state regulations.

SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job-site controls during application and handling.

24-Hour Emergency Information:
INFOTRAC at 800-535-5053

Product Data Sheet

Consolideck® PolishGuard

PREPARATION

Protect people, vehicles, property, plants and all surfaces not set to receive PolishGuard from product, splash and wind drift. Use polyethylene or other proven protective material. PolishGuard may be applied to existing, cured concrete of any age.

Surfaces must be clean, dry, absorbent and structurally sound. Remove all foreign materials including bond breakers, curing agents, surface grease and oil, and construction debris using the appropriate PROSOCO surface prep cleaner.

Follow the appropriate cleaner with thorough water rinsing. If a d-limonene based cleaner/stripper is used, clean treated surfaces with PROSOCO's Cleaner/Degreaser and rinse thoroughly.

Acid-stained concrete must be thoroughly neutralized and rinsed prior to application.

Application may begin as soon as prepared surfaces are dry.

Surface and Air Temperatures

Temperatures for application should be 40–100° F (4–38° C).

Equipment

Apply with low-pressure sprayer and a microfiber pad. Do not atomize.

Storage and Handling

Keep from freezing. Store in a cool, dry place. Always seal container after dispensing. Do not alter or mix with other chemicals. Published shelf life assumes upright storage of factory-sealed containers in a dry place. Maintain temperatures of 40–100°F (4–38°C). Do not double stack pallets. Dispose of in accordance with local, state and federal regulations.

APPLICATION

Read "Preparation" and the Safety Data Sheet before use.

ALWAYS TEST a small area of each surface to confirm suitability, coverage rate and desired results before beginning overall application. Include in the test area any previous repairs and patches, including aesthetic cementitious finishes. Different surface compositions may result in absorption and/or appearance differences. Test with the same equipment, recommended surface preparation and application procedures planned for general application. Let surface dry thoroughly before inspection.

Dilution & Mixing

Do not dilute or alter. Use as supplied. Mix well before use.

Typical Coverage Rates

Variations in surface texture, concrete quality, porosity, job-site conditions, temperature and relative humidity affect coverage rates and drying times. Calculate coverage rate by testing a representative section of the finished concrete surface using the following instructions. The following figures are for estimating only.

Estimated Coverage Rates

- 400–2,000 square feet per US gal
- 10–49 square meters per Liter

Maximum stain resistance is achieved at overall coverage rates of 400–800 sq.ft. per gallon applied in two thin coats. Two thin applications achieve better results than one heavy coat.

Calculating Project-Specific Target Coverage Rate

1. Prepare the test area using the information in the Preparation section.
2. Add 1-gallon of PolishGuard to a clean, pump-up sprayer fitted with a 0.5 gpm conical or fan spray tip. Apply according to the following Application Instructions. Repeat as needed for the desired level of finish.
3. Measure the test area and the amount of PolishGuard applied to establish the Target Coverage Rate per gallon. Protect the completed test area from moisture for at least 4 hours.

Application Instructions

PolishGuard may be applied to broomed, steel troweled, honed, polished or highly polished interior concrete surfaces. For best results, treat floors with PROSOCO's LS®, LS/CS® or Blended Densifier before application.

1. Lightly wet a clean microfiber pad with PolishGuard, leaving the pad damp.
2. Spray-apply using a clean, pump-up sprayer fitted with a 0.5 gpm conical or fan spray tip. Work from one control joint to another.
3. Spread with the damp microfiber pad. Maintain a thin, even coating and wet edge. Stop spreading once drying begins. Do not overlap. Use two people – one spraying and one spreading – for best results.
4. Allow to dry tack free, typically 20–60 minutes.
5. Repeat steps 1–4. Two thin coats are recommended for maximum protection and shine.

Product Data Sheet

Consolideck® PolishGuard

For increased gloss, wait at least 60 minutes after the final coat is applied, then use a high-speed burnisher fitted with a white polishing pad. Burnish at a fast walking pace. This is an optional step.

Drying Time

Protect from water for 4 hours. At 72°F [22°C] and 40% relative humidity, product dry times are:

- *To Touch*: 30–60 minutes
- *Light Foot Traffic*: 4 hours
- *Normal traffic*: overnight

Consolideck® PolishGuard gains its full stain repellency properties in 7 days.

Cleanup

Before product dries, clean tools and equipment with fresh water. Immediately wash off over spray from glass, aluminum, polished or other surfaces with fresh water.

Maintenance

Sweep the floor daily with a microfiber pad or dry dust mop. When needed, dry buff with a high-speed burnisher and a white pad to refresh the gloss.

PolishGuard improves the resistance of concrete floors to staining. However, acidic substances, including foods, may etch and stain. Clean ALL spills as quickly as possible.

Use PROSOCO's LSKlean or DailyKlean for maintenance cleaning. LSKlean contains lithium-silicate for improving surface density and preserving the surface sheen of Consolideck® floors. Do not use other cleaners, including off-the-shelf and common household cleaners, which may contain acidic or alkaline ingredients that can dull the finish of Consolideck® floors.

To restore maximum shine to high traffic areas, repeat Application Instructions steps 1–5 in affected areas.

WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support. Factory-trained representatives are established in principal cities throughout the continental United States. Call Customer Care at 800-255-4255, or visit our website at prosoco.com, for the name of the PROSOCO representative in your area.