



PROSOCO®

Sure Klean®

CLEANING & PROTECTIVE TREATMENTS

Vana Trol®

Sure Klean® Vana Trol® is an acidic cleaner for new masonry surfaces that are subject to vanadium, manganese and other metallic stains. Vana Trol® is designed to simplify rinsing and reduces potential for efflorescence.

TYPICAL TECHNICAL DATA

FORM	Clear, amber liquid pungent odor
SPECIFIC GRAVITY	1.11
pH	0.65 @ 1:4 dilution 0.82 @ 1:10 dilution
WT/GAL	9.20 lbs
FREEZE POINT	<-22° F (<-30° C)
SHELF LIFE	3 years in tightly sealed, unopened container

REGULATORY COMPLIANCE

VOC Compliance

Sure Klean® Vana Trol® is compliant with all national, state and district AIM VOC regulations.

SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job site controls during application and handling.

24-Hour Emergency Information:
INFOTRAC at 800-535-5053

ADVANTAGES

- Clings to masonry surface, and softens excess mortar and job dirt.
- Supplied in concentrate for easy on-site dilution.
- Slow-drying so it rinses clean without streaking.

- Controls green vanadium and brown manganese staining on color-sensitive brick and tile.
- Removes efflorescence on new brick, concrete block, and stone construction.
- Safe for use on most unpolished natural stone or cast stone.
- Designed for use with colored mortar.

Limitations

- Repeated applications may leave a detergent residue. To reduce potential for detergent residue: always prewet; rinse thoroughly; do not exceed two applications.
- May cause color loss when used on Thin Brick or Concrete Brick. Always test a small area for suitability and desired results before overall application.
- Not effective for removing atmospheric dirt and black carbon stains. Use the appropriate Sure Klean® restoration cleaner to remove atmospheric staining from older masonry.
- May damage exposed low-E glass treatments; acrylic and polycarbonate sheet glazing; and glazing with surface-applied reflective, metallic or other synthetic coatings and films. Modern soft coat or hard coat low-E glass is not intended to be on the external face of the glass and should not be exposed to or adversely affected by proper cleaning. Always test for adverse effects prior to overall application. If testing is not feasible or indicates adverse effects, such substrates must be protected.

PREPARATION

Clean masonry before installing non-masonry materials such as windows, doors, finished flooring, metal fixtures, hardware, light fixtures, roofing materials, etc. that the cleaner could harm. If cleaning is to be completed after installation of materials not intended to be treated or exposed to Vana Trol®, test all substrates not intended to be treated with Vana

Product Data Sheet

Sure Klean® Vana Trol®

Trol® before full scale application. If testing is not feasible or indicates adverse effects, protect substrates from product splash, residue, wind drift and fumes with PROSOCO's Strippable Masking or polyethylene prior to application.

All caulking and sealant materials should be in place and thoroughly cured before cleaning.

When applying to exteriors of occupied buildings, make sure all windows, exterior intake and air conditioning vents are covered and air handling equipment is shut down during application.

Construction soiling and mortar residues on new brick and tile surfaces clean most effectively if the cleaning is done within 14–28 days of

installation. Mortar and grout smears left on the surface longer result in a more difficult clean down and may cause undesirable results. Cleaning high-strength mortar/grout within seven days improves results.

The presence of excessive moisture in the wall contributes to efflorescence and other staining. Always protect open wall cavities from rain during construction.

When working over traffic, clean when traffic is at a minimum. Protect or divert traffic if necessary.

Surface and Air Temperature

For best results, clean when air and masonry surface temperatures are 40°F (4°C) or above. Cleaning when temperatures are below freezing or will be overnight may harm masonry. If freezing conditions existed before application, let the masonry thaw.

Equipment

Use low-pressure spray (50 psi max) or densely-packed, soft-fibred masonry-washing brush. Do not apply with pressure spray above 50 psi. Such application will drive the chemicals deep into the surface making it difficult to rinse completely. Transport and store in a cool, dry place.

Rinse with enough water and pressure to flush spent cleaner and dissolved soiling from the masonry surface and surface pores without damage. Inadequate rinsing leaves residues which may stain the cleaned surface.

Masonry-washing equipment generating 400–1000 psi with a water flow rate of 6–8 gallons per minute is the best water/pressure combination for rinsing porous masonry. Use a 15–45° fan spray tip. Heated water (150–180°F; 65–82°C) may improve cleaning efficiency. Use adjustable equipment for reducing water flow-rates and rinsing pressure as needed for sensitive surfaces. Rinsing pressures greater than 1000 psi and fan spray tips smaller than 15° may permanently damage sensitive masonry. Water flow-rates less than 6 gallons per minute may reduce cleaning productivity and contribute to uneven cleaning results.

Storage and Handling

Store in a cool, dry place with adequate ventilation. Vapors and liquid can damage a variety of metals and fabrics. Do not alter or mix with other chemicals. Always seal container after dispensing. Published shelf life assumes

Recommended for these substrates. Always test. Coverage is in sq.ft./m. per gallon.			
Substrate	Type	Use?	Coverage
Architectural Concrete Block*	Burnished+	yes	
	Smooth	yes	500–900 sq.ft.
	Split-faced	yes	46–84 sq.m.
	Ribbed	yes	
Concrete+	Brick	yes	
	Tile	yes	500–900 sq.ft.
	Precast Panels	yes	46–84 sq.m.
	Pavers	yes	
	Cast-in-place	yes	
Fired Clay	Brick	yes	
	Tile	yes	600–900 sq.ft.
	Terra Cotta (unglazed)	yes	56–84 sq.m.
	Pavers	yes	
Marble, Travertine, Limestone	Polished	no	N/A
	Unpolished	yes	600–900 sq.ft. 56–84 sq.m.
Granite	Polished	yes	800–1000 sq.ft. 74–93 sq.m.
	Unpolished	yes	700–1000 sq.ft. 65–93 sq.m.
Sandstone	Unpolished	yes	600–900 sq.ft. 56–84 sq.m.
Slate	Unpolished	yes	700–1000 sq.ft. 65–83 sq.m.
*Sure Klean® Custom Masonry Cleaner may be a more appropriate product. +Sure Klean® Light Duty Concrete Cleaner may be a more appropriate product. Repeated application may damage surfaces. Always perform a test panel of each surface to confirm suitability, proper dilution rates and desired results before overall application. Coverage estimates depend on surface texture and porosity.			

Product Data Sheet

Sure Klean® Vana Trol®

upright storage of factory-sealed containers in a dry place. Maintain temperature of 45–100°F (7–38°C). Do not double stack pallets. Dispose of unused product and container in accordance with local, state and federal regulations.

APPLICATION

Read “Preparation” and the Safety Data Sheet before use. **ALWAYS TEST** a small area of each surface to confirm suitability and desired results before beginning overall application. Test each type of masonry and each type of stain. Test with the same equipment, recommended surface preparation and application procedures planned for general application. Let test area dry 3–7 days before inspection and approval. Make the test panel available for comparison throughout cleaning project.

Dilution

Dilute Vana Trol® with 4–10 parts clean water to one part concentrate, based upon test results. Always pour cold water into empty bucket first, then carefully add cleaner. Never use hot water. Handle in high-density polyethylene or polypropylene containers only. No metal. Acidic materials and fumes attack metal.

Typical Coverage Rates

When calculating the volume of cleaner required for porous, textured surfaces, assume 50 square feet per gallon of prepared cleaner. For dense, smooth surfaces, assume up to 150 square feet per gallon of prepared cleaner. The coverage rate chart assumes an average coverage rate of 100 square feet per gallon of prepared cleaner.

Application Instructions

Exterior Surfaces

Test thoroughly and follow preparation instructions above. Provide adequate ventilation. The following cleaning procedure is recommended unless otherwise indicated during testing:

1. Thoroughly saturate a large portion of the masonry surface with fresh water, working from the bottom to the top.
2. Using a densely-packed, soft-fibered masonry-washing brush or low pressure (50 psi max) spray, apply diluted solution freely.
3. Leave cleaning solution on the wall for about 5 minutes, depending on absorption rate of masonry and drying conditions. Do not let cleaner dry into the masonry. This may leave a residue and cause staining.

4. Reapply cleaning solution and scrape off heavy buildup of excess mortar using a wooden scraper or piece of brick. Take care to avoid damaging the masonry surface. Do not use metal scrapers, which may contribute to metallic staining. To avoid streaking, keep adjacent and lower wall surfaces wet and rinsed free of cleaning residues.

Avoid more than one reapplication over the same area. Repeated applications may cause a white detergent film to be deposited on the masonry surface. If mortar deposits are not softened after the initial application, allow the solution to remain on the wall for a longer period of time, making sure that the cleaner does not dry into the masonry.

5. Rinse thoroughly with fresh water, removing all cleaning compound, free sand, loose material and debris. Rinse from the bottom of the work area to the top. Thorough rinsing is extremely important to ensure that all residues are removed from the porous masonry.

Interior Surfaces

Proper ventilation is necessary. Following the cleaning procedures outlined for exterior surfaces. Rinse thoroughly with fresh water using sponge or soft-fibered brush. If conditions do not allow sufficient water for complete rinsing, use a neutralizing rinse following this procedure:

1. Rinse with clear water.
2. Apply neutralizing rinse of 2 ounces baking soda to 1 gallon of clean water.
3. Saturate. Leave solution on surface 3 to 5 minutes.
4. Apply a final rinse of clear water.

Cleanup

Clean tools and equipment using fresh water.

WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

Product Data Sheet Sure Klean® Vana Trol®

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Field visits by PROSOCO personnel are for the purpose of making technical recommendations only. **PROSOCO is not responsible for providing job-site supervision or quality control.** Proper application is the responsibility of the applicator. Call Customer Care at 800-255-4255, or visit our website at prosoco.com, for the name of the PROSOCO representative in your area

