



# Mason & Mortar Mix Selector Guide

## Products



	Structural Mortar	Non-Load Bearing	Homeowner Non-Structural	Veneer Stone Application	2x Bond Strength	White Color Water Resistant
Attributes	<ul style="list-style-type: none"> <li>Structural block and brick applications</li> <li>Superior workability</li> <li>Above or below grade</li> </ul>	<ul style="list-style-type: none"> <li>Non-structural brick veneer applications</li> <li>Superior workability</li> <li>Above grade only</li> </ul>	<ul style="list-style-type: none"> <li>Type 'N' Mortar</li> <li>General Use</li> <li>Above grade only</li> </ul>	<ul style="list-style-type: none"> <li>Very low sag</li> <li>Use for scratch coat bond coat and grout joints</li> </ul>	<ul style="list-style-type: none"> <li>3200 psi (21.7 MPa) slant shear bond strength</li> <li>Water resistant</li> <li>Dry stack applications</li> <li>Very low sag</li> </ul>	<ul style="list-style-type: none"> <li>Waterproofing additives</li> <li>White color</li> </ul>
Strengths	• 1800 psi (12.4 MPa) at 28 days	• 750 psi (5.2MPa) at 28 days	• 750 psi (5.2MPa) at 28 days	• 1800 psi (12.4 MPa) at 28 days	• 1800 psi (12.4 MPa) at 28 days	• 1800 psi (12.4 MPa) at 28 days
ASTM	ASTM C 270 Type 'S'	ASTM C 270 Type 'N'	ASTM C 270 Type 'N'	ASTM C 270 Type 'S'	ASTM C 270 Type 'S'	ASTM C 270 Type 'S'
Application						
Structural Block Walls	•					
Brick Veneer	•	•	•	•		•
Tuck Point Mortar Joints	•	•	•	•	•	
Manufactured Veneer Stone	•			•	•	
Dry Stack Veneer Stone					•	
Natural Stone	•			•	•	
Barbeques / Planters		•	•			
Glass Block						•
Columns / Pillars	•					
Block Foundations	•					

For SPEC DATA and Guide Specification documents on all our Commercial Grade products, please visit our "On the Job" section at [www.quikrete.com](http://www.quikrete.com)