

PRODUCT CATEGORY: ProSTUD
PRODUCT NUMBER: 162PDS125-18
COATING: G40 (G60/G90 Available)



PHYSICAL PROPERTIES

WEB DEPTH: 1.620 IN
FLANGE HEIGHT: 1.250 IN
DESIGN THICKNESS: 0.019 IN
YIELD: 70 KSI
WEIGHT: 0.29 LB/LFT

GROSS SECTION PROPERTIES

CROSS SECTIONAL AREA (A): 0.086 IN²
MOMENT OF INERTIA (Ix): 0.04 IN⁴
RADIUS OF GYRATION (Rx): 0.685 IN
GROSS MOMENT OF INERTIA (Iy): 0.019 IN⁴
GROSS RADIUS OF GYRATION (Ry): 0.468 IN

EFFECTIVE SECTION PROPERTIES

EFFECTIVE AREA (Ae): 0.039 IN²
MOMENT OF INERTIA (Ix): 0.035 IN⁴
SECTION MODULUS (Sx): 0.028 IN³
ALLOWABLE BENDING MOMENT (Ma): 1194 IN-LBS
ALLOWABLE SHEAR FORCE (Vag): 405 LB
ALLOWABLE SHEAR FORCE (VANET): 149 LB

TORSIONAL PROPERTIES

ST VENANT TORSION CONSTANT (J x 1000): 0.01032 IN⁴
WARPING CONSTANT (Cw): 0.012 IN⁶
DISTANCE FROM SHEAR CENTER TO NEUTRAL AXIS (Xo): -1.105 IN
RADI OF GYRATION (Ro): 1.382 IN
TORSIONAL FLEXURAL CONSTANT (B): 0.361
UNBRACED LENGTH (LU): 24.8 IN

SECTION PROPERTIES TABLE NOTES:

- CALCULATED PROPERTIES ARE BASED ON AISI S100-12, NORTH AMERICAN SPECIFICATION FOR DESIGN OF COLD-FORMED STEEL STRUCTURAL MEMBERS AND AISI S220-15, NORTH AMERICAN STANDARD FOR COLD-FORMED STEEL FRAMING&ldquoNONSTRUCTURAL MEMBERS.
- EFFECTIVE PROPERTIES INCORPORATE THE STRENGTH INCREASE FROM THE COLD WORK OF FORMING AS APPLICABLE PER AISI A7.2.
- TABULATED GROSS PROPERTIES, INCLUDING TORSIONAL PROPERTIES, ARE BASED ON FULL-UNREDUCED CROSS SECTION OF THE STUDS, AWAY FROM PUNCHOUTS
- TABULATED GROSS PROPERTIES, INCLUDING TORSIONAL PROPERTIES, ARE BASED ON FULL-UNREDUCED CROSS SECTION OF THE TRACKS.
- FOR DEFLECTION CALCULATIONS, USE THE EFFECTIVE MOMENT OF INERTIA.
- ALLOWABLE MOMENT INCLUDES COLD WORK OF FORMING.
- ALLOWABLE MOMENT IS TAKEN AS THE LOWEST VALUE BASED ON LOCAL OR DISTORTIONAL BUCKLING. DISTORTIONAL BUCKLING STRENGTH IS BASED ON A K-PHI = 0.
- WEB DEPTH FOR TRACK SECTIONS IS EQUAL TO THE NOMINAL HEIGHT PLUS TWO TIMES THE DESIGN THICKNESS PLUS THE BEND RADIUS. HEMS ON NONSTRUCTURAL TRACK SECTIONS ARE IGNORED

LEED:

- COMPLIES WITH ASTM C955
- LEED CREDITS MR 2: CONSTRUCTION WASTE MATERIAL-RAM STEEL FRAMING IS 100% RECYCLEABLE
- LEED CREDITS MR 4: RAM STEEL FRAMING IS FORMED WITH A MINIMUM 25.5% POST CONSUMER AND 14.4% PRE-CONSUMER CONTENT
- LEED CREDITS MR 5: REGIONAL MATERIALS MAY APPLY

PRODUCT CATEGORY:

ProSTUD

PRODUCT NUMBER

162PDS125-18

COMPOSITE LIMITING HEIGHTS

SPACING INCHES	5 PSF			7.5 PSF			10 PSF		
	L/120	L/240	L/360	L/120	L/240	L/360	L/120	L/240	L/360
12	13' 2"	11' 5"	10' 0"	11' 6"	10' 0"	8' 5"	10' 6"	8' 9"	
16	12' 10"	11' 1"	9' 9"	11' 2"	9' 8"	7' 11"	10' 2"	8' 4"	
24	11' 10"	10' 3"	8' 6"	10' 4"	8' 5"		9' 2"		

COMPOSITE TABLE NOTES:

- ALLOWABLE COMPOSITE LIMITING HEIGHTS WERE DETERMINED IN ACCORDANCE WITH ICC-ES AC86-2015.
- ADDITIONAL COMPOSITE WALL TESTING AND ANALYSIS REQUIREMENTS OF THE SFIA CODE COMPLIANCE CERTIFICATION PROGRAM WERE OBSERVED.
- IN ACCORDANCE WITH CURRENT BUILDING CODES AND AISI DESIGN STANDARDS, THE 1/3 STRESS INCREASE FOR STRENGTH WAS NOT USED.
- THE COMPOSITE LIMITING HEIGHTS PROVIDED IN THE TABLES ARE BASED ON A SINGLE LAYER OF 5/8" TYPE X GYPSUM BOARD FROM THE FOLLOWING MANUFACTURERS: AMERICAN, CERTAINTED, GEORGIA PACIFIC, CONTINENTAL, NATIONAL, PABCO, AND USG.
- THE GYPSUM BOARD MUST BE APPLIED FULL HEIGHT IN THE VERTICAL ORIENTATION TO EACH STUD FLANGE AND INSTALLED IN ACCORDANCE WITH ASTM C754 USING MINIMUM NO. 6 TYPE S DRYWALL SCREWS SPACED AS LISTED BELOW:
- SCREWS SPACED A MINIMUM OF 16 IN. O.C. TO FRAMING MEMBERS SPACED AT 16 IN. OR 12 IN. O.C.
- SCREWS SPACED A MINIMUM OF 12 IN. O.C. TO FRAMING MEMBERS SPACED AT 24 IN. O.C.
- NO FASTENERS ARE REQUIRED FOR ATTACHING THE STUD TO THE TRACK EXCEPT AS DETAILED IN ASTM C754.
- STUD END BEARING MUST BE A MINIMUM OF 1 INCH.
- F ADJACENT TO THE HEIGHT VALUE INDICATES THAT FLEXURAL STRESS CONTROLS THE ALLOWABLE WALL HEIGHT.
- S ADJACENT TO THE HEIGHT VALUE INDICATES THAT SHEAR/END REACTION CONTROLS THE ALLOWABLE WALL HEIGHT.

NON-COMPOSITE LIMITING HEIGHTS

SPACING INCHES	5 PSF			7.5 PSF			10 PSF		
	L/120	L/240	L/360	L/120	L/240	L/360	L/120	L/240	L/360
12	9' 9"	7' 9"	6' 9"	8' 6"	6' 9"	5' 11"	7' 9"	6' 2"	5' 4"
16	8' 10"	7' 0"	6' 2"	7' 9"	6' 2"	5' 4"	7' 0"	5' 7"	4' 10"
24	7' 9"	6' 2"	5' 4"	6' 9"	5' 4"	4' 8"	6' 2"	4' 10"	4' 3"

NON-COMPOSITE TABLE NOTES

- HEIGHTS ARE BASED ON AISI S100-12, NORTH AMERICAN SPECIFICATION AND AISI S220-15, NORTH AMERICAN STANDARD FOR COLD-FORMED STEEL FRAMING NONSTRUCTURAL MEMBERS, USING STEEL PROPERTIES ALONE.
- ABOVE LISTED NON-COMPOSITE LIMITING HEIGHTS ARE APPLICABLE WHEN THE UNBRACED LENGTH IS LESS THAN OR EQUAL TO L_U.
- HEIGHTS ARE LIMITED BY MOMENT, DEFLECTION, SHEAR, AND WEB CRIPPLING (ASSUMING 1' END REACTION BEARING).
- WEB STIFFENERS ARE REQUIRED AT BEARING POINTS.