
DURA+SKRIM® 2FR & 10FR

FIRE RETARDANT FOUR-LAYER REINFORCED LAMINATE



PRODUCT DESCRIPTION

DURA♠SKRIM® 2FR and 10FR consist of two sheets of high-strength fire-retardant virgin film laminated together with a third layer of molten polyethylene. A heavy-duty scrim reinforcement placed between these plies greatly enhances tear resistance and increases service life. DURA♠SKRIM's fire-retardant films meet or exceed NFPA's 701



test, method 2 (Large Scale Requirements).

PRODUCT USE

DURA SKRIM® 2FR and 10FR are used in applications that require a fire-retardant material, and demand high puncture and tear strengths.

SIZE & PACKAGING

DURA SKRIM® 2FR and 10FR stock sizes are 6 and 20 feet wide by 100 feet long; they are also available in a variety of custom widths with minumum order quantities.



Building Abatement Enclosure

PRODUCT PART

APPLICATIONS

Construction Enclosures Temporary Walls

Asbestos Abatements Curtains

Fumigation Covers Job Site Coverings



DURA+SKRIM® 2FR & 10FR

FIRE RETARDANT FOUR-LAYER REINFORCED LAMINATE

| | | DURA♦SKRIM 2FR | | DURA♦SKRIM 10FR | |
|---|-------------------------|--|----------------------------------|---|----------------------------------|
| PROPERTIES | TEST METHOD | IMPERIAL | METRIC | IMPERIAL | METRIC |
| APPEARANCE | | Translucent, White Color | | Translucent, White Color | |
| THICKNESS, NOMINAL | | 6 mil | 0.15 mm | 10 mil | 0.25 mm |
| WEIGHT | | 18.5 lbs/MSF 2.7 oz./yd ² | 90 g/m² | 40.5 lbs/MSF 5.8 oz./yd ² | 198 g/m² |
| Construction | | Extrusion laminated with scrim reinforcement | | | |
| ² 1" Tensile Strength | ASTM D7003 | 45 lbf/in | 79 N/cm | 57 lbf/in | 100 N/cm |
| ² Elongation at Film Break | ASTM D7003 | 400 % | 400 % | 500 % | 500 % |
| ² Grab Tensile | ASTM D7004 | 55 lbf | 245 N | 75 lbf | 334 N |
| ¹ Trapezoid Tear | ASTM D4533 | 30 lbf | 133 N | 44 lbf | 196 N |
| Mullen Burst | ASTM D751 | 38 psi | 262 kPa | 75 psi | 517 kPa |
| MAXIMUM STATIC USE TEMPERATURE | | 180° F | 82° C | 180° F | 82° C |
| MINIMUM STATIC USE TEMPERATURE | | -70° F | -57° C | -70° F | -57° C |
| WVTR | ASTM E96 Procedure B | 0.587 grains/(100in ² ·day) | 0.590 g/(m².day) | 0.214 grains/(100in²-day) | 0.202 g/(m²·day) |
| Perm Rating | ASTM E96 Procedure B | 0.086 Perms grains/(ft²-hr·in Hg) | 0.057 Perms g/(24hr·m²·mm Hg) | 0.031 Perms grains/(ft²-hr·in Hg) | 0.021 Perms g/(24hr·m²·mm Hg) |
| BURNING CHARACTERISTICS FLAME SPREAD INDEX SMOKED DEVELOPED VALUE | ASTM E84 Procedure A | 5 20 | | 5 55 | |

¹ Tests are an average of diagonal directions.

MEETS OR EXCEEDS THE FOLLOWING FIRE TESTING:

- 1. National Fire Protection Association (NFPA) 701, Test Method 2 (Large Scale)
- 2. Class "A" Wall & Ceiling Finish Category as given in the National Fire Protection Association Life Safety Code 101, "Interior Wall and Ceiling Finish Classification" (ASTM E-84-97a).



DURA♦SKRIM® 2FR & 10FR are fire-retardant four-layer reinforced extrusion laminates. The outer layers consist of a high quality polyethylene film with a high concentration of fire-retardant additives. DURA♦SKRIM® 2FR & 10FR are reinforced with a heavy duty scrim laid in a diagonal pattern spaced 3/8" apart with an additional machine direction scrim every 9" (R5CCF) and 3" (R10CCF) across the width. The individual plies are laminated together with molten polyethylene. DURA♦SKRIM® 2FR & 10FR are designed to meet the stringent requirements of the Boston Fire Department for Temporary Enclosures.



download technical

data sheets.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. RAVEN INDUSTRIES MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.RavenEFD.com



P.O. Box 5107 Sioux Falls, SD 57117-5107 Ph: +1 (605) 335-0174 • TF: +1 (800) 635-3456



² Tests are an average of primary reinforcement directions.