

TECHNICAL DATA SHEET

DESCRIPTION

Banner Guard® barricade tapes are an effective way to limit entry to hazardous or restricted areas

Banner Guard® Super Strength II® conforms to the following safety codes:

- OSHA 29 CFR Part 1910.144 - Safety Color Codes for Marking Physical Hazards
- ANSI Z535.1 - Safety Color Codes
- ISO 3864 - Safety Colours and Safety Signs
- OSHA 29 CFR Part 1926.502 (G) - Controlled Access Zones

PHYSICAL PROPERTIES AND TYPICAL VALUES

PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
Thickness Overall	D-2103	11 MIL	0.28 MM
Weight	D-2103	35.5 LBS/1000 FT ²	17.3 KG/100 M ²
3" Tensile	D-882	400 LBF	1780 N
		12000 PSI	82.7 MPA
Elongation	D-882	20 %	20 %
PPT Resistance	D-2582	28 LBF	124.5 N
Printability	D-2578	≥ 40 Dynes	≥ 40 Dynes

FEATURES AND BENEFITS

- Warn against hazardous areas by containing and alerting people of hazardous or restricted areas. Perfect for crime scenes, fire scenes, dangerous work areas, crowd control, open trenches, construction sites, wet floors, wet paint, overhead dangers, ski and race track boundaries, etc.
- Attention-getting message repeats warning continuously in bold black letters.
- Tough, durable and lightweight, yet strong enough to be used over and over again.
- Easy application and removal. Tape quickly wraps around poles, trees, and barrels; it can be stapled or nailed to posts, walls or barricades to establish a highly visible barrier with the appropriate message. Banner Guard® is the fast, effective way to identify and define areas with restricted entry.
- Made from reusable non-adhesive pigmented polyethylene. Manufactured for durability and resistance to the elements while being an environmentally friendly, heavy metal free product.

OUR CUSTOMERS DON'T JUST *cover their business,*
➤ THEY PROTECT IT



REEF INDUSTRIES, INC.
 9209 Almeda Genoa Rd. • Houston, Texas 77075
 P: 713.507.4251 • F: 713.507.4295
 E-mail: ri@reefindustries.com • www.reefindustries.com

TOLLFREE 1.800.231.6074

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.