

Alpha Genie Base Coat

100% acrylic leveling base coat

COLOR

Off white prior to addition of Portland

PACKAGING

5 gallon pail (19 liters)

60 lbs. (27.2 kg)

COVERAGE PER PAIL

Leveling

1/8" (3.2mm) Thick: 110 ft² (10m²)

1/4" (6.4mm) Thick: 55 ft² (5m²)

Mesh Embedment

Flexguard 4: 280 ft² (26 m²)

Coverage rates vary depending on porosity of substrates and application techniques.

SHELF LIFE

Two (2) years, properly stored in original containers

VOC

Less than 50 g/l, or 0 lbs/gal less water and exempt solvent.

DESCRIPTION

Alpha Genie is a 100% acrylic fiber reinforced base coat that is field mixed with Type I, 1L or I-II Portland cement to produce a cementitious leveling base coat for Senergy systems or a leveling agent for masonry and concrete substrates

USES

For leveling masonry, stucco, and other cementitious substrates and for Senergy reinforcing mesh embedment as part of Senergy Wall Systems.

ADVANTAGES

Easy 1:1 mixing ratio that reduces change or error.

High build fiber reinforced achieves excellent resistance to drying shrinkage cracks.

Water based, safe, non-toxic, clean up easily with soap and water.

Trowels on easily, speeds mesh embedment, reduces applicator arm fatigue, increases job-site productivity.

Can be used as a leveling coat minimizes multiple applications when leveling up 1/8" thick per pass, 1/4" total

MIXING

In a clean container, mix the contents of the Alpha Genie pail with a low speed drill and paddle mixer until thoroughly blended. Divide pail content in two equal parts, mix 30 lbs. (13.6 kg) of Alpha Genie with 30 lbs. (13.6 kg) of Portland cement in small increments; thoroughly mix to a homogeneous consistency after each additional increment. Let the mixture sit for 5 minutes then stir to a creamy consistency. Up to 32 oz. (0.9 L) of water per half pail, may be added to achieve the desired workability.

- Do not use a container which has contained or been cleaned with a petroleum-based product.
- Do not overmix. Excessive stirring will cause faster setting of the Alpha Genie and significantly reduce working time.
- For best results, mix at 400-500 rpm, using a heavy-duty drill with a jiffler type paddle (Goldblatt Jiffler Mixer No. 15311 H7 or similar).
- Additives are not permitted.
- Close container when not in use.
- Clean tools with soap and water immediately after use. Dried material can only be removed mechanically.

TEST RESULTS

TEST	METHOD	CRITERIA	RESULT
VOC	ASTM D3960 (based in part on EPA method 24)	Report Value	< 50 g/L less water and exempt solvents
Accelerated Weathering	ASTM G 23	No deleterious effects after 2000 hours.	Pass
Accelerated Weathering	ASTM G 53	No deleterious effects after 7500 hours.	Pass
Water Resistance of Coating in 100% R.H.	ASTM D 2247	No deleterious effects after 14 days exposure	Pass
Water Vapor Transmission	ASTM E96 Method B	Report Value	Alpha Genie Coat with Flexguard 4 and Senerflex Finish: 15.1 Perms
Surface Burning Characteristics	ASTM E 84	Report Value	Flame Spread < 25 Smoke Development < 450 (Class A)
Tensile Bond	ASTM C297, E2134	15 psi minimum	> 15 psi

SURFACE PREPARATION

Substrates must be clean, dry, sound and free of loose material, releasing agents, paint, efflorescence, contaminants and bond inhibiting coatings. Use Surface Stabilizer WB by Master Builders Solutions for chalky or previously painted concrete and masonry surfaces prior to application of base coat.

- Concrete: allow to cure a minimum of 28 days prior to application of base coat.
- Unit Masonry: allow to cure prior to application of base coat.
- Stucco: allow to cure a minimum of 6 days prior to application of base coat.

APPLICATION AS LEVEL COAT

- To level unit masonry so that joints are not visible, apply Alpha Genie up to 1/8" (3.2 mm) over the block face, filling joints and covering block surface with a smooth coating. If block joints are not struck flush, installed a second coat, repeat process over first application after it has dried. Maximum total thickness should not exceed 1/4" (6.4mm)
- To level concrete substrates, grind down irregularities higher than (1/4") 6.4mm. Fill voids of up to 1/8" (3.2mm) with Alpha Genie. Then apply a 1/8" (3.2mm) leveling coat of Alpha Genie over the concrete substrate.

Note: Allow to cure for at least 24 hours before applying finish.

APPLICATION AS BASE COAT FOR REINFORCING MESH EMBEDMENT

Trowel apply base coat to the surface of the insulation board or approved substrate. Fully embed Senergy reinforcing mesh in to wet base coat, ensure no mesh color is visible. Lap reinforcing mesh a minimum 2 1/2" (64 mm) at edges and 8" (203 mm) around corners. Ensure reinforcing mesh is free of wrinkles. Allow reinforced base coat to dry hard (normally 8 to 10 hours) prior to application of Senergy Primer or Finish.

DRY TIME

As a leveler allow to cure 24 hours prior to finish application. As base coat for mesh embedment allow 8-10 hours. Alpha Genie achieves full strength in approximately 28 days. Protect from rain and temperatures of less than 40°F (4°C) for a minimum of 24 hours. Higher humidity and/or cooler temperatures may require longer protection.

LIMITATIONS

1. Not for use directly over wood-based substrates or metal.
2. Do not exceed applied thickness of 1/4" (6.4mm).
3. Efflorescence of Portland cement-based substrates such as concrete, masonry units and stucco may cause staining or discoloration on the surface of applied base coat.

4. When temperatures less than 40°F (4°C) prevail, provide supplementary heat during installation and drying period for at least 24 hours after installation and until dry.
5. Do not apply in ambient temperature above 100°F (38°C) or surface temperature above 120°F (49°C)
6. Do not apply Master Builders Solutions materials to frozen surfaces.
7. Not for use on damp surfaces, below-grade applications or on surfaces subject to water immersion.

SHIPPING & STORAGE

- Protect materials during transportation to avoid physical damage. Store in a cool, dry place protected from freezing, extreme heat and direct sun. Store at no less than 40°F (4°C).
- Do not stack pallets.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting senergy-mbcc.sika.com/en, e-mailing your request to mbsbscst@mbcc-group.com or calling +1 (800) 433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

TECHNICAL SUPPORT

Consult Master Builders Solutions Technical Services Department at +1 (800) 589-1336 for specific recommendations concerning all other applications. Consult the Wall Systems website at senergy-mbcc.sika.com/en, for additional information about products and systems and for updated literature.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

For the most current version of this literature, please visit our website at senergy-mbcc.sika.com/en.