

Senerflash™ / Flashing Primer

Uses

1. Used as an air barrier accessory to connect different air barrier materials or assemblies together to make the air barrier continuous.
2. Flashing at sills, approved sheathing joints, rough openings, and terminations.
3. As an expansion joint seal.

FLASHING PRIMER is to be used under SENERFLASH membrane on these acceptable substrates and other surfaces:

1. Wood framing (Note: Verify adhesion before applying to wood that has been treated in any way.)
2. ASTM C1177 sheathings, e.g. e²XP™, GlasRoc®, Securock™ and DensGlass™
3. Water-resistant core gypsum sheathing (ASTM C79/ASTM C1396)
4. Cement-board (ASTM C1325 Type A Exterior)
5. Masonry
6. Exposure 1 or exterior plywood sheathing
7. Exposure 1 OSB
8. Steel framing
9. SENERFLASH (itself)
10. SENERSHIELD-R
11. SENERSHIELD-VB

Technical Information

Consult the BASF Wall Systems Technical Services Department for specific recommendations concerning all other applications. Consult the Senergy website, www.senergy.basf.com, for additional information about products and systems and for updated literature.

Preparation

1. Acceptable substrate shall be dry, clean, sound and free of releasing agents, paint, contaminants, residue or other coatings. Verify substrate is flat, free of fins or anything that would hinder the adhesion of the membrane.
2. Unsatisfactory conditions shall be reported to the general contractor and corrected before application of the Senergy materials.
3. Wrap openings in accordance with *Senergy Wall System's Air/Water-Resistive/ Vapor Barrier Application Guidelines* technical bulletin.

Advantages

Self-sealing, self-healing; maintains a seal when penetrated by fasteners

SENERSHIELD-R and BASF Base Coats can be applied to polyester face of SENERFLASH; use as part of adhesively applied EIFS

Description

SENERFLASH is a patented, 30-mil thick, self-adhering, self-sealing, self-healing composite membrane of polyester fabric and rubberized asphalt. SENERFLASH is supplied in rolls, on release paper, for easy application.

FLASHING PRIMER is a single component, water-based primer specially formulated for use with SENERFLASH™ and SENERWRAP.

Color

FLASHING PRIMER is pinkish during application, drying to semi-transparent.

Packaging

SENERFLASH 4:
10.2 cm x 30.5 m (4" x 100') rolls
9 rolls per carton

SENERFLASH 9:
22.9 cm x 30.5 m (9" x 100') rolls
4 rolls per carton

FLASHING PRIMER:
19-liter (5-gallon) pails
3.8-liter (1-gallon) bottles
4 bottles per carton

Coverage

SENERFLASH 4:
274.3 Lin m (900 Lin ft) per carton
SENERFLASH 9:
121.9 Lin m (400 Lin ft) per carton

FLASHING PRIMER:
Coverage rates will vary depending on the texture, porosity of the existing substrate. Approximate coverages:

ASTM C1177 exterior sheathing:
11.6–13.9 m² (125–150 ft²)
per 3.8 L (1-gallon) bottle,
58–69.5 m² (625–750 ft²)
per 19 L (5-gallon) pail

Gypsum sheathing:
14.9–17.7 m² (160–190 ft²)
per 3.8 L (1-gallon) bottle,
74.5–88.5 m² (800–950 ft²)
per 19 L (5-gallon) pail

Exterior plywood sheathing & cement-board (ASTM C1325):
16.7–20.4 m² (180–220 ft²)
per 3.8 L (1-gallon) bottle,
83.5–102 m² (900–1100 ft²)
per 19 L (5-gallon) pail

Senerflash™ / Flashing Primer

Application

FLASHING PRIMER/SENERFLASH application

1. Shake or stir FLASHING PRIMER until uniform consistency, approximately one minute.
2. Apply FLASHING PRIMER with a brush or roller to achieve an average coverage rate of 11.6–20.4 m² per 3.8 liter (125–220 ft² per gallon). Coverage rate will vary according to substrate. .
3. Apply FLASHING PRIMER evenly. Surfaces shall be uniformly coated, free from voids, pinholes or blisters.
4. Protect primed surface from dust to prevent adhesion problems.
5. A second coat of primer may be required for porous surfaces or if the initial adhesion is not optimal.
6. Apply SENERFLASH as soon as the FLASHING PRIMER is dry and tacky. Additional FLASHING PRIMER will be required over areas that are no longer tacky.
7. Cut SENERFLASH roll to desired length with a utility knife or scissors.
8. Remove usable size of the release film immediately before application and center the SENERFLASH over the area to be sealed.
9. Using a wallpaper roller, extension-handled countertop roller or weighted hand roller, firmly roll the SENERFLASH to the area being sealed. As the SENERFLASH is applied, pull more of the release film from the SENERFLASH, exposing the adhesive surface, pressing down on the SENERFLASH with a roller and keeping the SENERFLASH smooth.
10. If blisters occur, they can be slit with a utility knife and the membrane pressed flat with a roller. Ensure no voids or holes are present. Repair as necessary.
11. Installed materials should be checked for delamination of edges before final system application. Repair as necessary.
12. Overlap SENERFLASH a minimum of 50 mm (2") horizontally and 150 mm (6") vertically.
13. Clean tools as soon as possible with warm water and soap. Dried FLASHING PRIMER is difficult to remove from tools.
14. Install exterior cladding system in accordance with manufacturer's current specifications and details.

Limitations

1. Store material in a well ventilated, clean, dry area where temperatures will not exceed 32°C (90°F).
2. Do not apply Senergy materials in ambient temperatures below 4°C (40°F). Provide supplementary heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 4°C (40°F) are anticipated.
3. When applying the membrane in cooler temperatures, store material for 24 hours inside at room temperature for better adhesion. Adhesion properties of SENERFLASH during application in cooler temperatures may also be improved by the use of a heat gun.
4. Do not store rolls on end.
5. Protect from rain and physical damage until installation of exterior cladding system.
6. Do not apply the material to any surfaces not listed as an acceptable substrate/surface, including silicone caulk or other solvent base products.
7. Do not expose material to sunlight for over 30 days.
8. Apply SENERFLASH only to dry surfaces. Allow surfaces to dry a minimum of 24 hours after precipitation.
9. Do not apply Senergy materials to frozen surfaces.
10. Shelf life is one year when stored in original container or factory sealed packaging as directed.

TECHNICAL DATA

Property	ASTM Test Method	Result
Peel Adhesion (To primed Steel)	D1000	10 lbs/in. width
Elongation at Break	D882 Method A	(Modified) > 100%
Low Temperature Pliability	D146 modified	No cracking -26°C (-15°F)

Note

BASF Wall Systems is an operating unit of BASF Corporation (herein referred to as "BASF Wall Systems")

Disclaimer

This information and all further technical advice are based on BASF Wall Systems' present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF Wall Systems disclaims any and all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF WALL SYSTEMS SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF Wall Systems reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.



Scan this code to find the most current Senergy literature

BASF Wall Systems

3550 St. Johns Bluff Road South
Jacksonville, FL 32224-2614
Phone 800 • 221 • 9255
Fax 904 • 996 • 6300
www.senergy.basf.com

©2012 BASF Corporation
Printed in U.S.A. 06/12