



We create chemistry

Senerlastic™ Coating

100% acrylic-based smooth elastomeric coating

Product Bulletin

COLORS

Available in standard and custom colors.

PACKAGING

55 lbs per 5-gallon pail (24.9 kg per 19-liter pail).

COVERAGE

Coverage may vary depending on the texture, porosity and color of the existing substrate. Two coats are recommended to obtain the maximum elastomeric properties and for substrates with a moderate texture. Total wet film thickness is 32 mils (16 mils DFT) at 50 ft²/gal (4.6m²/L) or 250 ft²/pail (23m²/pail).

TECHNICAL INFORMATION

Consult our Technical Services department for specific recommendations concerning all other applications. Consult the BASF Wall Systems website, www.wallsystems.basf.com, for additional information about products and systems and for updated literature.

DESCRIPTION

Factory-mixed, 100% acrylic-based smooth elastomeric coating that provides excellent flexibility and weatherability.

USES

SENERLASTIC COATING is intended for use as a coating on exterior wall surfaces such as concrete, stucco, unit masonry, or compatible EIFS finish coat.

SURFACE PREPARATION

Substrates must be clean, dry, sound and free of loose material, releasing agents, paint, efflorescence, contaminants and other coatings. Cracks or voids must be filled with MasterProtect® FL 746/ FL 748 or appropriate, compatible material to provide a solid substrate prior to application of SENERLASTIC COATING. Ensure patching material is dry prior to application of SENERLASTIC COATING.

Concrete:

1. Allow concrete to cure a minimum of 28 days prior to application of SENERLASTIC COATING.
2. Remove all projections and form lines.

3. When needed, apply BASF TINTED PRIMER to cured concrete with a sprayer, 3/8" (10mm) nap roller or good-quality latex paint brush at a rate of approximately 150–250 ft² per gallon (3.6–6.1 m² per 3.8 liter). BASF TINTED PRIMER shall be dry to the touch before proceeding to the SENERLASTIC COATING application.

Unit masonry:

1. Allow unit masonry to cure prior to application of SENERLASTIC COATING
2. Remove all loose mortar and projections.
3. When needed, apply a leveling coat of BASF Base Coat to provide a smooth surface prior to application of SENERLASTIC COATING.

Stucco:

1. Allow stucco to cure a minimum of 6 days prior to application of SENERLASTIC COATING.
2. When needed, apply BASF STUCCO PRIME to cured stucco with a sprayer, 3/8" (10 mm) nap roller or good-quality latex paint brush at a rate of approximately 150-250 ft² per gallon (3.6-6.1 m² per liter). BASF STUCCO PRIME shall be dry to the touch before proceeding to the SENERLASTIC COATING application.

Features	Benefits
Over 300% elongation	Bridges cracks and enhances performance
Low temperature flexibility	Enhances crack resistance
Excellent weatherproof coating	Protects against wind-driven rain
Durable	Extends the life of the building
Breathable	Resists blistering and peeling
UV resistant	Retains color
Water based	Safe, non-toxic, clean up easily with soap and water

MIXING

1. Mix the contents of the SENERLASTIC COATING pail with a low speed drill and paddle mixer until thoroughly blended.
2. A small amount of clean, potable water may be added to adjust workability, but is generally unnecessary since a thick consistency is desired.
3. Additives are not permitted.
4. Close container when not in use.
5. Clean tools with soap and water immediately after use.

APPLICATION

1. SENERLASTIC COATING is meant to be applied as a two coat system, achieving a total wet thickness of 32 mils.
2. Apply SENERLASTIC COATING with a brush, 1" (25 mm) nap roller, or spray. Maintain a wet edge at all times during application.
3. Work SENERLASTIC COATING to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area.
4. When rolled, ensure roller is completely saturated and keep it loaded. Do not roll dry.

LIMITATIONS

1. Protect BASF materials during transportation and installation to avoid physical damage.

2. Store BASF materials in a cool, dry place protected from freezing. Store at no less than. Protect from extreme heat and direct sunlight. Shelf life is two years when unopened and stored as directed.
3. Do not apply BASF materials in ambient temperature below 40°F (4°C). Provide supplementary heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 40°F (4°C) prevail.
4. Protect work from precipitation until dry.
5. Do not apply BASF materials to frozen surfaces

VOC Content

60–73 g/l, or 0.50–0.61 lbs/gal less water and exempt solvents

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets (SDS) and product label information for this product prior to use. The SDS can be obtained by visiting www.wallsystems.basf.com or e-mailing a request to bwscustomerservice@basf.com. Use only as directed.

For medical emergencies only, call ChemTrec® 1-800-424-9300.

TECHNICAL DATA

Property	Result	Test Method
Weight per gallon, lbs	11.5 ± 0.2	
Solids by weight, %	56 ± 2.0	
Solids by volume, %	44 ± 2.0	
Viscosity, KU	108 ± 4	
VOC content, lbs/gal (g/L)	0.32–0.42 (38–50)	ASTM D3960
Ultimate elongation, %	344	ASTM D412
Elongation recovery, %		ASTM D412
After 10 minutes	96.9	
After 24 hours	98.4	
Ultimate tensile strength, psi (MPa)	220 (1.5)	ASTM D412
Crack bridging, mils (mm)		PR EN1062-7
-77°F (-60°C)	12 (0.3)	
32°F (0°C)	19.5 (0.5)	
73°F (23°C)	27.5 (0.7)	
Flexibility, in (mm) mandrel, at -30°F (-34°C)	1/8 (3)	ASTM D552
Pull-off strength adhesion, psi (MPa)	210 (1.4)	ASTM D4541
Wind-driven rain	Passes	TT-C-555B

Property	Result	Test Method
Water-vapor permeance, perms	10	ASTM D1653
Carbon-dioxide diffusion		PR EN1062-6
R (equivalent air layer thickness), ft (m)	263 (80)	
Sc (equivalent concrete thickness), in (cm)	8 (20)	
Accelerated weathering, 5,000 hrs	Passes	ASTM G23, Type D
Visual color change, 5,000 hrs	Passes	ASTM D1729
Chalking, 5,000 hrs	Passes	ASTM D4214
Freeze/thaw resistance, 60 cycles	Passes	ASTM C67
Salt spray resistance, 300 hrs	Passes	ASTM B117
Dirt pick-up, after 6 months exposure	Dc = 94.33 (100 = Best Performance)	ASTM D3719
Mildew resistance	No growth	ASTM D3273/3274

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

THEORETICAL FILM THICKNESS

Coverage rate ft ² /gal(m ² /L)	Wet mils (Microns)	Dry mils (Microns)
50 (4.6)	32 (813)	16 (406)
80 (7.4)	20 (508)	10 (254)
100 (9.3)	16 (406)	8 (203)

Actual DFT to achieve the stated performance properties is 16 mils (406 microns).

Senerlastic Coating

WARRANTY

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Product Bulletin, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. **BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS.** The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. In the absence of an extended warranty issued by BASF, any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. **BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.**

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.