

Senerlastic Finish

100% acrylic-based, textured elastomeric finish

Product Bulletin

DESCRIPTION

Factory-mixed, 100% acrylic-based, textured elastomeric finish that provides excellent flexibility, weatherability, and maximum resistance to mildew growth.

COLORS & TEXTURES

Available in Senergy's 128 standard colors and custom colors, in Senergy's, CLASSIC, FINE, SAHARA and TEXTURE Finishes.

PACKAGING

31.7 kg per 19-liter pail
(70 lbs per 5-gallon pail)

COVERAGE

Coverage rates may vary depending on the coating texture porosity of substrate and application techniques.

Approximate coverages:

Classic Finish:

13.0m² (140 ft²) per pail

Fine Finish:

13.0m² (140 ft²) per pail

Sahara Finish:

11.1 m² (120 ft²) per pail

Texture Finish:

Coverage varies depending upon application

USES

SENERLASTIC FINISH is primarily intended for use as a coating over non-textured exterior wall surfaces such as cured stucco, concrete and unit masonry. SENERLASTIC FINISH can also be used to provide an aesthetically pleasing surface color and texture for poured concrete or unit masonry, SENERGY Cement-Board Stucco System, conventional stucco, SENERGY STUCCO Wall Systems, all Senergy Surfacing Systems and certain insulating concrete forms.

MIXING

1. Thoroughly mix SENERLASTIC FINISH to a uniform workable consistency.
2. A small amount of clean, potable water may be added to adjust workability.

3. Additives are not permitted.
4. Close container when not in use.
5. Clean tools with soap and water immediately after use.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.senergy.basf.com. Use only as directed.

TECHNICAL SUPPORT

Consult our Technical Services Department for specific recommendations concerning all other applications. Consult the web site, www.senergy.basf.com for additional information and for updated literature.

Advantages

Bridges hairline cracks smaller than 1/32"; protects

100% acrylic polymer-based chemistry; provides long-term durability and weather resistance

Integral color; reduces maintenance and recoating

Weather resistant; repels water and resists wind-driven rain

Seals existing, non-moving hairline cracks; protects

Breathable; does not blister, peel or flake

Abrasion resistant; durable

Factory mixed; ready to use, no additives to mix

Water based; safe, non-toxic, clean up easily with soap and water

High UV resistance; resist fading

SURFACE PREPARATION

Substrates must be clean, dry, sound and free of loose material, releasing agents, paint, efflorescence, contaminants and other coatings. Fill cracks or voids with an appropriate, compatible material to provide a solid substrate prior to application of SENERLASTIC FINISH. Ensure patching material is dry prior to application of SENERLASTIC FINISH.

Note: The primers are desired to improve color uniformity and have a negligible effect on adhesion.

Concrete:

1. Allow concrete to cure prior to application of SENERLASTIC FINISH.
2. Remove all projections, form lines and release agents.
3. When needed, apply SENERGY TINTED PRIMER to cured concrete with a sprayer, 10 mm (3/8") nap roller or good-quality latex paint brush at a rate of approximately 3.6–6.1 m² per liter (150–250 ft² per gallon). TINTED PRIMER shall be dry to the touch before proceeding to the SENERLASTIC FINISH application.

Unit masonry:

1. Allow unit masonry to cure prior to application of SENERLASTIC FINISH.
2. Remove all loose mortar and projections.
3. When needed, apply a leveling coat of STANDARD BASE COAT or ALPHA GENIE BASE COAT to provide a smooth surface and minimize the likelihood of mortar joint read through prior to application of SENERLASTIC FINISH.

Stucco:

1. Allow stucco to cure before applying SENERLASTIC FINISH.
2. When needed, apply SENERGY STUCCO PRIME to cured stucco with a sprayer, 10 mm (3/8") nap roller or good-quality latex paint brush at a rate of approximately 3.6–6.1 m² per liter (150–250 ft² per gallon). STUCCO PRIME shall be dry to the touch before proceeding to the SENERLASTIC FINISH application.

APPLICATION

1. Apply SENERLASTIC FINISH directly to the SENERGY Base Coat/ Reinforcing Mesh with clean stainless steel trowel.
Note: In order to minimize the possibility of Base Coat or SENERGY STUCCOBASE read-through with color #330 Maxi-White in CLASSIC, we recommend the use of Senergy Tinted Primer or Stucco Prime. Base Coat read-through with CLASSIC Finish in Maxi-White is very applicator sensitive.
2. Apply and level SENERLASTIC FINISH during the same operation to minimum obtainable thickness consistent with uniform coverage.
3. Maintain a wet edge on SENERLASTIC FINISH by applying and texturing continually over the wall surface.
4. Work SENERLASTIC FINISH to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area.
5. Float SENERLASTIC FINISH to achieve final texture.

LIMITATIONS

1. Cracks greater than 0.8 mm (1/32") must be pre-sealed.
2. Must be stored, applied and protected until dry at 4°C (40°F) or more.
3. Appearance of CLASSIC might vary if floated by different mechanics.

4. Protect Senergy materials during transportation and installation to avoid physical damage.
5. Store SENERGY materials in a cool, dry place protected from freezing. Store at no less than 4°C (40°F). Protect from extreme heat and direct sunlight. Shelf life is two years when unopened and stored as directed.
6. Do not apply SENERGY materials in ambient temperatures below 4°C (40°F). Provide supplementary heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 4°C (40°F) prevail.
7. Do not apply Senergy materials to frozen surfaces.
8. **Select Finish Coat color with a light reflective value (LRV) of 20% or higher. The use of dark colors (LRV less than 20%) is not recommended with walls that incorporate expanded polystyrene (EPS). EPS has a sustained service temperature limitation of approximately 160°F (71°C).**

WARRANTY

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Product Bulletin, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. In the absence of an extended warranty issued by BASF, any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

For the most current version of this literature, please visit our website at www.senergy.basf.com.

BASF Corporation - Wall Systems | 3550 St Johns Bluff Rd South Jacksonville, Florida 32224 P: 800.221.9255 F: 904.996.6300 www.senergy.basf.com

© 2016 BASF Corporation rev 160428