

Loxon® Acrylic Conditioner

LX03W0100 Guide Coat White, LX03V0100 Clear



**SHERWIN
WILLIAMS®**

CHARACTERISTICS

Loxon Acrylic Conditioner is a 100% acrylic emulsion conditioner that will penetrate and seal interior and exterior surfaces and bond light chalk to the surface. With excellent alkali and efflorescence resistance, this sealer allows new concrete, stucco, and other cementitious surfaces to be coated prior to a 30-day cure, and will adhere to new or existing concrete with a pH of 6 to 13.

For use on these surfaces:

Concrete, Concrete Block, Brick, Stucco, Fiber Cement Siding, Plaster, Mortar, EIFS Exterior Wall Cladding

Color: Guide Coat White & Clear

Coverage:

Coverage sq.ft. per gallon 200-300

Do not build a surface glaze.

Drying Schedule 77° F @ 50% RH:

Drying and recoat times are temperature, humidity and film thickness dependent.

Touch: 30 minutes

Tack free: 1 hour

Recoat: 3 hours

Tinting with CCE only:

Requires ColorCast Ecotoner colorant for tinting. If desired, up to 1 oz per gallon of ColorCast Ecotoner colorant can be used to approximate the topcoat color. Check color before use.

Clear LX03V0100

V.O.C. (less exempt solvents):

less than 50 grams per litre; 0.42 lbs.per gallon
As per 40 CFR 59.406

Volume Solids: 15 ± 2%

Weight Solids: 17 ± 2%

Weight per Gallon: 8.43 lb

Flash Point: N/A

Vehicle Type: Proprietary

Shelf Life: 36 months,unopened

Guide Coat White LX03W0100

V.O.C. (less exempt solvents):

less than 50 grams per litre; 0.42 lbs.per gallon
As per 40 CFR 59.406

Volume Solids: 17 ± 2%

Weight Solids: 24 ± 2%

Weight per Gallon: 8.92 lb

Flash Point: N/A

Vehicle Type: Proprietary Acrylic

Shelf Life: 36 months,unopened

WVP Perms (US): 27.55 grains/(hr ft² in Hg)

COMPLIANCE

As of 09/23/2021, Complies with:

OTC	Yes
OTC Phase II	Yes
S.C.A.Q.M.D.	Yes
CARB	Yes
CARB SCM 2007	Yes
CARB SCM 2020	Yes
Canada	Yes
LEED® v4 & v4.1 Emissions	Yes
LEED® v4 & v4.1 V.O.C.	Yes
EPD-NSF® Certified	Yes
MIR-Manufacturer Inventory	No
MPI®	N.A.

APPLICATION

Temperature:
minimum 50°F

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compatible with the existing environmental and application conditions.

Reducer: No reduction necessary

Airless Spray:

Pressure 700-1000 p.s.i.

Tip .015-.019 inch

Brush Use a nylon/polyester or foam brush.

Roller Cover Use a 3/8 to 3/4 inch nap synthetic cover.

If the surface requires a full bodied prime/block filler coat rather than a thin penetrating sealer, use Loxon Concrete & Masonry Primer or Loxon Acrylic Block Surfer.

Apply at temperatures above 50°F. When the air temperature is at 50°F, substrates may be colder; prior to painting, check to be sure the air, surface, and material temperature are above 50°F and at least 5°F above the dew point.

Do not apply if the surface temperature is below 50°F, when rain is expected within 3 hours, or when the relative humidity is 90% or more.

Do not paint in direct sun or on a hot surface.

Do not reduce.

APPLICATION TIPS

Do not build a surface glaze.

Do not apply to a damp surface.

Do not apply over heavy chalk.

For maximum resistance to efflorescence, you must topcoat with one of the Loxon Masonry Finishes.

On exterior applications, Loxon Acrylic Conditioner must be topcoated within 7 days or the surface may need to be re-cleaned.

RECOMMENDED SYSTEMS

Masonry, Concrete, Stucco, Block,
1 coat Loxon Acrylic Conditioner
2 coats Appropriate topcoat

Fiber Cement Siding, EIFS:
1 coat Loxon Acrylic Conditioner
2 coats Appropriate topcoat

Previously Painted:
1 coat Loxon Acrylic Conditioner
2 coats Appropriate topcoat

Recommended Architectural Topcoats:

Loxon Masonry Coatings
ConFlex Masonry Coatings
A-100 Exterior Latex
Duration Exterior & Duration Home Interior
Emerald Exterior & Interior
SuperPaint Exterior & Interior
ProMar Interior

Loxon®

Acrylic Conditioner

SURFACE PREPARATION

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

New and Previously Painted:

Remove all surface contamination (peeling paint, heavy chalk, efflorescence, laitance, concrete dust, etc.) by washing or pressure washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

Masonry, Concrete, Stucco:

All new surfaces must cure for at least 7 days. Remove all form release and curing agents. Pressure clean to remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, peeling and defective coatings, chalks, etc. Allow the surface to dry before proceeding. Repair cracks, voids, and other holes with an appropriate patching compound or sealant.

Concrete and mortar must be cured at least 7 days at 75°F. Moisture content must be 15% or lower. On tilt-up and poured-in-place concrete, commercial detergents and sandblasting may be necessary to remove sealers, release compounds, and to provide an anchor pattern. Fill bugholes, air pockets and other voids with an elastomeric patch or sealant.

Plaster

Must be cured, usually 30 days, and hard. If painting cannot wait, allow the surface to dry 7 days (within a pH range of 6 to 13) and prime with Loxon Acrylic Conditioner. **Do not build a surface glaze.** If the surface requires a full bodied prime coat rather than a thin penetrating sealer, use Loxon Concrete & Masonry Primer. Soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with water and allow to dry before painting.

Brick

Must be free of dirt, loose and excess mortar, and foreign material. All brick should be allowed to weather for at least one year followed by wire brushing to remove efflorescence. Treat the bare brick with one coat of Loxon Acrylic Conditioner.

SURFACE PREPARATION

Mildew:

Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised.

Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach-water solution.

CAUTIONS

For interior or exterior use.

Protect from freezing.

Not for use on floors

Before using, carefully read **CAUTIONS** on label.

CRYSTALLINE SILICA: Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE.** Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**

HOTW	09/23/2021	LX03W0100	17 00
HOTW	09/23/2021	LX03V0100	13 00
FRC, SP			

CLEANUP INFORMATION

Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with a compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.