

PRODUCT DATA SHEET

Sika® FerroGard®-903

Penetrating, corrosion inhibiting, impregnation coating for hardened concrete

PRODUCT DESCRIPTION

engineering structures

Sika® FerroGard®-903 is a corrosion inhibiting impregnation coating for hardened concrete surfaces. It is designed to penetrate the surface and then to diffuse in vapor or liquid form to the steel reinforcing bars embedded in the concrete. Sika® FerroGard®-903 forms a protective layer on the steel surface which inhibits corrosion caused by the presence of chlorides as well as by carbonation of concrete.

How it works

Sika® FerroGard®-903 is a combination of amino alcohols, and organic and inorganic inhibitors that protects both the anodic and cathodic parts of the corrosion cell. This dual action effect dramatically delays the initiation of corrosion and greatly reduces the overall corrosion activity. Sika® FerroGard®-903 protects the embedded steel by depositing a physical barrier in the form of a protective layer on the surface of the steel reinforcement. This barrier inhibits corrosion of the steel.

USES

Sika® FerroGard®-903 is recommended for all steel-reinforced, prestressed, precast, post tensioned or marine concrete. Use of Sika® FerroGard®-903:

- Steel-reinforced concrete, bridges and highways exposed to corrosive environments (deicing salts, weathering)
- Building facades and balconies
- Steel-reinforced concrete in or near a marine environment
- Parking garages
- Piers, piles, and concrete dock structures
- As part of Sika's system approach for buildings and civil

Product Data Sheet

Sika® FerroGard®-903

October 2018, Version 01.01

020303040010000001

CHARACTERISTICS / ADVANTAGES

Sika® FerroGard®-903 offers owners, specifiers, port authorities, DOTs, and engineers, a new technology in corrosion inhibition that can easily be applied to the surface of existing concrete to extend the service life of any reinforced concrete structure.

- Protects against the harmful effects of corrosion by penetrating the surface of even the most dense concrete and diffusing to the steel to inhibit corrosion.
- Enhances the durability of reinforced concrete.
- Does not require concrete removal.
- Environmentally sound.
- Does not contain calcium nitrite.
- Easily applied by either spray or roller to all existing reinforced concrete.
- Can be applied to reinforced concrete that already exhibits corrosion.
- Adds additional benefits when used prior to protective coatings in concrete restoration systems.
- Water based for easy handling and application.
- Not a vapor barrier; allows vapor diffusion.
- FerroGard has been proven effective in both laboratory (ASTM G109/Cracked Beams) and field analysis.
- ANSI/NSF Standard 61 potable water approved

PRODUCT INFORMATION

Packaging	5 gallon pails with spout, 55 gallon drums.
Appearance / Color	Pale Yellow
Shelf Life	18 months minimum in original, unopened container
Storage Conditions	Store at 40–95 °F (4–35 °C). Protect from freezing. If frozen, discard.
Density	1.13 (9.4 lbs./gal.)
pH-Value	11 (±1)
Viscosity	15 cps

TECHNICAL INFORMATION

Penetration Depth

Key Criteria	Performance Level	Test Method/Institute
Corrosion Inhibition	Sika® FerroGard®-903 corrosion inhibitors delay the onset of corrosion and reduce the rate of corrosion by 65% versus control specimen after 1 year.	1
Penetration Rate in hardened concrete	Sika® FerroGard®-903 penetrates independently of orientation (horizontal, vertical, overhead) at a rate of 1/10 to 4/5 inches (2.5 to 20 mm) per day, depending on the density of the concrete.	2
Depth of Penetration	Sika® FerroGard®-903 penetrates up to 3 inches (76 mm) in 28 days.	2
Protective layer on steel	Sika® FerroGard®-903 forms a protective layer on the reinforcing steel of high integrity measured at as much as 100 Å in thickness	3
Displacement of chlorides from steel surface	Sika® FerroGard®-903 forms a continuous film on the reinforcing steel and displaces chloride ions from the steel surface.	3
Corrosion Rate Field Monitoring	Reduction of corrosion rates in excess of 65%.	4

Test Method/Institute:

¹ Cracked Concrete Beam Test (adapted from ASTM G109)

² Secondary Neutron Mass Spectroscopy (SNMS) / Institute for Radiochemistry, Karlsruhe (Germany), Prof. Dr. J. Goschnick.

³ X-ray Photon Spectroscopy (XPS) and Secondary Ion Mass Spectroscopy (SIMS) / Brundle and Associates, San Jose, CA and University Heidelberg (Germany), Prof. M. Grunze.

⁴ Performance of Corrosion Inhibitors in Practice, Graeme Jones, C-Probe Technologies Ltd., 2000

APPLICATION INFORMATION

Coverage

For normal concrete, application is 200 ft.²/gal. each coat. A minimum of two coats is always recommended. For dense concrete, application may exceed 300 ft.²/gal. Therefore, more than two coats may be required to achieve the **total application rate: 100 ft.²/gal.**

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Before applying Sika® FerroGard®-903 be sure the

surface is clean and sound. Remove all dirt, dust, oil, grease, efflorescence or existing coatings from concrete surface by steam cleaning, waterblasting or slightly sandblasting. Allow concrete surface to dry prior to application of Sika® FerroGard®-903. The dryer the surface the better the penetration and effectiveness.

APPLICATION

Sika® FerroGard®-903 is applied by roller, brush or spray on concrete surfaces. When spraying, use a conventional airless spray system or hand-pressure equipment. **A minimum of two coats is always recommended.** Dense substrates may require more coats. Waiting time between coats of Sika® FerroGard®-903 is at least 1 hour. Allow a minimum of one day to allow Sika FerroGard 903 to dry and penetrate.

When Sika® FerroGard®-903 is used prior to the application of a repair mortar, concrete overlay, protective coating, Sikafloor system or any other application, care must be taken to remove any residue remaining on the surface from the application of Sika® FerroGard®-903. Clean the substrate in such a manner (i.e. push the water in one direction away and off from the surface to be overcoated) to completely remove any residue. Horizontal surfaces require pressure washing (2,000 psi minimum) to remove the residue. Vertical surfaces may be rinsed with water or pressure washed. The use of Sika Armatec 110 EpoCem as a bonding agent prior to the application of repair mortars or concrete overlays is suggested. Drying times depend on environmental conditions, absorbency of the substrate and maximum recommended moisture content for the subsequently applied system.

LIMITATIONS

- Minimum ambient and substrate temperatures 35 °F.
- Do not apply when temperature is expected to fall below 35 °F within 12 hours.
- If the applied surfaces will be submerged after the application of Sika® FerroGard®-903, a waterproofing coating must be applied prior to submersion.
- Substrate should be as dry as possible prior to the application.
- Protect glass, wood, brick, galvanized steel, copper and exposed aluminum during the application.
- Maximum chloride content of concrete structures intended to be treated with Sika® FerroGard®-903 is 6 lbs./y³ (measured at the level of the reinforcing steel). For levels up to 10 lbs./y³, consult technical service.

BASIS OF PRODUCT DATA

Sika Corporation
Results may differ based upon statistical variations depending on mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.
usa.sika.com

Sika Mexicana S.A. de C.V.
Calle de la Industria 685
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
Sika® FerroGard®-903
October 2018, Version 01.01
020303040010000001

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

