



Sika[®] Level-325

CEMENTITIOUS, SELF LEVELING UNDERLAYMENT

- High strength underlayment
- For use on cement and gypsum based substrates
- Designed for fast leveling in interior and exterior areas
- Can be installed above 1/8" up to 1.5" and up to 3" with aggregate
- No MVER (Moisture Vapor Emission Rate) limits on well prepared concrete

Available in
55 lb. Bag



BUILDING TRUST



Sika® Level-325

CEMENTITIOUS, SELF LEVELING UNDERLAYMENT

WHERE TO USE

- Interior and Exterior applications
- Concrete, cement, and gypsum substrates
- OSB board and plywood
- Ceramic tiles and terrazzo
- Old, water-resistant adhesive residues

FEATURES AND BENEFITS

- Very low emission
- Suitable on underfloor heating systems
- Low shrinkage
- Pumpable and Self-Leveling
- Acceptable for castor wheel loadings above 1/8"

TYPICAL DATA (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

Color	Concrete Gray
Application Thickness	1/8" up to 1.5" (3 mm up to 38 mm) Can be extended with aggregate to 3" (76 mm)
Density (ASTM C185)	133 lbs/cu.ft.
Working Time	Approx. 30 minutes
Set Time	Initial - 70 - 90 min Final - 80 - 110 min
Ready for Foot Traffic	Approx. 4 hours
Ready for Covering	For tile or stone: approx. 4 hours For floor covering products: After 24 hours up to 1/4" thick After 48 hours up to 3/8" thick.
Flexural Strength (ASTM C348)	1,500 psi (10 MPa) at 28 days
Compressive Strength (ASTM C109)	5,300 psi (37 MPa) at 28 days
Tensile Strength (ASTM C1583)	500 psi (3.4 MPa) after 3 days at 1/8"
VOC (EPA METHOD 24)	0 g/l

Sika® Classification Table

Strength					
Flow					
Depth					
Floor Cover Time					

NOTE: Always refer to current PDS and SDS for detailed performance specifications prior to use.



FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: www.sikasecure.com

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 201-933-8800
Fax: 201-933-6225



BUILDING TRUST

