

PRODUCT DATA SHEET

SikaFiber® Enduro® Prime

Macro-Synthetic Fiber

PRODUCT DESCRIPTION

SikaFiber® Enduro® Prime is macro synthetic reinforcing fiber. SikaFiber® Enduro® Prime is 100% virgin copolymer fiber designed to provide a uniform three dimensional reinforcement system in the concrete mix. Specifically engineered and manufactured in an ISO 9001 certified manufacturing facility. SikaFiber® Enduro® Prime previously Enduro Prime.

USES

SikaFiber® Enduro® Prime can be successfully used as a safe and simple alternative to wire mesh and rebar. Due to its mechanical properties SikaFiber® Enduro® Prime is recommended for use in following applications:

- Industrial slab-on-ground
- Pavements
- Bridge decks
- Overlays
- Composite metal deck
- Precast

CHARACTERISTICS / ADVANTAGES

- Widely DOT approved - contact regional sale manager for state-by-state acceptance.
- Efficient and cost-effective, three-dimensional reinforcement alternative to steel wire mesh, rebar, and steel fibers.
- Sustainable reinforcement solution by reducing embodied carbon through the replacement of convention steel reinforcement with synthetic structural fibers.
- Reduction in construction time. No cutting, placing, tying, and chairing required.
- Safer and easier to use than wire mesh and rebar.
- Superior increase durability, ductility, and flexural toughness of concrete.
- Reduces plastic shrinkage, settlement, and drying shrinkage cracking in concrete.
- Improves impact and shatter resistance of concrete.
- Geometrically engineered to resist matrix pullout.
- Will not corrode, non-magnetic and highly alkali resistant.
- Pumpable safe reinforcement.

APPROVALS / STANDARDS

- Complies with the ICC (International Code Council) AC308 and carries the ICC ES Evaluation Report ESR-4282
- SikaFiber® Enduro® Prime is UL/ULC certified and approved for usage in all D700, D800 and D900 series decks as an alternate to welded wire fabric.
- Complies with ASTM C 1116/C1116M Type III Fiber Reinforced Concrete and ASTM D7508/D7508M.
- Complies with European Standard EN 14889-2: 2006 Fibres for Concrete Part 2: Class II

PRODUCT INFORMATION

Packaging	SikaFiber® Enduro® Prime are packed and placed various sizes of "toss-in" degradable bags. The bags are packed into cartons and palletized.
Shelf Life	If stored in dry conditions shelf life is 5 years.
Storage Conditions	SikaFiber® Enduro® Prime should be stored in a cool dry warehouse. Protect product from the rain and direct sunlight.
Appearance / Color	<ul style="list-style-type: none"> ▪ Fiber Type: monofilament macro synthetic fiber ▪ Fiber Network: 37,000 fibers/lb (81,500 fibers/kg)
Dimensions	Length: Available in 2.17 or 2.4" (55 or 60 mm) lengths Equivalent Diameter: 0.02" (0.56mm). Aspect Ratio: 98 (at 55 mm length) or 107 (at 60 mm length)
Density	0.91
Melting Point	324 °F (162 °C)

TECHNICAL INFORMATION

Resistance to Alkalinity	Excellent
---------------------------------	-----------

APPLICATION INFORMATION

Recommended Dosage	The dosage of the SikaFiber® Enduro® Prime will vary according to the type of application and the performance requirements of the project. Standard recommended dosage rate of SikaFiber® Enduro® Prime is between 3–7 lbs/cu. yd. (1.8–4.15 kg/m³) of concrete. Dosages outside the recommended dosage range can be used to meet project specific requirements. If this is the case please contact your Sika representative for technical support.
---------------------------	---

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY

• FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.**

SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
SikaFiber® Enduro® Prime
July 2023, Version 02.01
02140802100000114

SikaFiberEnduroPrime-en-US-(07-2023)-2-1.pdf

