SikaProof[®] P-1201 System

Fully Bonded, Post-Applied FPO Sheet Membrane Waterproofing System for Basement and Below Ground Structures

scription	SikaProof [®] P-1201 System is a fully bonded composite sheet membrane waterproofing system for reinforced concrete structures. It consists of an embossed flexible polyolefin (FPO) based membrane SikaProof [®] P-1200 and an 2 component PU adhesive SikaProof [®] Adhesive.		
nere To Use	Damp-proofing, waterproofing and concrete protection for basements and other below ground structure against ground water ingress. Suitable for use on:		
	Vertical reinforced concrete walls horizontal reinforced concrete slabs, protrusions, decks and podiums		
	 Extensions and reconstruction works 		
	 Prefabricated structures 		
Advantages	 Fully bonded onto the hardened concrete structure 		
	 No lateral water underflow between the reinforced concrete structure and the membrane system 		
	 Highly flexible with crack-bridging abilities 		
	 High watertightness tested according various standards 		
	 Easy to install with fully adhered joints (no welding required) 		
	 Cold applied (no heat or open flames required) 		
	 Temporary resistant to weathering and UV light during construction 		
	Resistant to aging		
	 Resistant to aggressive mediums and gases in natural ground water and soil 		
	 Can be combined with other approved Sika[®] Waterproofing / Joint Sealing Systems 		
pical Data			
Coverage	SikaProof® P-1200 membrane: 1 Roll = 215 sf		
	SikaProof® Adhesive-01 Component A&B mixed:		
		substrate - minimum 1 kg/10 sf	
	Average Consumption for Vertical applications on smooth, even		
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf d	epending on roughness of substrate	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data		
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200	epending on roughness of substrate	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B	epending on roughness of substrate ASTM Test Method	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200	epending on roughness of substrate	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B	epending on roughness of substrate ASTM Test Method	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf do Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.)	ASTM D3767	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.) Tensile Strength (membrane): 2,000 psi min.	ASTM D3767 ASTM D412	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.) Tensile Strength (membrane): 2,000 psi min. Elongation (membrane): 500% min.	ASTM D3767 ASTM D412 ASTM D412	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.) Tensile Strength (membrane): 2,000 psi min. Elongation (membrane): 500% min. Peel Adhesion to Concrete: 30 lbs/in	ASTM D3767 ASTM D412 ASTM D412 ASTM D903	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.) Tensile Strength (membrane): 2,000 psi min. Elongation (membrane): 500% min. Peel Adhesion to Concrete: 30 lbs/in Lap Peel Adhesion: 18 lbs/in	ASTM D3767 ASTM D412 ASTM D412 ASTM D903 ASTM D1876	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.) Tensile Strength (membrane): 2,000 psi min. Elongation (membrane): 500% min. Peel Adhesion: 18 lbs/in Water vapor transmission: 3.45 X 10-9 g/Pa-S-m2 (0.06 perms)	ASTM D3767 ASTM D412 ASTM D412 ASTM D903 ASTM D1876 ASTM E96	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.) Tensile Strength (membrane): 2,000 psi min. Elongation (membrane): 500% min. Peel Adhesion to Concrete: 30 lbs/in Lap Peel Adhesion: 18 lbs/in Water vapor transmission: 3.45 X 10-9 g/Pa·S·m2 (0.06 perms) Low temperature: Pass (no cracking @ -29°)	ASTM D3767 ASTM D412 ASTM D412 ASTM D412 ASTM D903 ASTM D1876 ASTM E96 ASTM D1970	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.) Tensile Strength (membrane): 2,000 psi min. Elongation (membrane): 500% min. Peel Adhesion: 18 lbs/in Water vapor transmission: 3.45 X 10-9 g/Pa·S·m2 (0.06 perms) Low temperature: Pass (no cracking @ -29°) Puncture resistance: 190 lbs	ASTM D3767 ASTM D412 ASTM D412 ASTM D412 ASTM D412 ASTM D903 ASTM D1876 ASTM D1876 ASTM D1970 ASTM E154	
	Average Consumption for Vertical applications on smooth, even a Average Consumption for Horizontal applications = >1 kg/10 sf de Product Data System Components: SikaProof® P-1200 SikaProof® Adhesive-01, Component A,B Thickness (membrane): 1.2 mm (0.047 in.) Tensile Strength (membrane): 2,000 psi min. Elongation (membrane): 500% min. Peel Adhesion: 18 lbs/in Water vapor transmission: 3.45 X 10-9 g/Pa·S·m2 (0.06 perms) Low temperature: Pass (no cracking @ -29°) Puncture resistance: 190 lbs Crack Cycling: Pass (no cracking at -15°F)	ASTM D3767 ASTM D412 ASTM D412 ASTM D412 ASTM D903 ASTM D1876 ASTM E96 ASTM D1970 ASTM E154 ASTM C836	

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT HTTP://USA.SIKA.COM/ OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800-933-7452. NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTION FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.



Packaging	SikaProof® P-1200 Roll = 1.0 x 20.0 m		
	SikaProof [®] Adhesive-01 Component A = Pail 25 kg		
	SikaProof [®] Adhesive-01 Component B, Hardener = Pail 5 kg		
Cure Mechanism	See current Product Data Sheet for SikaProof® Adhesive-01		
How to Use			
Surface Preparation	SUBSTRATE QUALITY		
	The reinforced concrete structure must be:		
	 Hardened and of sufficient compressive strength, minimum 3,600 psi 		
	 Minimal pull off strength, 200 psi 		
	 Dry, sound, clean and free of any contamination (e.g. dust, oil, grease, release agent, etc.) 		
	 Free from surface defects (e.g. blowholes, voids, honeycombing, cracks, protrusions, etc.) 		
	SUBSTRATE PREPARATION		
	The concrete or other suitable cementitious substrate must meet the defined substrate quality. If the substrate does not fulfil the requirements, the surface must be pretreated prior to the application, in orde to prevent any subsequent damage to the membrane sheets.		
	For more detailed information and guidance please refer to the current Method Statement for the SikaProof® P-1201 System system.		
Mixing	See current Product Data Sheet for SikaProof® Adhesive-01		
Application	The installation method of the SikaProof [®] P-1201 System is state of the art for adhered membrane systems, by simple and easy bonding of the membrane sheets into a previously applied adhesive bed. Th following work steps need to be taken in consideration:		
	 Substrate preparation and cleaning, to fulfill the required substrate quality. 		
	 Mix the 2c SikaProof[®] Adhesive-01 according the Product Data Sheet. 		
	 Apply the adhesive with a notched trowel onto the entire substrate (no primer required). 		
	 Prepare and apply the SikaProof[®] P-1200 membrane accordingly. 		
	 Roll in and press the membrane properly into the fresh applied adhesive. 		
	 Make sure enough adhesive is left (minimum 1 mm). Overlap and adhere the membrane sheets with the adhesive minimum 90 mm. 		
	 Treat all details and connections according to the Method Statement. 		





PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT HTTP://USA.SIKA.COM/ OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800-933-7452. NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTION FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE. Ambient Air Temperature: Minimum +40°F / maximum +120°F

Substrate Temperature: Surface to be bonded: Minimum +40°F, if below appropriate measures must be taken.

Substrate Moisture Content: Dry, ≤ 4% moisture content, no rising moisture

SikaProof[®] P-1201 System must only be installed by Sika trained and approved contractors. The SikaProof[®] P-1201 System Method Statement, with its technical guidelines and information, must be complied with.

• Do not install SikaProof® P-1201 System during continuous or prolonged rain, snowfall or sand storm.

• The substrate quality and condition must be fulfilled or appropriate treatment or measures must be taken.

• An adequate concrete quality (mix design and workmanship) is required to achieve optimum full bond of the SikaProof® P-1201 System membrane system to the harden structural concrete.

• Additional Sika® Joint Sealing Solutions must be used for connections, around penetrations and in construction and expansion joints.

• Protect the membrane system immediately after installation is completed to prevent any damage.

• SikaProof[®] P-1201 System is not permanently UV and weather resistant. It must always be protected from exposure within a defined time period depending on the climate conditions and region. Therefore it must not be installed on structures permanently exposed to UV light and weathering. For further information please refer to the current Method Statement of SikaProof[®] P-1201 System.

SikaProof® P-1201 System is not designed for use on structures with direct impact of traffic.

 For more detailed information and guidance please refer to the current Method Statement for the SikaProof® P-1201 System.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY • FOR PROFESSIONAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at http://usa.sika.com/ or by calling 800-933-7452.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sika Greenstreak Sales Office 3400 Tree Court Industrial Blvd. St. Louis, MO 63122 Tel: (636) 225-9400 Fax: (636) 225-2049 usa.sika.com Sika Corporation 201 Polito Avenue Lyndhurst, NJ 07071 Phone: (201) 933-8800 Fax: (201) 933-6225 usa.sika.com Sika Canada Inc. 601, Delmar Avenue Pointe-Claire, QC H9R 4A9 Phone: (514) 697-2610 Fax: (514) 697-3087 can.sika.com

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT HTTP://USA.SIKA.COM/ OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800-933-7452. NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTION FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.



