



# SikaQuick® 800

## RAPID SETTING REPAIR MORTAR

- Rapid hardening as defined by ASTM C 928
- Not gypsum-based
- Freeze / thaw resistant
- Easy to mix and apply - labor-saving

Available in 50 lb pail



**BUILDING TRUST**



# SikaQuick® 800

## RAPID SETTING REPAIR MORTAR

### PRODUCT DESCRIPTION

SikaQuick®-800 is one-part, cementitious, rapid hardening, early strength gain, cementitious, patching mortar for concrete.

### BENEFITS

- Rapid hardening as defined by ASTM C 928
- Epoxy coatings can be applied as early as 6 hours at 73° F (23° C)
- Freeze / thaw resistant
- Easy to mix and apply - labor-saving
- Not gypsum-based
- High early strength
- Fast setting
- Open to foot traffic in 2 hours / Open to vehicular traffic in 3 hours at 73° (23° C)

### APPLICATIONS

- On grade, above grade and below grade concrete conditions
- Highway overlays and repairs
- Structural repair material for concrete roadways, parking structures, bridges, dams, ramps, runways, warehouse floor & loading docks
- Full depth patching repairs (may require multiple lifts)



### PRODUCT INFORMATION

<b>Appearance / Color</b>	Gray powder
<b>Shelf Life</b>	12 months from date of manufacture if stored properly in original, unopened and undamaged, sealed packaging
<b>Storage Conditions</b>	Store dry at 40° - 95° F (4° - 35° C). Protect from moisture. If damp, discard material.

### COMPRESSIVE STRENGTH (ASTM C 109) 50 % R.H.

Age	73° F ( 23° C)
3 hours	3,500 psi (24.1 MPa)
1 day	6,000 psi (41.4 MPa)
7 days	7,000 psi (48.3 MPa)
28 days	8,500 psi (58.6 MPa)

**Note:** Advice on specific applications is available from the Technical Service Department of Sika Construction Products Division.

## FOR MORE INFORMATION:

Contact Sika: Phone 800 933 7452 Website: [usa.sika.com](http://usa.sika.com)

### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 201-933-8800  
Fax: 201-933-6225

**BUILDING TRUST**

