

## PRODUCT DATA SHEET

# SikaQuick® Patch

RAPID CURING, TWO COMPONENT, REPAIR MORTAR FOR HORIZONTAL REPAIRS

### PRODUCT DESCRIPTION

SikaQuick® Patch is a two-part, pre-proportioned cementitious mix which when applied, produces a rapid curing repair patch. It has been specifically formulated and packaged to be an easy, mix-in-the-bag, highstrength product. SikaQuick® Patch is based upon Sika's proven cement technology.

### USES

- Bonds to concrete
- Horizontal spall repairs
- Concrete basement floors
- Concrete driveways
- Concrete patios
- Concrete side walks and much more

### CHARACTERISTICS / ADVANTAGES

- Packaged in a lightweight, easy to handle pouch
- Simple application - just roll, mix and pour
- Increased bond strength, Polymer Modified
- Sets in 10 to 20 minutes (varies with temperature)
- Interior or exterior use
- Improved repair durability
- Can drive over in 1 hour
- No primer needed, just a damp surface, SSD (no standing water)

### PRODUCT INFORMATION

<b>Packaging</b>	29 fl. oz. (858 ml) pouch; 6 in a case
<b>Shelf Life</b>	12 months in original, unopened containers
<b>Storage Conditions</b>	Store in cool, frost-free conditions with temperatures between 50 and 90°F (10–32 °C). Condition product to between 65 and 77 °F (18–25 °C)

### TECHNICAL INFORMATION

<b>Compressive Strength</b>	1 hour	1,472 psi (10.1 MPa)	(ASTM C-109) Tested at: 73 °F (23 °C) 50 % R.H.
	1 day	1,922 psi (13.2 MPa)	
	7 days	4,027 psi (27.7 MPa)	
	28 days	5,537 psi (38.1 MPa)	

## APPLICATION INFORMATION

<b>Coverage</b>	Unit yields approx.: 1 ft <sup>2</sup> at a half in. (12.7 mm) depth
<b>Layer Thickness</b>	Minimum Application Depth: 1/8" Maximum Application Depth: 3"
<b>Pot Life</b>	1–5 minutes
<b>Set Time</b>	5–10 minutes
<b>Final Set Time</b>	10–20 minutes
<b>Waiting / Recoat Times</b>	30 minutes to 1 hour to drive on / 7 days to paint (depending on humidity/temperature)

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

Remove all deteriorated concrete, dirt, oil, grease, and all bond-inhibiting materials from surface. Preparation work should be done by high pressure water blast, scabber, or other appropriate mechanical means to obtain an aggregate-fractured surface with a minimum CSP 3 surface profile or greater. Ensure there are no curing compounds or other contaminants remaining on the substrate before application. Substrate must be damp (SSD) before application. No standing water.

### MIXING

Have scissors or a knife next to the hole or spall and ready to cut a corner of the bag after mixing is completed. Roll the pouch, starting at the compartment containing Component A, working towards the 'burst seal' in the direction of the arrows shown on the label. Apply pressure to the rolled section to rupture the seal and allow Component A (Liquid) to flow into the compartment containing Component B (Powder). Mix thoroughly by then rolling out the pouch and rubbing the bag along any 90 degree surface (no sharp edges). Mix for 20 seconds by forcing the material to travel inside the bag, from one end to the other (using a "shoe shining" technique). Make sure there is no powder left behind, the clear packaging allows the user to see when the product is properly mixed.

### APPLICATION

After mixing, cut one of the bag's corners and pour mixed material in the hole/spall. The material will settle into the hole/repair. Smooth it with a wide putty knife to get a smooth/flat finish.

## LIMITATIONS

- Do not apply on frozen or frost covered substrates.
- Low temperatures or high humidity will extend curing time.
- Low temperatures will cause a thicker consistency.
- Do not allow stored product to freeze.
- Do not apply on vertical surfaces.

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## OTHER RESTRICTIONS

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



### Product Data Sheet

SikaQuick® Patch  
February 2019, Version 01.01  
020302040030000308

SikaQuickPatch-en-US-(02-2019)-1-1.pdf